2

**PM-1 3½"x4" PHOTOGRAPHIC MICROCOPY TARGET
NBS 1010a ANSI/ISO #2 EQUIVALENT**

PRECISIONSM RESOLUTION TARGETS

PIONEERS IN METHYLENE BLUE TESTING SINCE 1974

18000 COUNTY ROAD 6, BURNINGWELL, WY 82401 USA
TEL: 912 426 7887 FAX: 912 426 7887 TLE: 9124267887

Table 4.3 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{(\pi b)}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	b/c						
	1.05	1.10	1.20	1.40	1.50	1.60	1.80
0.01	0.125	0.101	0.076	0.041	0.032	0.025	0.016
0.05	0.572	0.464	0.348	0.188	0.147	0.117	0.076
0.10	1.030	0.834	0.620	0.337	0.263	0.210	0.137
0.20	1.727	1.392	1.019	0.559	0.438	0.349	0.229
1	3.953	3.111	2.175	1.222	0.966	0.775	0.514
5	6.070	4.588	3.109	1.767	1.402	1.128	0.752
10	6.811	5.064	3.419	1.947	1.547	1.247	0.834
20	7.369	5.410	3.682	2.106	1.677	1.356	0.913
100	7.994	5.789	4.406	2.620	2.130	1.760	1.240

Table 4.4 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{(\pi b)}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	b/c						
	1.05	1.10	1.20	1.40	1.50	1.60	1.80
0.01	0.050	0.032	0.020	0.009	0.006	0.005	0.003
0.05	0.237	0.155	0.097	0.044	0.033	0.025	0.015
0.10	0.438	0.289	0.182	0.084	0.063	0.048	0.030
0.20	0.763	0.512	0.322	0.151	0.113	0.088	0.055
1	2.003	1.397	0.860	0.423	0.322	0.251	0.160
5	3.350	2.353	1.406	0.711	0.544	0.426	0.273
10	3.867	2.699	1.593	0.807	0.617	0.483	0.309
20	4.341	3.006	1.753	0.886	0.676	0.528	0.336
100	5.038	3.436	1.931	0.952	0.717	0.552	0.340

Table 4.5 Normalised Stress Intensity Factors, $K_1/\bar{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{\pi b}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	b/c						
	1.05	1.10	1.20	1.40	1.50	1.60	1.80
0.01	0.023	0.013	0.007	0.003	0.002	0.0016	0.0004
0.05	0.114	0.066	0.036	0.017	0.013	0.010	0.006
0.10	0.216	0.126	0.070	0.033	0.025	0.019	0.012
0.20	0.389	0.233	0.130	0.062	0.047	0.036	0.023
1	1.158	0.744	0.421	0.204	0.155	0.121	0.077
5	2.160	1.431	0.794	0.388	0.295	0.230	0.147
10	2.534	1.679	0.920	0.449	0.341	0.265	0.168
20	2.886	1.902	1.028	0.498	0.376	0.291	0.183
100	3.556	2.297	1.186	0.546	0.401	0.302	0.177

Table 4.6 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	0.0530	0.0676	0.0766	0.0849	0.0859
0.05	0.165	0.234	0.278	0.317	0.329
0.10	0.175	0.303	0.389	0.464	0.497
0.20	0.0514	0.271	0.430	0.565	0.645
1	-1.126	-0.624	-0.187	0.210	0.537
5	-2.657	-2.017	-1.379	-0.759	-0.201
10	-3.007	-2.345	-1.637	-0.911	-0.280
20	-3.172	-2.454	-2.135	-1.471	-0.791
100	-3.400	-2.938	-2.346	-1.518	-0.926

Table 4.7 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	-0.0055	0.0105	0.0218	0.0292	0.0335
0.05	-0.0438	0.0219	0.0822	0.119	0.141
0.10	-0.122	0.0101	0.109	0.179	0.224
0.20	-0.308	-0.0865	0.0865	0.216	0.306
1	-1.325	-0.869	-0.462	-0.100	0.206
5	-2.325	-1.846	-1.352	-0.841	-0.344
10	-2.529	-2.092	-1.617	-1.087	-0.545
20	-2.635	-2.244	-1.806	-1.275	-0.676
100	-2.720	-2.398	-2.054	-1.584	-0.775

Table 4.8 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	-0.0464	-0.0286	-0.0153	-0.0058	0.0006
0.05	-0.206	-0.128	-0.0688	-0.0251	0.0047
0.10	-0.370	-0.235	-0.130	-0.0503	0.0052
0.20	-0.615	-0.404	-0.233	-0.100	-0.0026
1	-1.302	-0.958	-0.642	-0.361	-0.122
5	-1.645	-1.337	-1.005	-0.658	-0.328
10	-1.693	-1.415	-1.108	-0.754	-0.391
20	-1.694	-1.462	-1.192	-0.850	-0.447
100	-1.693	-1.507	-1.319	-1.068	-0.615

Table 4.9 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	-0.0506	-0.0331	-0.0203	-0.0111	-0.0048
0.05	-0.211	-0.140	-0.0870	-0.0471	-0.0190
0.10	-0.354	-0.241	-0.153	-0.0804	-0.0347
0.20	-0.537	-0.373	-0.247	-0.141	-0.0607
1	-0.935	-0.715	-0.507	-0.320	-0.159
5	-1.111	-0.911	-0.692	-0.470	-0.264
10	-1.131	-0.954	-0.747	-0.524	-0.305
20	-1.134	-0.981	-0.794	-0.578	-0.348
100	-1.126	-1.008	-0.881	-0.722	-0.488

Table 4.10 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	-0.0479	-0.0313	-0.0193	-0.0106	-0.0046
0.05	-0.187	-0.126	-0.0789	-0.0434	-0.0179
0.10	-0.299	-0.207	-0.133	-0.0752	-0.0318
0.20	-0.430	-0.308	-0.205	-0.121	-0.0536
1	-0.704	-0.541	-0.389	-0.250	-0.129
5	-0.870	-0.708	-0.536	-0.365	-0.211
10	-0.910	-0.753	-0.584	-0.408	-0.217
20	-0.913	-0.782	-0.625	-0.451	-0.284
100	-0.910	-0.816	-0.698	-0.556	-0.382

Table 4.11 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	0.0735	0.0869	0.0926	0.0938	0.0890
0.05	0.356	0.414	0.438	0.442	0.419
0.10	0.678	0.786	0.829	0.837	0.797
0.20	1.233	1.441	1.526	1.548	1.491
1	3.709	4.704	5.227	5.591	5.803
5	6.974	10.13	12.31	14.23	16.24
10	8.973	13.77	17.56	20.77	23.69
20	13.05	20.99	28.93	35.94	39.26
100	30.58	43.39	64.83	90.71	116.7

Table 4.12 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	0.0722	0.0848	0.0894	0.0891	0.0833
0.05	0.344	0.404	0.425	0.424	0.399
0.10	0.648	0.762	0.805	0.806	0.763
0.20	1.156	1.377	1.465	1.481	1.423
1	3.097	4.046	4.561	4.901	5.119
5	4.754	7.337	9.183	10.79	12.47
10	5.258	8.720	11.59	14.21	16.74
20	5.971	10.35	14.71	19.07	22.91
100	11.51	18.68	29.66	45.19	65.49

Table 4.13 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	0.0679	0.0762	0.0761	0.0719	0.0646
0.05	0.310	0.355	0.359	0.343	0.312
0.10	0.560	0.654	0.670	0.649	0.599
0.20	0.937	1.132	1.188	1.178	1.113
1	1.994	2.814	3.259	3.549	3.738
5	2.360	4.398	5.915	7.196	8.367
10	2.319	4.934	7.204	9.296	11.10
20	2.324	5.440	8.645	12.05	15.02
100	3.350	7.409	13.34	22.27	36.54

Table 4.14 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	0.0560	0.0582	0.0588	0.0518	0.0459
0.05	0.238	0.259	0.255	0.242	0.219
0.10	0.402	0.456	0.462	0.449	0.417
0.20	0.616	0.747	0.787	0.791	0.760
1	1.128	1.179	2.073	2.289	2.441
5	1.244	2.911	4.087	5.007	5.860
10	1.041	3.277	5.053	6.547	8.018
20	0.703	3.460	5.970	8.249	10.63
100	-0.615	2.793	7.288	12.31	19.45

Table 4.15 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{[\pi(b+d)]}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	$b/2c$				
	0.20	0.35	0.50	0.65	0.80
0.01	0.0462	0.0475	0.0454	0.0423	0.0379
0.05	0.185	0.202	0.201	0.193	0.178
0.10	0.299	0.344	0.355	0.349	0.333
0.20	0.438	0.542	0.584	0.598	0.594
1	0.793	1.262	1.525	1.694	1.834
5	0.934	2.399	3.373	4.047	4.610
10	0.729	2.830	4.392	5.545	6.543
20	0.318	3.059	5.383	7.239	8.941
100	-1.370	2.184	6.871	11.30	15.06

Table 4.16 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling:
 $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{\pi d}$; $c/a=1/3$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-0.0070	-0.0424	-0.0280	-0.0070
0.05	-0.0585	-0.1979	-0.1220	-0.0202
0.10	-0.1641	-0.3880	-0.2311	-0.0355
0.20	-0.4115	-0.7427	-0.4259	-0.0623
1.00	-1.8041	-2.5252	-1.3491	-0.1851
5.00	-3.3930	-4.5695	-2.4473	-0.3167
10.0	-3.7679	-5.0452	-2.7508	-0.3236
20.0	-3.9756	-5.3049	-2.9435	-0.3709
100.	-4.0922	-5.5406	-3.0964	-0.4591

Table 4.17 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling:
 $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{\pi d}$; $c/a=1/2$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-0.0479	-0.0588	-0.0255	-0.0065
0.05	-0.2257	-0.2693	-0.1135	-0.0242
0.10	-0.4198	-0.5019	-0.2139	-0.0477
0.20	-0.7408	-0.8887	-0.3886	-0.0806
1.00	-1.9416	-2.3637	-1.1562	-0.2482
5.00	-2.8944	-3.5300	-1.9829	-0.4595
10.0	-3.0767	-3.7371	-2.1974	-0.5254
20.0	-3.1730	-3.8370	-2.3296	-0.5790
100.	-3.2548	-3.8955	-2.4573	-0.7568

Table 4.18 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling:
 $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}$; $c/a=1$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-0.0690	-0.0436	-0.0216	-0.0089
0.05	-0.3017	-0.1943	-0.0952	-0.0372
0.10	-0.5281	-0.3514	-0.1756	-0.0689
0.20	-0.8438	-0.5918	-0.3067	-0.1227
1.00	-1.5681	-1.2991	-0.7764	-0.3404
5.00	-1.8152	-1.6768	-1.1298	-0.5448
10.0	-1.8395	-1.7325	-1.1989	-0.5939
20.0	-1.8494	-1.7578	-1.2370	-0.6278
100.	-1.8523	-1.7496	-1.2703	-0.7149

Table 4.19 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling:
 $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}$; $c/a=2$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-0.0521	-0.0316	-0.0210	-0.0128
0.05	-0.2154	-0.1332	-0.0888	-0.0530
0.10	-0.3591	-0.2293	-0.1554	-0.0942
0.20	-0.5392	-0.3598	-0.2503	-0.1559
1.00	-0.8843	-0.6598	-0.4639	-0.3341
5.00	-0.9921	-0.7846	-0.6147	-0.4389
10.0	-1.0041	-0.8004	-0.6341	-0.4593
20.0	-1.0090	-0.8044	-0.6444	-0.4740
100.	-1.0069	-0.7688	-0.6535	-0.5231

Table 4.20 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling:
 $\bar{K} = E\alpha_1\Delta T\sqrt{\pi d}$; $c/a=3$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-0.0426	-0.0277	-0.0209	-0.0150
0.05	-0.1675	-0.1116	-0.0846	-0.0603
0.10	-0.2689	-0.1844	-0.1418	-0.1026
0.20	-0.3867	-0.2752	-0.2157	-0.1596
1.00	-0.5996	-0.4597	-0.3753	-0.2922
5.00	-0.6800	-0.5377	-0.4439	-0.3520
10.0	-0.6958	-0.5540	-0.4546	-0.3591
20.0	-0.7107	-0.5701	-0.4601	-0.3584
100.	-0.7878	-0.6568	-0.4652	-0.3164

Table 4.21 Normalised Stress Intensity Factors, $K_1/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling:
 $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}$; $c/a=1/3$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	0.1435	0.1574	0.1257	0.0674
0.05	0.5888	0.6868	0.6072	0.3219
0.10	0.9674	1.1894	1.1646	0.6109
0.20	1.4460	1.8916	2.1526	1.1110
1.00	2.8267	3.8817	6.7586	3.3819
5.00	4.4841	5.3768	12.039	6.3617
10.0	4.9697	5.6653	13.324	7.2984
20.0	5.2886	5.8290	14.064	7.9479
100.	5.9558	6.6480	14.723	9.3339

Table 4.22 Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling:
 $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}$; $c/a=1/2$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	0.1471	0.1581	0.1176	0.0674
0.05	0.6430	0.7230	0.5626	0.3228
0.10	1.1139	1.3047	1.0673	0.6135
0.20	1.7674	2.1966	1.9365	1.1188
1.00	3.5671	4.8696	5.6219	3.4270
5.00	4.9164	6.3450	9.3011	6.3390
10.0	5.1914	6.4641	10.152	7.1723
20.0	5.3261	6.4398	10.642	7.6859
100.	5.3564	6.1323	11.081	8.1218

Table 4.23 Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling:
 $K = E_1 \alpha_1 \Delta T \sqrt{\pi d}$; $c/a=1$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	0.1393	0.1323	0.1020	0.0743
0.05	0.6337	0.6126	0.4854	0.3531
0.10	1.1406	1.1225	0.8962	0.6657
0.20	1.9056	1.9240	1.5821	1.1960
1.00	4.2048	4.5525	4.1626	3.3857
5.00	5.6779	6.4192	6.3995	5.5838
10.0	5.9466	6.7723	6.8879	6.1105
20.0	6.0831	6.9391	7.1645	6.4251
100.	6.1138	6.8148	7.4077	6.8060

Table 4.24 Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling:
 $K = E_1 \alpha_1 \Delta T \sqrt{\pi d}$; $c/a=2$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	0.0977	0.0959	0.0885	0.0785
0.05	0.4466	0.4371	0.4070	0.3643
0.10	0.7990	0.7916	0.7428	0.6703
0.20	1.3476	1.3470	1.2736	1.1608
1.00	3.4510	3.3796	3.2011	2.9471
5.00	5.6037	5.3120	5.0034	4.5571
10.0	6.1268	5.7607	5.4301	4.9377
20.0	6.4284	5.9992	5.6785	5.1734
100.	6.6502	5.9794	5.9008	5.5412

Table 4.25 Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling:
 $K = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}$; $c/a=3$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	0.0796	0.0785	0.0758	0.0724
0.05	0.3497	0.3510	0.3419	0.3294
0.10	0.6200	0.6285	0.6150	0.5959
0.20	1.0468	1.0642	1.0429	1.0146
1.00	2.8737	2.8071	2.7133	2.5891
5.00	5.0951	4.7552	4.4874	4.1633
10.0	5.7105	5.2796	4.9385	4.5399
20.0	6.1184	5.6289	5.2059	4.7422
100.	6.8681	6.3339	5.4471	4.7342

Table 4.26 Characteristic Phase Angles, ψ' (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/2})$; $c/a=1/3$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-8.136	-13.46	-33.52	-78.49
0.05	-8.168	-12.45	-32.09	-78.05
0.10	-8.558	-11.38	-30.48	-77.58
0.20	-9.958	-9.724	-27.73	-76.80
1.00	-21.56	-5.306	-16.81	-74.35
5.00	-34.02	-5.356	-9.433	-73.59
10.0	-36.50	-6.433	-9.634	-73.26
20.0	-37.76	-7.615	-10.78	-72.14
100.	-36.94	-10.32	-12.36	-60.49

Table 4.27 Characteristic Phase Angles, ψ' (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/2})$; $c/a=1/2$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-9.584	-15.89	-35.92	-76.30
0.05	-10.23	-15.28	-34.96	-75.86
0.10	-11.06	-14.60	-33.89	-75.38
0.20	-12.70	-13.50	-32.08	-74.56
1.00	-21.06	-9.606	-25.34	-71.61
5.00	-29.42	-7.559	-22.26	-69.92
10.0	-31.37	-7.629	-22.86	-69.94
20.0	-32.58	-7.818	-23.67	-70.34
100.	-33.95	-7.266	-24.89	-74.13

Table 4.28 Characteristic Phase Angles, ψ' (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/2})$; $c/a=1$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-20.23	-34.51	-51.22	-68.81
0.05	-21.43	-34.66	-50.95	-68.24
0.10	-22.67	-34.81	-50.63	-67.60
0.20	-24.51	-35.02	-50.05	-66.47
1.00	-29.34	-35.32	-47.40	-61.58
5.00	-31.27	-35.00	-44.64	-56.86
10.0	-31.48	-34.80	-44.01	-55.96
20.0	-31.57	-34.51	-43.66	-55.75
100.	-31.46	-32.57	-43.41	-58.56

Table 4.29 Characteristic Phase Angles, ψ' (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/2})$; $c/a=2$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-47.20	-54.87	-60.36	-66.83
0.05	-49.54	-56.14	-61.06	-66.94
0.10	-51.77	-57.40	-61.74	-66.99
0.20	-54.73	-59.15	-62.64	-66.94
1.00	-59.21	-62.34	-63.63	-64.91
5.00	-57.20	-61.28	-61.71	-60.84
10.0	-56.29	-60.59	-61.01	-59.77
20.0	-55.69	-60.00	-60.58	-59.33
100.	-54.98	-57.82	-60.21	-60.81

Table 4.30 Characteristic Phase Angles, ψ' (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/2})$; $c/a=3$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β (degrees)			
	30	60	90	120
0.01	-58.14	-59.69	-62.35	-66.86
0.05	-61.28	-61.88	-64.01	-67.88
0.10	-64.12	-63.97	-65.60	-68.83
0.20	-67.63	-66.75	-67.71	-70.03
1.00	-71.74	-71.41	-71.02	-70.74
5.00	-68.73	-70.52	-69.66	-67.25
10.0	-67.68	-70.04	-69.00	-65.79
20.0	-67.17	-69.96	-68.58	-65.00
100.	-68.07	-72.09	-68.21	-62.15

Table 5.1 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for Axisymmetric Problem I Subject to Thermal Cooling: $\bar{K}=E_1\alpha_1\Delta T\sqrt{\pi c}$; $\alpha_2/\alpha_1=10$; $b/c<1$.

μ_2/μ_1	b/c				
	0.50	0.70	0.90	0.95	0.99
0.01	0.0730	0.0754	0.0662	0.0588	0.0405
0.05	0.350	0.366	0.327	0.294	0.208
0.20	1.222	1.318	1.248	1.159	0.888
0.50	2.440	2.759	2.845	2.766	2.347
1.00	3.640	4.323	4.903	5.009	5.021
2.00	4.888	6.155	7.813	8.468	9.687
5.00	6.207	8.368	12.29	14.32	19.94
20.0	7.151	10.10	16.80	22.54	39.33
100.	8.168	11.46	20.05	26.67	51.43

Table 5.2 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for Axisymmetric Problem I Subject to Thermal Cooling: $\bar{K}=E_1\alpha_1\Delta T\sqrt{\pi c}$; $\alpha_2/\alpha_1=10$; $b/c>1$.

μ_2/μ_1	b/c				
	1.01	1.05	1.10	1.20	1.50
0.01	0.105	0.0850	0.0632	0.0397	0.0153
0.05	0.449	0.386	0.287	0.178	0.0645
0.20	1.571	1.200	0.900	0.567	0.209
0.50	2.869	2.130	1.608	1.030	0.392
1.00	4.008	2.912	2.195	1.423	0.559
2.00	5.266	3.699	2.777	1.813	0.725
5.00	6.934	4.646	3.426	2.243	0.897
20.0	9.337	5.698	4.120	2.652	1.067
100.	10.64	6.244	4.459	2.852	1.149

Table 5.3 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for Axisymmetric Problem II at Point A Subject to Thermal Cooling: $\bar{K}=E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β				
	15°	30°	45°	60°	75°
0.01	-0.0138	-0.0094	-0.0051	-0.0024	-0.0001
0.05	-0.0704	-0.0512	-0.0331	-0.0186	-0.0073
0.20	-0.221	-0.172	-0.118	-0.0697	-0.0302
0.50	-0.384	-0.317	-0.231	-0.142	-0.0627
1.00	-0.506	-0.440	-0.339	-0.215	-0.0970
2.00	-0.600	-0.543	-0.442	-0.290	-0.132
5.00	-0.673	-0.629	-0.541	-0.368	-0.170
20.0	-0.715	-0.681	-0.609	-0.427	-0.199
100.	-0.727	-0.696	-0.630	-0.446	-0.209

Table 5.4 Normalised Stress Intensity Factors, $K_0/\bar{K}$, for Axisymmetric Problem II at Point B Subject to Thermal Cooling: $\bar{K}=E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β				
	15°	30°	45°	60°	75°
0.01	0.0855	0.0886	0.0776	0.0695	0.0754
0.05	0.405	0.418	0.339	0.333	0.362
0.20	1.336	1.382	1.245	1.143	1.256
0.50	2.511	2.600	2.401	2.258	2.497
1.00	3.596	3.742	3.533	3.400	3.804
2.00	4.630	4.871	4.695	4.627	5.241
5.00	5.636	6.037	5.943	6.000	6.894
20.0	6.340	6.913	6.908	7.095	8.246
100.	6.524	7.147	7.138	7.332	8.538

Table 5.5 Characteristic Phase Angles, ψ' , for Axisymmetric Problem II at Point B Subject to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/6})$; $\alpha_2/\alpha_1=10$

μ_2/μ_1	β				
	15°	30°	45°	60°	75°
0.01	30.0	34.7	39.2	39.9	34.5
0.05	29.7	33.6	37.6	38.2	32.7
0.20	28.2	30.1	33.0	32.9	27.2
0.50	24.9	25.4	27.0	26.0	19.9
1.00	20.7	20.9	21.3	19.4	12.8
2.00	15.8	16.3	15.9	13.2	6.0
5.00	10.5	11.8	10.8	7.2	-0.8
20.0	6.4	8.6	7.2	3.0	-5.6
100.	5.1	7.5	6.1	1.7	-7.1

Table 5.6 Normalised Stress Intensity Factors, $K_0/\bar{K}$, for Axisymmetric Problem III Subject to Thermal Cooling:
 $K=E_1\alpha_1|\Delta T|\sqrt{(\pi c)}$; $\alpha_2/\alpha_1=10$.

μ_2/μ_1	β		
	22.5°	45°	67.5°
0.01	0.0761	0.0986	0.100
0.05	0.360	0.466	0.461
0.20	1.191	1.538	1.542
0.50	2.218	2.854	2.918
1.00	3.099	3.974	4.158
2.00	3.915	5.017	5.365
5.00	4.672	5.987	6.556
20.0	5.223	6.663	7.498
100.	5.642	7.030	8.463

Table 5.7 Characteristic Phase Angles, ψ' , for Axisymmetric Problem III Subject to Thermal Cooling: $\psi' = \text{Arg}(Kc^{-1/2})$; $\alpha_2/\alpha_1=10$

μ_2/μ_1	β		
	22.5°	45°	67.5°
0.01	29.7	36.9	47.4
0.05	27.9	35.2	45.6
0.20	22.3	30.0	40.3
0.50	14.9	23.1	33.2
1.00	7.8	16.5	26.5
2.00	0.8	10.2	20.1
5.00	-6.1	4.0	14.1
20.0	-11.0	0.0	11.3
100.	-11.3	0.0	17.5

Figure 2.1 Local Coordinate Systems for Crack in Homogeneous Material

Figure 2.2a Opening Mode (Mode *I*) Crack Deformation

Figure 2.2b Shear Mode (Mode *II*) Crack Deformation

Figure 2.3 **Bimaterial Interface Crack**

Figure 2.4 **Relative Crack Face Displacements**

Figure 3.1 An Elastic Body R with Boundary S

$$N^1(\xi) = -\frac{1}{2}\xi(1 - \xi)$$

$$N^2(\xi) = 1 - \xi^2$$

$$N^3(\xi) = \frac{1}{2}\xi(1 + \xi)$$

Figure 3.2 The Quadratic Shape Functions

Figure 3.3 BEM Modelling of a Symmetric Crack Problem

Figure 3.4 Modelling of a General Crack by Multi-region BEM

$S^\alpha (\alpha = 1, 2)$ - Surface of Subregion α , $\bar{S}$ - Common Surface

Figure 3.5 Determination of Stress Intensity Factors Using Extrapolation Method

Figure 3.6 Quadratic Quarter-point Crack-tip Element

Figure 3.7 Quarter-point Elements on Crack Faces and Quarter-point Traction Singular Elements ahead of the Crack-tip

Figure 3.8 Centrally Located Crack Subject to Remote Tension

Figure 3.9 Boundary Element Mesh for Example 1

Figure 3.10 Single Edge Crack Embedded in Plate of Finite Width

Figure 3.11 Boundary Element Mesh for Example 2

Figure 3.12 Bimaterial Interface Straight Crack

Figure 3.13 Boundary Element Mesh for Example 3

Figure 3.14 Bimaterial Interface Arc Crack

Figure 3.15 Boundary Element Mesh for Example 4

Figure 3.16 Diametrical Plane of the Penny-shaped Interface Crack

Figure 3.17 Boundary Element Mesh for Example 5

Figure 4.1 Elliptical Inclusion with a Completely Penetrating Crack

Figure 4.2 Boundary Element Mesh for 2D Problem I

Figure 4.3 Stress Intensity Factors
for 2D Problem I; $c/a=1/3$

Figure 4.4 Stress Intensity Factors
for 2D Problem I; $c/a=1/2$

Figure 4.5 Stress Intensity Factors
for 2D Problem I; $c/a=1$

Figure 4.6 Stress Intensity Factors
for 2D Problem I; $c/a=2$

Figure 4.7 Stress Intensity Factors
for 2D Problem I; $c/a=3$

Figure 4.8 Elliptical Inclusion with a Partially Penetrating Crack

Figure 4.9 Boundary Element Mesh for 2D Problem II

Figure 4.10 Stress Intensity Factors
for 2D Problem II at Point A; $c/a=1/3$

Figure 4.11 Stress Intensity Factors
for 2D Problem II at Point A; $c/a=1/2$

Figure 4.12 Stress Intensity Factors
for 2D Problem II at Point A; $c/a=1$

Figure 4.13 Stress Intensity Factors
for 2D Problem II at Point A; $c/a=2$

Figure 4.14 Stress Intensity Factors
for 2D Problem II at Point A; $c/a=3$

Figure 4.15a Stress Intensity Factors
for 2D Problem II at Point B; $c/a=1/3$

Figure 4.15b Stress Intensity Factors
for 2D Problem II at Point B; $c/a=1/3$

Figure 4.16a Stress Intensity Factors
for 2D Problem II at Point B; $c/a=1/2$

Figure 16b Stress Intensity Factors
for 2D Problem II at Point B; $c/a=1/2$

Figure 4.17a Stress Intensity Factors
for 2D Problem II at Point B; $c/a=1$

Figure 4.17b Stress Intensity Factors
for 2D Problem II at Point B; $c/a=1$

Figure 4.18a Stress Intensity Factors
for 2D Problem II at Point B; $c/a=2$

Figure 4.18b Stress Intensity Factors
for 2D Problem II at Point B; $c/a=2$

Figure 4.19a Stress Intensity Factors
for 2D Problem II at Point B; $c/a=3$

Figure 4.19b Stress Intensity Factors
for 2D Problem II at Point B; $c/a=3$

Figure 4.20 **Tensile Stress at the Inclusion and Compressive Stress at the Matrix Acting Normal to the Plane of the Crack**

Figure 4.21 Elliptical Inclusion with a Y-shaped Crack

Figure 4.22 Boundary Element Mesh for 2D Problem III

Figure 4.23 Stress Intensity Factors
for 2D Problem III at Point A; $c/a=1/3$

Figure 4.24 Stress Intensity Factors
for 2D Problem III at Point A; $c/a=1/2$

Figure 4.25 Stress Intensity Factors
for 2D Problem III at Point A; $c/a=1$

Figure 4.26 Stress Intensity Factors
for 2D Problem III at Point A; $c/a=2$

Figure 4.27 Stress Intensity Factors
for 2D Problem III at Point A; $c/a=3$

Figure 4.28 Stress Intensity Factors
for 2D Problem III at Point B; $c/a=1/3$

Figure 4.29 Stress Intensity Factors
for 2D Problem III at Point B; $c/a=1/2$

Figure 4.30 Stress Intensity Factors
for 2D Problem III at Point B; $c/a=1$

Figure 4.31 Stress Intensity Factors
for 2D Problem III at Point B; $c/a=2$

Figure 4.32 Stress Intensity Factors
for 2D Problem III at Point B; $c/a=3$

Figure 4.33 Characteristic Phase Angles
for 2D Problem III at Point B; $c/a=1/3$

Figure 4.34 Characteristic Phase Angles
for 2D Problem III at Point B; $c/a=1/2$

Figure 4.35 Characteristic Phase Angles
for 2D Problem III at Point B; $c/a=1$

Figure 4.36 Characteristic Phase Angles
for 2D Problem III at Point B; $c/a=2$

Figure 4.37 Characteristic Phase Angles
for 2D Problem III at Point B; $c/a=3$

Figure 5.1 **Diametrical Plane of a Spherical Inclusion
with a Penny-shaped Crack**

Figure 5.2 Boundary Element Mesh for Axisymmetric Problem I

Figure 5.3a Stress Intensity Factors
for Axisymmetric Problem I; $b/c < 1$

Figure 5.3b Stress Intensity Factors
for Axisymmetric Problem I; $b/c < 1$

Figure 5.4 Stress Intensity Factors
for Axisymmetric Problem I; $b/c > 1$

Figure 5.5 **Diametrical Plane of a Spherical Inclusion with a Y-shaped Crack**

Figure 5.6 Boundary Element Mesh for Axisymmetric Problem II

Figure 5.7 Stress Intensity Factors
for Axisymmetric Problem II at Point A

Figure 5.8 Stress Intensity Factors
for Axisymmetric Problem II at Point B

Figure 5.9 Characteristic Phase Angles
for Axisymmetric Problem II at Point B

Figure 5.10 Diametrical Plane of an Ellipsoidal Inclusion with a Circumferential Interface Crack

Figure 5.11 Boundary Element Mesh for Axisymmetric Problem III

Figure 5.12 Stress Intensity Factors
for Axisymmetric Problem III; $c/a=1$

Figure 5.13 Stress Intensity Factors
for Axisymmetric Problem III; $c/a=2$

Figure 5.14 Stress Intensity Factors
for Axisymmetric Problem III; $c/a=3$

Figure 5.15 Characteristic Phase Angles
for Axisymmetric Problem III; $c/a=1$

1

**PM-1 3½"x4" PHOTOGRAPHIC MICROCOPY TARGET
NBS 1010a ANSI/ISO #2 EQUIVALENT**

PRECISIONSM RESOLUTION TARGETS

PIONEERS IN METHYLENE BLUE TESTING SINCE 1974

1800 COUNTY ROAD 5 BURNINGWELL, WY 82401 USA
TEL: 617 435 7897 FAX: 617 435 7897 TLA: 810000000

National Library
of Canada

Bibliothèque nationale
du Canada

Canadian Theses Service

Service des thèses canadiennes

Ottawa, Canada
K1A 0N4

NOTICE

The quality of this microform is heavily dependent upon the quality of the original thesis submitted for microfilming. Every effort has been made to ensure the highest quality of reproduction possible.

If pages are missing, contact the university which granted the degree.

Some pages may have indistinct print especially if the original pages were typed with a poor typewriter ribbon or if the university sent us an inferior photocopy.

Reproduction in full or in part of this microform is governed by the Canadian Copyright Act, R.S.C. 1970, c. C-30, and subsequent amendments.

AVIS

La qualité de cette microforme dépend grandement de la qualité de la thèse soumise au microfilmage. Nous avons tout fait pour assurer une qualité supérieure de reproduction.

S'il manque des pages, veuillez communiquer avec l'université qui a conféré le grade.

La qualité d'impression de certaines pages peut laisser à désirer, surtout si les pages originales ont été dactylographiées à l'aide d'un ruban usé ou si l'université nous a fait parvenir une photocopie de qualité inférieure.

La reproduction, même partielle, de cette microforme est soumise à la Loi canadienne sur le droit d'auteur, SRC 1970, c. C-30, et ses amendements subséquents.

Boundary Element Fracture Mechanics Analysis of Elastic Inclusion Problems

Xian-Jun Zheng

*A thesis submitted to
the Faculty of Graduate Studies and Research
in partial fulfillment of
the requirements for the degree of
Master of Engineering*

**Department of Mechanical and Aerospace Engineering
Carleton University
Ottawa, Ontario K1S 5B6
Canada**

June 1991

National Library
of Canada

Bibliothèque nationale
du Canada

Canadian Theses Service Service des thèses canadiennes

Ottawa, Canada
K1A 0N4

The author has granted an irrevocable non-exclusive licence allowing the National Library of Canada to reproduce, loan, distribute or sell copies of his/her thesis by any means and in any form or format, making this thesis available to interested persons.

The author retains ownership of the copyright in his/her thesis. Neither the thesis nor substantial extracts from it may be printed or otherwise reproduced without his/her permission.

L'auteur a accordé une licence irrévocable et non exclusive permettant à la Bibliothèque nationale du Canada de reproduire, prêter, distribuer ou vendre des copies de sa thèse de quelque manière et sous quelque forme que ce soit pour mettre des exemplaires de cette thèse à la disposition des personnes intéressées.

L'auteur conserve la propriété du droit d'auteur qui protège sa thèse. Ni la thèse ni des extraits substantiels de celle-ci ne doivent être imprimés ou autrement reproduits sans son autorisation.

ISBN 0-315-75985-2

Canada

The undersigned recommend to the Faculty of Graduate Studies and Research acceptance of the thesis 'Boundary Element Fracture Mechanics Analysis of Elastic Inclusion Problems' submitted by Xian-Jun Zheng, in partial fulfillment of the requirements for the degree of Master of Mechanical Engineering.

Thesis Supervisor

**Chairman
Department of Mechanical
and Aerospace Engineering**

Abstract

The theory of linear elastic fracture mechanics and the formulation of the multi-region boundary element method (BEM) with quarter-point crack-tip elements are reviewed in this study. In addition, the concepts of the overall stress intensity factor and the characteristic phase angle are introduced. These two quantities are required for the full characterisation of the oscillatory singular stress fields in the vicinity of a bimaterial interface crack-tip. A review of the derivation of the formulae which may be used for evaluating the stress intensity factors directly from the BEM computed values of the nodal displacements or the traction coefficients at the crack-tip elements, is also presented here. The veracity and efficiency of the BEM approach undertaken are demonstrated by several test problems.

The multi-region BEM with quarter-point crack-tip elements is then applied to the two-dimensional and axisymmetric linear elastic fracture mechanics analysis of cracks occurring at inclusions, subject to either mechanical loading or thermal cooling. Several crack configurations are considered, and for a given crack problem, a range of crack sizes is treated. The effects of the mismatch between the shear modulus and the thermal expansion coefficient of the inclusion and those of the matrix are also investigated. The numerical results obtained may be applied to, for example, the study of microcracking in composite materials.

Acknowledgements

I wish to express my sincere appreciation to my thesis supervisor Prof. C. L. Tan for his invaluable guidance and suggestions during the course of this work. I also wish to thank Dr. Y. L. Gao for the assistance he has offered in the study.

Contents

Abstract	i
Acknowledgements	ii
Contents	iii
Nomenclature	vi
List of Tables	x
List of Figures	xvii
1 Introduction	1
2 Near-tip Fields of a Crack and Fracture Characterising Parameters	5
2.1 Crack Embedded in Homogeneous Material	6
2.2 The Bimaterial Interfacial Crack	10
2.3 Closing Remarks	16
3 The Use of the Boundary Element Method in Fracture Mechanics	18
3.1 Introduction	18
3.2 The Boundary Integral Equation for Elastostatics	19
3.3 Numerical Solution of the BIE	22
3.4 Application of BEM to Linear Elastic Fracture Mechanics	25
3.4.1 Quarter-point Element	25
3.4.2 Determination of Fracture Characterising Parameters	28
3.5 Examples	31
3.5.1 Infinite Plate with a Central Crack	32

3.5.2	Plate of Finite Width with a Single Edge Crack	32
3.5.3	Infinite Plate with an Interface Straight Crack	33
3.5.4	Inclusion Problem with an Interface Arc Crack	35
3.5.5	Infinite Body with a Penny-shaped Interface Crack	36
3.5.6	Further Remarks	37
3.6	Closing Remarks	38
4	Two Dimensional Fracture Analysis for Cracks at Inclusions	39
4.1	2D Problem I: Crack which has completely penetrated an inclusion .	41
4.1.1	Mechanical Load	41
4.1.2	Thermal Cooling	42
4.2	2D Problem II: Partially penetrating crack	43
4.2.1	Mechanical Load	43
4.2.2	Thermal Cooling	44
4.3	2D Problem III: Y-shaped crack	45
4.3.1	Mechanical Load	46
4.3.2	Thermal Cooling	47
4.4	Conclusion	47
5	Axisymmetric Fracture Analysis for Cracks at Inclusions	48
5.1	Axisymmetric Problem I: Penny-shaped crack	49
5.1.1	Mechanical Load	50
5.1.2	Thermal Cooling	51
5.2	Problem II: Y-shaped crack	51
5.2.1	Mechanical Load	52
5.2.2	Thermal Cooling	53
5.3	Problem III: Circumferential interface crack	53
5.3.1	Mechanical Load	53
5.3.2	Thermal Cooling	54
5.4	Conclusions	55

6 Summary and Conclusions	56
References	58

Nomenclature

a	- Characteristic crack length
a	- Semi-axis of an elliptical or ellipsoidal inclusion
A_i^1, A_i^2, A_i^3	- Coefficients of the expression for the displacement variation over the quarter-point crack-tip element
B_i^1, B_i^2, B_i^3	- Coefficients of the expression for the traction variation over the quarter-point crack-tip element
$\overline{B}_i^1, \overline{B}_i^2, \overline{B}_i^3$	- Coefficients of the expression for the traction variation over the quarter-point traction singularity crack-tip element
c	- Semi-axis of an elliptical or ellipsoidal inclusion
c	- Radius of a spherical inclusion
$C_{ij}(P)$	- Limiting value of the surface integral of $T_{ij}(P, Q)$
E, E_1, E_2	- Young's moduli
f_i	- Body force vector
G	- Strain energy release rate
G_I	- Strain energy release rate for mode <i>I</i> crack deformation
G_{II}	- Strain energy release rate for mode <i>II</i> crack deformation
G_C	- Critical strain energy release rate
G_{IC}	- Critical strain energy release rate for mode <i>I</i> crack deformation
G_{IIC}	- Critical strain energy release rate for mode <i>II</i> crack deformation
h	- Characteristic length for the phase angle ψ^*
$J(\xi)$	- Jacobian of transformation
K	- Complex stress intensity factor

K_I	- Mode <i>I</i> stress intensity factor
K_{IC}	- Critical stress intensity factor for mode <i>I</i> crack deformation
K_{II}	- Mode <i>II</i> stress intensity factor
K_{IIC}	- Critical stress intensity factor for mode <i>II</i> crack deformation
K_0	- Overall stress intensity factor
l	- Length of the crack-tip element
M	- Total number of boundary elements
N	- Total number of boundary nodes
n_i	- Components of the unit outward normal
$N^c(\xi)$	- Shape functions
$\bar{N}^c(\xi)$	- Modified shape functions
p	- Internal pressure
P	- A point on the boundary
P^a	- a-th node of the boundary element mesh
$P^{d(b,c)}$	- c-th node of the b-th element
Q	- General boundary point
r	- Distance between P and Q
r	- Distance away from the crack-tip; a polar coordinate
R	- Crack resistance
S	- Boundary of domain
t_i	- Traction
t_i^1, t_i^2, t_i^3	- Nodal tractions
$\bar{t}_i^1, \bar{t}_i^2, \bar{t}_i^3$	- Traction coefficients
$T_{ij}(P, Q)$	- The Kelvin fundamental solution for tractions
ΔT	- Temperature change
U	- Stored strain energy
u_i	- Displacements
u_x, u_y	- Displacements in the x,y directions

u_i^1, u_i^2, u_i^3	- Nodal displacements
$U_{ij}(P, Q)$	- The Kelvin fundamental solution for displacements
v_1, v_2	- Complex displacements
v_{1r}, v_{2r}	- Displacements in the r -th direction
$v_{1\theta}, v_{2\theta}$	- Displacements in the θ -th direction
Δv	- The complex relative crack face displacement
$\Delta v_r, \Delta v_\theta$	- Components of Δv
W	- Total surface energy
W	- Width of the plate with a edge crack
$\alpha, \alpha_1, \alpha_2$	- Coefficients of thermal expansion
α'	- Equivalent coefficient of thermal expansion
β	- An angle measuring the extent of debonding between the inclusion and the matrix
γ	- A bimaterial constant
γ_s	- Specific surface energy
Γ	- Special gamma function
δ_{ij}	- Kronecker delta
ϵ	- A bimaterial constant
θ	- Temperature change
θ	- An angle measuring the extent of debonding between the inclusion and the matrix
θ	- A polar coordinate
λ	- A bimaterial constant
μ, μ_1, μ_2	- Shear moduli
ν, ν_1, ν_2	- Poisson's ratios
ξ	- The local or intrinsic coordinate
ρ	- Density
$\sigma_{xx}, \sigma_{yy}, \sigma_{xy}, \sigma_{r\theta}, \sigma_{\theta\theta}$	- Stress components

- $\sigma_{\alpha rr}, \sigma_{\alpha r\theta}, \sigma_{\alpha\theta\theta}$ - Stress components for material α ($\alpha = 1, 2$)
- $\sigma_{\alpha r}, \sigma_{\alpha\theta}$ - Complex stresses for material α ($\alpha = 1, 2$)
- ϕ - A potential related to body force and temperature change
- ψ - Phase angle for bimaterial interface crack
- ψ^* - Non-dimensionalised phase angle for bimaterial interface crack

List of Tables

Table 3.1	Percentage Error in the Stress Intensity Factor for Plate with a Central Crack: $\bar{K} = \sigma\sqrt{(\pi a)}$; $(K_I)_t$ - Traction Formula Result; $(K_I)_d$ - Displacement Formula Result. $(K_I/\bar{K})_{exact} = 1$	63
Table 3.2	Percentage Error in the Stress Intensity Factor for Finite Plate with a Edge Crack: $\bar{K} = \sigma\sqrt{(\pi a)}$; $(K_I)_t$ - Traction Formula Result; $(K_I)_d$ - Displace- ment Formula Result. $(K_I/\bar{K})_{exact} = 1.5047$	63
Table 3.3a	Percentage Error in the Normalised Overall Stress Intensity Factor for Infinite Plate with a Bimaterial Central Crack: $\bar{K} = (\sigma)_y^\infty \sqrt{(\pi a)}$; $(K_0)_t$ - Traction For- mula Result; $(K_0)_d$ - Displacement Formula Result.	64
Table 3.3b	Percentage Error in the Phase Angle for Infinite Plate with a Bimaterial Central Crack: $\psi^* = \text{Arg}(K a^{-i\epsilon})$	65
Table 3.4a	Percentage Error in the Normalised Stress Intensity Factor for the Bimaterial Interface Arc Crack: $\bar{K} = \sigma\sqrt{(\pi a)}$; $(K_0)_t$ - Traction Formula Result; $(K_0)_d$ - Displacement Formula Result.	66
Table 3.4b	Percentage Error in the Phase Angle for the Bi- material Interface Arc Crack: $\psi^* = \text{Arg}(K a^{-i\epsilon})$	67

Table 3.5a	Percentage Error in the Normalised Stress Intensity Factor for the Penny-shaped Bimaterial Interface Crack: $\overline{K} = p\sqrt{(\pi a)}$; $(K_0)_t$ - Traction Formula Result; $(K_0)_d$ - Displacement Formula Result.	68
Table 3.5b	Percentage Error in the Phase Angle for the Penny-shaped Bimaterial Interface Crack: $\psi^* = \text{Arg}(K a^{-1/2})$	69
Table 4.1	Normalised Stress Intensity Factors, $K_I/\overline{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\overline{K} = E_1\alpha_1\Delta T\sqrt{(\pi b)}$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.	70
Table 4.2	Normalised Stress Intensity Factors, $K_I/\overline{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\overline{K} = E_1\alpha_1\Delta T\sqrt{(\pi b)}$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.	70
Table 4.3	Normalised Stress Intensity Factors, $K_I/\overline{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\overline{K} = E_1\alpha_1\Delta T\sqrt{(\pi b)}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.	71
Table 4.4	Normalised Stress Intensity Factors, $K_I/\overline{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\overline{K} = E_1\alpha_1\Delta T\sqrt{(\pi b)}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.	71
Table 4.5	Normalised Stress Intensity Factors, $K_I/\overline{K}$, for 2D Inclusion Problem with Completely Penetrating Crack	

	Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi b)}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.	72
Table 4.6	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{[\pi(b+d)]}$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.	73
Table 4.7	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{[\pi(b+d)]}$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.	73
Table 4.8	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{[\pi(b+d)]}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.	74
Table 4.9	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{[\pi(b+d)]}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.	74
Table 4.10	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{[\pi(b+d)]}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.	75
Table 4.11	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal	

$$\text{Cooling: } \bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}; c/a = 1/3; \\ \alpha_2/\alpha_1 = 10. \quad 75$$

Table 4.12	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}; c/a = 1/2; \alpha_2/\alpha_1 = 10.$	76
------------	---	----

Table 4.13	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}; c/a = 1; \alpha_2/\alpha_1 = 10.$	76
------------	---	----

Table 4.14	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}; c/a = 2; \alpha_2/\alpha_1 = 10.$	77
------------	---	----

Table 4.15	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem II at Point B Subject to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{[\pi(b+d)]}; c/a = 3; \alpha_2/\alpha_1 = 10.$	77
------------	---	----

Table 4.16	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}; c/a = 1/3; \alpha_2/\alpha_1 = 10.$	78
------------	---	----

Table 4.17	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling: $\bar{K} = E_1 \alpha_1 \Delta T \sqrt{(\pi d)}; c/a = 1/2; \alpha_2/\alpha_1 = 10.$	78
------------	---	----

Table 4.18	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.	79
Table 4.19	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.	79
Table 4.20	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem III at Point A Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.	80
Table 4.21	Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.	81
Table 4.22	Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.	81
Table 4.23	Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.	82
Table 4.24	Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.	82
Table 4.25	Normalised Stress Intensity Factors, $K_0/\bar{K}$, for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi d)}$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.	83

Table 4.26	Characteristic Phase Angles, ψ^* (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.	83
Table 4.27	Characteristic Phase Angles, ψ^* (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.	84
Table 4.28	Characteristic Phase Angles, ψ^* (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $c/a = 1$; $\alpha_2/\alpha_1 = 10$.	84
Table 4.29	Characteristic Phase Angles, ψ^* (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $c/a = 2$; $\alpha_2/\alpha_1 = 10$.	85
Table 4.30	Characteristic Phase Angles, ψ^* (deg.), for 2D Inclusion Problem III at Point B Subjected to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $c/a = 3$; $\alpha_2/\alpha_1 = 10$.	85
Table 5.1	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for Axisymmetric Problem I Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1 = 10$; $b/c < 1$.	86
Table 5.2	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for Axisymmetric Problem I Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1 = 10$; $b/c > 1$.	86
Table 5.3	Normalised Stress Intensity Factors, $K_I/\bar{K}$, for Axisymmetric Problem II at Point A Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1 = 10$.	87

Table 5.4	Normalised Stress Intensity Factors, $K_0/\overline{K}$, for Axisymmetric Problem II at Point B Subject to Thermal Cooling: $\overline{K} = E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1 = 10$.	87
Table 5.5	Characteristic Phase Angles, ψ^* , for Axisymmetric Problem II at Point B Subject to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $\alpha_2/\alpha_1 = 10$.	88
Table 5.6	Normalised Stress Intensity Factors, $K_0/\overline{K}$, for Axisymmetric Problem III Subject to Thermal Cooling: $\overline{K} = E_1\alpha_1\Delta T\sqrt{(\pi c)}$; $\alpha_2/\alpha_1 = 10$.	89
Table 5.7	Characteristic Phase Angles, ψ^* , for Axisymmetric Problem III Subject to Thermal Cooling: $\psi^* = \text{Arg}(Kc^{-i\epsilon})$; $\alpha_2/\alpha_1 = 10$.	89

List of Figures

Figure 2.1	Local Coordinate Systems for Crack in Homogeneous Materials	90
Figure 2.2a	Opening Mode (Mode <i>I</i>) Crack Deformation	91
Figure 2.2b	Shear Mode (Mode <i>II</i>) Crack Deformation	91
Figure 2.3	Bimaterial Interface Crack	92
Figure 2.4	Relative Crack Face Displacements	93
Figure 3.1	An Elastic Body <i>R</i> with Boundary <i>S</i>	94
Figure 3.2	The Quadratic Shape Functions	95
Figure 3.3	BEM Modelling of a Symmetric Crack Problem	96
Figure 3.4	Modelling of a General Crack by Multi-region BEM	97
Figure 3.5	Determination of Stress Intensity Factors Using Extrapolation Method	98
Figure 3.6	Quadratic Quarter-point Crack-tip Element	99
Figure 3.7	Quarter-point Elements on Crack Faces and Quarter-point Traction Singular Elements ahead of the Crack tip	99

Figure 3.8	Centrally Located Crack Subject to Remote Tension	100
Figure 3.9	Boundary Element Mesh for Example 1	101
Figure 3.10	Single Edge Crack Embedded in Plate of Finite Width	102
Figure 3.11	Boundary Element Mesh for Example 2	103
Figure 3.12	Bimaterial Interface Straight Crack	104
Figure 3.13	Boundary Element Mesh for Example 3	105
Figure 3.14	Bimaterial Interface Arc Crack	106
Figure 3.15	Boundary Element Mesh for Example 4	107
Figure 3.16	Diametrical Plane of a bimaterial body with a Penny-shaped Interface Crack	108
Figure 3.17	Boundary Element Mesh for Example 5	109
Figure 4.1	Elliptical Inclusion with a Completely Penetrating Crack	110
Figure 4.2	Boundary Element Mesh for 2D Problem I	111
Figure 4.3	Stress Intensity Factors for 2D Problem I; $c/a = 1/3$	112
Figure 4.4	Stress Intensity Factors for 2D Problem I; $c/a = 1/2$	113
Figure 4.5	Stress Intensity Factors for 2D Problem I; $c/a = 1$	114
Figure 4.6	Stress Intensity Factors for 2D Problem I; $c/a = 2$	115

Figure 4.7	Stress Intensity Factors for 2D Problem I: $c/a = 3$	116
Figure 4.8	Elliptical Inclusion with a Partially Penetrating Crack	117
Figure 4.9	Boundary Element Mesh for 2D Problem II	118
Figure 4.10	Stress Intensity Factors for 2D Problem II at Point A; $c/a = 1/3$	119
Figure 4.11	Stress Intensity Factors for 2D Problem II at Point A; $c/a = 1/2$	120
Figure 4.12	Stress Intensity Factors for 2D Problem II at Point A; $c/a = 1$	121
Figure 4.13	Stress Intensity Factors for 2D Problem II at Point A; $c/a = 2$	122
Figure 4.14	Stress Intensity Factors for 2D Problem II at Point A; $c/a = 3$	123
Figure 4.15a	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 1/3$	124
Figure 4.15b	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 1/3$	125
Figure 4.16a	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 1/2$	126
Figure 4.16b	Stress Intensity Factors for 2D Problem II at	

	Point B; $c/a = 1/2$	127
Figure 4.17a	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 1$	128
Figure 4.17b	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 1$	129
Figure 4.18a	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 2$	130
Figure 4.18b	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 2$	131
Figure 4.19a	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 3$	132
Figure 4.19b	Stress Intensity Factors for 2D Problem II at Point B; $c/a = 3$	133
Figure 4.20	Tensile Stress at the Inclusion and Compressive Stress at the Matrix Acting Normal to the Plane of the Crack	134
Figure 4.21	Elliptical Inclusion with a Y-shaped Crack	135
Figure 4.22	Boundary Element Mesh for 2D Problem III	136
Figure 4.23	Stress Intensity Factors for 2D Problem III at Point A; $c/a = 1/3$	137
Figure 4.24	Stress Intensity Factors for 2D Problem III at	

Point A; $c/a = 1/2$	138
Figure 4.25 Stress Intensity Factors for 2D Problem III at Point A; $c/a = 1$	139
Figure 4.26 Stress Intensity Factors for 2D Problem III at Point A; $c/a = 2$	140
Figure 4.27 Stress Intensity Factors for 2D Problem III at Point A; $c/a = 3$	141
Figure 4.28 Stress Intensity Factors for 2D Problem III at Point B; $c/a = 1/3$	142
Figure 4.29 Stress Intensity Factors for 2D Problem III at Point B; $c/a = 1/2$	143
Figure 4.30 Stress Intensity Factors for 2D Problem III at Point B; $c/a = 1$	144
Figure 4.31 Stress Intensity Factors for 2D Problem III at Point B; $c/a = 2$	145
Figure 4.32 Stress Intensity Factors for 2D Problem III at Point B; $c/a = 3$	146
Figure 4.33 Characteristic Phase Angles for 2D Problem III at Point B; $c/a = 1/3$	147
Figure 4.34 Characteristic Phase Angles for 2D Problem III	

	at Point B; $c/a = 1/2$	148
Figure 4.35	Characteristic Phase Angles for 2D Problem III at Point B; $c/a = 1$	149
Figure 4.36	Characteristic Phase Angles for 2D Problem III at Point B; $c/a = 2$	150
Figure 4.37	Characteristic Phase Angles for 2D Problem III at Point B; $c/a = 3$	151
Figure 5.1	Diametrical Plane of a Spherical Inclusion with a Penny-shaped Crack	152
Figure 5.2	Boundary Element Mesh for Axisymmetric Problem I	153
Figure 5.3a	Stress Intensity Factors for Axisymmetric Problem I; $b/c < 1$	154
Figure 5.3b	Stress Intensity Factors for Axisymmetric Problem I; $b/c < 1$	155
Figure 5.4	Stress Intensity Factors for Axisymmetric Problem I; $b/c > 1$	156
Figure 5.5	Diametrical Plane of a Spherical Inclusion with a Y-shaped Crack	157
Figure 5.6	Boundary Element Mesh for Axisymmetric Problem II	158

Figure 5.7	Stress Intensity Factors for Axisymmetric Problem II at Point A	159
Figure 5.8	Stress Intensity Factors for Axisymmetric Problem II at Point B	160
Figure 5.9	Characteristic Phase Angles for Axisymmetric Problem II at Point B	161
Figure 5.10	Diametrical Plane of an Elliptical Inclusion with a Circumferential Interface Crack	162
Figure 5.11	Boundary Element Mesh for Axisymmetric Problem III	163
Figure 5.12	Stress Intensity Factors for Axisymmetric Problem III; $c/a = 1$	164
Figure 5.13	Stress Intensity Factors for Axisymmetric Problem III; $c/a = 2$	165
Figure 5.14	Stress Intensity Factors for Axisymmetric Problem III; $c/a = 3$	166
Figure 5.15	Characteristic Phase Angles for Axisymmetric Problem III; $c/a = 1$	167
Figure 5.16	Characteristic Phase Angles for Axisymmetric Problem III; $c/a = 2$	168
Figure 5.17	Characteristic Phase Angles for Axisymmetric Problem III; $c/a = 3$	169

Chapter 1

Introduction

Advanced composite materials are increasingly being used in recent years for structural applications because of their high strength-to-weight ratios which often cannot be achieved by the use of homogeneous materials. These materials can be categorized, in general, into fiber-reinforced composites and particulate-reinforced composites. While the former offers the highest specific strength and stiffness along the direction of the reinforcement, particulate composites are more isotropic in their properties and are relatively easier to process.

The study of a composite material may be carried out from the macro point of view, in which the material is considered to be a single continuum with mechanical properties that are related to those of both the matrix and the inclusion. In the micromechanics of these materials, however, the details of the matrix and the inclusion must be taken into consideration. In this regard, the fiber and particulate reinforced composites may often be modelled as two-dimensional and axisymmetric inclusion problems, respectively, in simple geometric and load conditions. The fracture analysis of these problems is of practical importance because cracks often initiate from the inclusions due to the relatively high localised stresses. These stresses can arise from the differences in the elastic properties and the thermal expansion coefficient. The presence of microcracks will in general cause a deterioration of the resistance to fracture of the material. However, a limited amount of microcracking in a number

of ceramics have been shown to provide a shielding mechanism which may partially or totally offset the growth of a, say, macro-crack, leading to improvement in their fracture toughness (Evans and Faber (1984)). The fracture analysis of microcracks at inclusions thus helps to provide a better understanding of their effects on the macro-properties of the composite.

Crack(s) may initiate within the inclusion and then extend into the matrix, or occur along the inclusion-matrix interface (which may also extend into the matrix) if the interface is relatively weak. For cracks with crack-tips located in a piece-wise homogeneous region, either the inclusion or the matrix, the near-tip stress and displacement fields are well known in linear elastic fracture mechanics, and the stress intensity factors of the opening and shear modes have long been established as the characterising fracture parameters. In the case of bimaterial interface cracks, however, the stresses are oscillatorily singular as the interface crack-tip is approached (Williams (1959)). Also, the tensile and shear effects are always coupled, see, Rice and Sih (1965); as a result, the classical stress intensity factor of either tensile or shear mode can no longer be separately defined. An implication of the oscillatory stress and displacement fields is that the crack surfaces overlap in the vicinity of the interface crack-tip, see, e.g. England (1965). This is of course physically unrealistic and is due to the fact that the contact conditions between the crack surfaces in the vicinity of the crack-tip have not been considered in the analysis, Comninou (1977). However, as will be discussed in the next chapter, the associated complex stress intensity factor can still be used as the fracture characterising parameter as long as the contact region is very small compared to the crack size, as is often the case for tensile loads. The strain energy release rate, on the other hand, is not oscillatory in form, and the related fracture criterion has been suggested by some authors, see, e.g. Mulville and Mast (1976).

Analytical solutions for inclusion problems with cracks are available only for a few cases with relatively simple geometric configurations and load conditions. For

more complex crack problems, recourse to numerical or experimental methods becomes necessary for determining the fracture characterising parameters. As far as general numerical techniques are concerned, the finite element method (FEM) and the boundary element method (BEM) (also commonly known as the boundary integral equation (BIE) method) are the most widely used for treating crack problems. The latter, in particular, has been found over the years to be a very efficient tool for the fracture analysis of cracks embedded in homogeneous bodies, ever since it was first used in this area by Cruse (1971, 1974). Its application to crack problems involving composite materials has, however, been limited to only a few cases so far. For cracks with crack-tips located in piece-wise homogeneous regions of the composite, the fracture analysis using the BEM is relatively straight-forward. The BEM procedures for the determination of the stress intensity factors, in this regard, are well established in the literature. On the other hand, the treatment of bimaterial interface cracks is relatively more difficult because the stresses in the vicinity of the crack-tips are oscillatorily singular in form. Reports of the analysis of such problems using BEM are very limited indeed. Among them are the works of Lee and Choi (1988) who employed the conventional multi-region BEM with extremely refined elements near the crack-tip to obtain the stress intensity factors. Yuuki et al (1987,1988) and Hasegawa (1988), on the other hand, used a special fundamental solution, namely, the Hetenyi's solution for a crack lying between two different homogeneous half-planes, in their BIE formulations. More recently, Tan and Gao (1990a, 1990b, 1991) performed a series of studies on crack problems involving dissimilar materials, using the conventional BEM method in conjunction with the quarter-point crack-tip elements. They derived analytical relations for the direct evaluation of the fracture characterising parameters from the BEM computed results and showed that accurate numerical results may be obtained even with relatively course mesh discretisations using their approach.

In the present study, the conventional multi-region BEM with quarter-point crack-tip elements, following Tan and Gao, is used for the two dimensional and axisymmetric fracture analysis of cracks occurring at inclusions. The crack configurations considered

include those originating in the inclusion and then extending into the matrix, as well as those with bimaterial interface cracks which may also develop into the matrix. For each problem, a range of crack geometries is treated under both mechanical loading as well as thermal cooling, and the effects of the mismatch in shear modulus ratio between the inclusion and the matrix are also investigated. Before the BIE analysis of these problems are discussed, however, the theory of linear elastic fracture mechanics and the formulation of the multi-region BEM with quarter-point crack-tip elements will first be reviewed, in the next two chapters, respectively.

Chapter 2

Near-tip Fields of a Crack and Fracture Characterising Parameters

Cracks are present to a certain degree in all engineering materials. If left unchecked, their growth under service loads will lead to failure by catastrophic fracture in structures. Where they are known to exist, their presence must be considered in engineering design or analysis. Under conditions of very small scale yielding, the concepts of linear elastic fracture mechanics (LEFM) may be employed. In this regard, the near-tip stress and displacement fields of a crack in homogeneous material are well known and the use of the stress intensity factors, K_I and K_{II} , as the fracture characterising parameters has been well established. On the other hand, the near-tip fields for a crack lying at the interface between two dissimilar materials are not as well understood. Interest in such problems has been rekindled in recent years due to the increasing use of advanced composite materials for structural applications. Unlike cracks in homogeneous bodies, the tensile and shear effects are always coupled even for single mode loading for a bimaterial interface crack. K_I and K_{II} therefore can not be interpreted in the classical separate form as in homogeneous materials. In this chapter, the near-tip fields for both types of cracks are reviewed. The choice of characterising parameters for the latter type problem is further discussed.

2.1 Crack Embedded in Homogeneous Material

Using the complex analytic function approach of Muskhelishvili (1953) the near-tip stress and displacement distributions for a crack embedded in homogeneous material may be derived from the basic equations of linear elasticity (see Sih and Rice (1964), Rice and Sih (1965)). They are

Stresses

$$\sigma_{xx} = \frac{K_I \cos(\theta/2)}{\sqrt{2\pi r}} [1 - \sin(\theta/2) \sin(3\theta/2)] - \frac{K_{II} \sin(\theta/2)}{\sqrt{2\pi r}} [2 + \cos(\theta/2) \cos(3\theta/2)] + O(r^0) \quad (2.1)$$

$$\sigma_{yy} = \frac{K_I \cos(\theta/2)}{\sqrt{2\pi r}} [1 + \sin(\theta/2) \sin(3\theta/2)] + \frac{K_{II} \sin(\theta/2)}{\sqrt{2\pi r}} \cos(\theta/2) \cos(3\theta/2) + O(r^0) \quad (2.2)$$

$$\sigma_{xy} = \frac{K_I \cos(\theta/2)}{\sqrt{2\pi r}} \sin(\theta/2) \sin(3\theta/2) + \frac{K_{II} \cos(\theta/2)}{\sqrt{2\pi r}} [1 - \sin(\theta/2) \sin(3\theta/2)] + O(r^0) \quad (2.3)$$

Displacements

$$u_x = \frac{K_I \sqrt{r/(2\pi)}(1+\nu)}{2E} [(2k-1) \cos(\theta/2) - \cos(3\theta/2)] + \frac{K_{II} \sqrt{r/(2\pi)}(1+\nu)}{2E} [(2k+3) \sin(\theta/2) + \sin(3\theta/2)] \quad (2.4)$$

$$u_y = \frac{K_I \sqrt{r/(2\pi)}(1+\nu)}{2E} [(2k+1) \sin(\theta/2) - \sin(3\theta/2)]$$

$$-\frac{K_{II}\sqrt{r/(2\pi)}(1+\nu)}{2E}[(2k-3)\cos(\theta/2) + \cos(3\theta/2)] \quad (2.5)$$

where subscripts x and y refer to the x and y directions of the local Cartesian coordinate system respectively, as shown in Figure 2.1, while r and θ are polar coordinates defined with the same local origin at the crack-tip. Also, E and ν are the Young's modulus and Poisson's ratio, respectively, and

$$k = \begin{cases} (3-\nu)/(1+\nu), & \text{for plane stress} \\ (3-4\nu), & \text{for plane strain} \end{cases} \quad (2.6)$$

The parameters K_I and K_{II} are coefficients reflecting the intensities of the stress fields in the vicinity of the crack-tip caused by the opening and shear mode deformations respectively, see Figure 2.2a and Figure 2.2b. They are commonly referred to as stress intensity factors of mode I and mode II deformation, respectively.

In linear elastic fracture mechanics, the critical stress intensity factor K_{IC} (or K_{IIC}), also commonly called the material fracture toughness, may be introduced. It is the stress intensity factor at or beyond which unstable crack propagation occurs in the material. A fracture criterion for the onset of crack growth is established as below:

$$\begin{cases} K_I \geq K_{IC}, & \text{in mode I deformation} \\ K_{II} \geq K_{IIC}, & \text{in mode II deformation} \end{cases} \quad (2.7)$$

Note that K_{IC} and K_{IIC} are material properties, while the stress intensity factors K_I and K_{II} are characterising parameters which are functions of load and geometry.

Another fracture characterising parameter for crack problems is the strain energy release rate G introduced by Griffith in 1920. In terms of stored strain energy U (in

the elastic body) and crack length a , G may be defined as:

$$G = -\frac{\partial U}{\partial a} \quad (2.8)$$

Associated with G is Griffith's energy criterion, which predicts the onset of crack growth when the strain energy release rate exceeds the rate of increase in surface energy. The rate of increase in surface energy, due to crack extension, is a material property alternatively called the crack resistance R :

$$R = \frac{\partial W}{\partial a} = 2\gamma_s \quad (2.9)$$

where W and γ_s are total and specific surface energy, respectively. According to Griffith's energy criterion, unstable crack extension happens when

$$\frac{\partial}{\partial a}(W + U) = 0 \quad (2.10)$$

or

$$G = R = G_C \quad (2.11)$$

where G_C is a material property called critical strain energy release rate.

Further theoretical analysis (see, e.g., Owen and Fawkes (1983)) relates G to the stress intensity factors K_I and K_{II} , for mixed mode deformation, according to:

$$G = (K_I^2 + K_{II}^2) \frac{(k+1)}{8\mu} \quad (2.12)$$

where μ is the shear modulus for the material. Or for separate form of deformation

$$\begin{cases} G_I = K_I^2(k+1)/(8\mu), & \text{in mode I deformation} \\ G_{II} = K_{II}^2(k+1)/(8\mu), & \text{in mode II deformation} \end{cases} \quad (2.13)$$

in which subscripts *I* and *II* of *G* represent mode I and mode II deformation, respectively. A similar relationship exists between G_{IC} and K_{IC} or G_{IIC} and K_{IIC} as shown below:

$$\begin{cases} G_{IC} = K_{IC}^2(k+1)/(8\mu), & \text{in mode I deformation} \\ G_{IIC} = K_{IIC}^2(k+1)/(8\mu), & \text{in mode II deformation} \end{cases} \quad (2.14)$$

Analytical solutions for the stress intensity factors (or the strain energy release rate) are however restricted to only a small number of crack problems of relatively simple geometric configurations. Experimental or numerical methods usually have to be employed to meet the needs of increasingly wide engineering applications of fracture mechanics.

It can be seen from the Eqs. (2.1)-(2.3) that the theory of linear elastic fracture mechanics predicts stress singularities at the crack-tip of order $r^{-1/2}$. This is, of course, physically not true and is the result of neglecting the plastic zone due to high local stresses in the vicinity of the crack-tip. In most cases involving brittle materials, however, the plastic zone is too small to be of much significance. Under such circumstances, although actual stresses and displacements differ locally in a very small region around the crack-tip from those obtained using Eqs. (2.1)-(2.3), the stress intensity factor K_I and K_{II} do provide a unique characterization for the stress and displacement fields which determines the onset of crack propagation.

In cases where significant amount of plastic deformation occurs, recourse to elastic-plastic fracture mechanics becomes necessary. In this respect, a number of fracture parameters, such as the *J*-integral and *COD*, have been proposed to determine the onset of crack growth. The theory of elastic-plastic fracture mechanics is beyond the

scope of the current work and will therefore not be discussed further.

2.2 The Bimaterial Interfacial Crack

With increasing use of advanced composite materials in structural applications, more and more attention has been paid to the study of bimaterial interface crack problems. Such problems were first investigated by Williams (1959), who discovered that the near-tip stresses and displacements behave in an oscillatory manner. Erdogan (1963) has studied the same problem and found that this oscillatory character is limited to an extremely small region, about 10^{-6} times the crack length. England (1965) considered the interface crack under loading of the crack faces and concluded that the solution is physically inadmissible since it predicts that the crack surfaces overlap, albeit in the very small region very near the crack-tip, in the order of 10^{-4} of the crack length. This problem was resolved by Comninou (1977) who solved the problem assuming contact of the interface at the crack-tip. However as was discussed in detail again by Rice (1988) and Comninou (1990) recently, the oscillatory field solutions may still be used to provide the characterising fracture parameters where the region of contact at the interface crack-tip is small, as is often the case. Using the complex variable technique of Muskhelishvili (1953) in conjunction with eigenfunction expansion method, Rice and Sih (1965) have obtained the explicit expressions for near-tip fields. A similar approach of analysis has also been followed in a more recent study by Hong and Stern (1978). The near-tip solutions are now presented below after some key variables are first defined.

Consider an arbitrary interface crack as shown in Figure 2.3, and let a local Cartesian coordinate system and a polar coordinate system be introduced with their origins at the crack-tip. The crack surfaces, represented by $\theta = -\pi$ and $\theta = \pi$ for material 1 and material 2 respectively, are assumed to be traction free. In such

problems, it is also convenient to define displacements and stresses using complex functions. Thus complex displacements v_α and complex stresses $\sigma_{\alpha r}$ and $\sigma_{\alpha\theta}$ ($\alpha = 1, 2$), where subscript α denotes material 1 when $\alpha = 1$ and material 2 when $\alpha = 2$, (see Figure 2.3), are introduced as follows:

$$v_\alpha = v_{\alpha r} + i v_{\alpha\theta} \quad (2.15)$$

$$\sigma_{\alpha r} = \sigma_{\alpha rr} + i \sigma_{\alpha r\theta} \quad (2.16)$$

$$\sigma_{\alpha\theta} = \sigma_{\alpha\theta\theta} - i \sigma_{\alpha r\theta} \quad (2.17)$$

In Eqs. (2.15)-(2.17), $i = \sqrt{-1}$; v_r and v_θ are the displacements in the r - and θ -directions, respectively; σ_{rr} , $\sigma_{r\theta}$ and $\sigma_{\theta\theta}$ are the stress components with respect to the local $r - \theta$ coordinate system. It is also necessary to introduce the complex stress intensity factor K as

$$K = K_I + i K_{II} \quad (2.18)$$

Employing the method of complex potentials (see Hong and Stern (1978)), the stress and displacement fields in the vicinity of the crack-tip can be shown to be as follows:

Stresses

$$\begin{aligned} \sigma_{1r} = & \frac{\cosh(\pi\epsilon)}{\sqrt{2\pi}(1+\gamma)} \{ \bar{K} r^{\lambda-1} [e^{i(\lambda-1)\theta} - \gamma e^{-i(1+\lambda)\theta}] \\ & + K r^{\bar{\lambda}-1} [\lambda e^{-i(1+\bar{\lambda})\theta} - (\bar{\lambda}-2)e^{i(1-\bar{\lambda})\theta}] \} + O(r^0) \end{aligned} \quad (2.19)$$

$$\begin{aligned} \sigma_{2r} = & \frac{\cosh(\pi\epsilon)}{\sqrt{2\pi}(1+\gamma)} \{ \bar{K} r^{\lambda-1} [\gamma e^{i(\lambda-1)\theta} - e^{-i(1+\lambda)\theta}] \\ & + \gamma K r^{\bar{\lambda}-1} [\lambda e^{-i(1+\bar{\lambda})\theta} - (\bar{\lambda}-2)e^{i(1-\bar{\lambda})\theta}] \} + O(r^0) \end{aligned} \quad (2.20)$$

$$\begin{aligned} \sigma_{1\theta} = & \frac{\cosh(\pi\epsilon)}{\sqrt{2\pi}(1+\gamma)} \{ \bar{K} r^{\lambda-1} [e^{i(\lambda-1)\theta} + \gamma e^{-i(1+\lambda)\theta}] \\ & + \bar{\lambda} K r^{\bar{\lambda}-1} [e^{-i(1+\bar{\lambda})\theta} - e^{i(1-\bar{\lambda})\theta}] \} + O(r^0) \end{aligned} \quad (2.21)$$

$$\begin{aligned} \sigma_{2\theta} = & \frac{\cosh(\pi\epsilon)}{\sqrt{2\pi}(1+\gamma)} \{ \bar{K} r^{\lambda-1} [\gamma e^{i(\lambda-1)\theta} + e^{-i(1+\lambda)\theta}] \\ & + \bar{\lambda} \gamma K r^{\bar{\lambda}-1} [e^{-i(1+\bar{\lambda})\theta} - e^{i(1-\bar{\lambda})\theta}] \} + O(r^0) \end{aligned} \quad (2.22)$$

Displacements

$$\begin{aligned} v_1 = & \frac{\cosh(\pi\epsilon)}{2\sqrt{2\pi}\mu_1(1+\gamma)\lambda} \{ \bar{K} r^{\lambda} [k_1 e^{i(\lambda-1)\theta} - \gamma e^{-i(1+\lambda)\theta}] \\ & + \lambda K r^{\bar{\lambda}} [e^{-i(1+\bar{\lambda})\theta} - e^{i(1-\bar{\lambda})\theta}] \} \end{aligned} \quad (2.23)$$

$$\begin{aligned} v_2 = & \frac{\cosh(\pi\epsilon)}{2\sqrt{2\pi}\mu_2(1+\gamma)\lambda} \{ \bar{K} r^{\lambda} [k_2 \gamma e^{i(\lambda-1)\theta} - e^{-i(1+\lambda)\theta}] \\ & + \lambda \gamma K r^{\bar{\lambda}} [e^{-i(1+\bar{\lambda})\theta} - e^{i(1-\bar{\lambda})\theta}] \} \end{aligned} \quad (2.24)$$

In Eqs. (2.19)-(2.24) the overbar denotes the complex conjugate, and

$$\lambda = 1/2 + i\epsilon \quad (2.25)$$

$$\epsilon = \frac{1}{2\pi} \ln \gamma \quad (2.26)$$

$$\gamma = \frac{\mu_1 + k_1 \mu_2}{\mu_2 + k_2 \mu_1} \quad (2.27)$$

$$k_\alpha = \begin{cases} 3 - 4\nu_\alpha, & \text{for plane strain} \\ (3 - \nu_\alpha)/(1 + \nu_\alpha), & \text{for plane stress} \end{cases} \quad (2.28)$$

in which μ_α and ν_α are the shear modulus and Poisson's ratio for material α ($\alpha = 1, 2$) respectively.

At the interface ahead of the crack, the near-tip stress distribution can be easily obtained by setting θ to be zero in Eq. (2.21) or (2.22). Thus

$$\sigma_{\theta\theta} = \frac{\cosh(\pi\epsilon)}{\sqrt{2\pi r}} [K_I \cos(\epsilon \ln r) - K_{II} \sin(\epsilon \ln r)] \quad (2.29)$$

$$\sigma_{r\theta} = \frac{\cosh(\pi\epsilon)}{\sqrt{2\pi r}} [K_I \sin(\epsilon \ln r) + K_{II} \cos(\epsilon \ln r)] \quad (2.30)$$

or alternatively,

$$(\sigma_{\theta\theta} + i\sigma_{r\theta})|_{\theta=0} = \frac{K r^{-i\epsilon} \cosh(\pi\epsilon)}{\sqrt{2\pi r}} \quad (2.31)$$

from which it is evident that although the stress fields are also of $r^{-1/2}$ singular, they are, unlike the near-tip stress fields for homogeneous materials, highly oscillatory as r approaches zero. Also exhibited in the above equation is that under no combinations of K_I and K_{II} will the tensile or shear stress field disappear. This implies that tensile or shear mode can not be separately defined for bimaterial interfacial cracks. Therefore K_I and K_{II} are not the stress intensity factors of classical tensile and shear modes respectively, although they may still be used as characterising parameters for the near-tip fields, see Rice (1988).

The complex stress intensity factor K can also be expressed as

$$K = K_0 e^{i\psi} \quad (2.32)$$

where

$$K_0 = |K| = \sqrt{K_I^2 + K_{II}^2} \quad (2.33)$$

and

$$\psi = \arctan(K_{II}/K_I) \quad (2.34)$$

It can be easily shown, see, e.g., Hong and Stern (1978), that the modulus K_0 of the complex stress intensity factor is related to the stresses as

$$K_0 = \frac{\sqrt{2\pi r}}{\cosh(\pi\epsilon)} \sqrt{\sigma_{\theta\theta}^2 + \sigma_{r\theta}^2} \quad (2.35)$$

and although K_I and K_{II} are oscillatory in form, K_0 is not. Furthermore, it has been shown that the strain energy release rate G is directly related to K_0 , as shown below, Malyshev and Salganik (1965),

$$G = \frac{1}{4} \left[\frac{1-\nu_1}{\mu_1} + \frac{1-\nu_2}{\mu_2} \right] K_0^2 \quad (2.36)$$

This leads to some authors to refer to K_0 , notionally, as the *overall stress intensity factor*. The combination of K_0 and ψ thus gives a full characterisation of the near-tip stress fields and they may be related to a suitable criterion for crack extension. For example, some recent studies on the fracture energy of interface cracks, see, e.g., Hutchinson et al (1989), and Charalambides et al (1989), have suggested that fracture may be characterised by a locus involving a critical value of G (hence K_0) and ψ .

Substituting $\theta = \pm\pi$ into Eqs. (2.23)-(2.24), the crack face displacements can be obtained as follows:

$$v_1|_{\theta=-\pi} = \frac{\cosh(\pi\epsilon)}{2\sqrt{2\pi}\mu_1(1+\gamma)\lambda} \bar{K} r^\lambda [-k_1 e^{-i\lambda\pi} + \gamma e^{i\lambda\pi}] \quad (2.37)$$

$$v_2|_{\theta=\pi} = \frac{\cosh(\pi\epsilon)}{2\sqrt{2\pi}\mu_2(1+\gamma)\lambda} \bar{K} r^\lambda [-k_2 \gamma e^{i\lambda\pi} + e^{-i\lambda\pi}] \quad (2.38)$$

from which K_0 can be alternatively written as, Tan and Gao(1990):

$$K_0 = \sqrt{\frac{2\pi}{r}} [(D_1 v_{1r} - D_2 v_{2r})^2 + (D_1 v_{1\theta} - D_2 v_{2\theta})^2]^{1/2} \quad (2.39)$$

The coefficients in the above equation are

$$D_1 = A_0 \frac{\mu_1}{k_1 e^{\pi\epsilon} + \gamma e^{-\pi\epsilon}} \quad (2.40)$$

$$D_2 = A_0 \frac{\mu_2}{k_2 \lambda e^{-\pi\epsilon} + e^{\pi\epsilon}} \quad (2.41)$$

$$A_0 = \frac{1+\gamma}{\cosh(\pi\epsilon)} (1/4 + \epsilon^2)^{1/2} \quad (2.42)$$

For the expression of the phase angle ψ , the definition of the complex relative crack face displacement Δv is introduced as:

$$\begin{aligned} \Delta v &= v_1|_{\theta=-\pi} - v_2|_{\theta=\pi} \\ &= \Delta v_r + i\Delta v_\theta \end{aligned} \quad (2.43)$$

where Δv_r and Δv_θ are the r -th and θ -th components of Δv , respectively, as shown in Figure 2.4. In terms of modulus $|\Delta v|$ and argument ϕ^* , Δv can alternatively be expressed as

$$\Delta v = |\Delta v| e^{i\phi^*} \quad (2.44)$$

It has been shown, see Smelser (1979), that the phase angle of the complex stress intensity factor K is related to the argument ϕ^* as below:

$$\psi = \epsilon \ln r - \arctan(2\epsilon) - \phi^* - \pi/2 \quad (2.45)$$

or if ϕ is introduced as

$$\phi = \arctan(\Delta v_r / \Delta v_\theta) \quad (2.46)$$

Eq. (2.45) can be simplified as

$$\psi = \epsilon \ln r - \arctan(2\epsilon) + \phi \quad (2.47)$$

The above expression for the phase angle is, unfortunately, scale-dependent, the significance of which has been discussed in detail by Rice (1988). A scale-independent phase angle ψ^* may be introduced, however, as follows

$$\psi^* = \epsilon \ln(r/h) - \arctan(2\epsilon) + \phi \quad (2.48)$$

where h is a characteristic physical dimension of the crack problem.

2.3 Closing Remarks

In this chapter the near-tip fields have been reviewed for both the crack in a homogeneous body and the bimaterial interface crack. For the latter type of crack the

complex stress intensity factor K is introduced as fracture characterising parameter for the oscillatory near-tip fields. This leads further to the introduction of modulus of K , K_0 , also referred to as the *overall stress intensity factor*, and the phase angle ψ . The fields as expressed above are for two dimensional crack problems. For cases in axisymmetry the respective expressions may be obtained from those corresponding to plane strain case above. They are not presented here to avoid repetition.

Chapter 3

The Use of the Boundary Element Method in Fracture Mechanics

3.1 Introduction

The boundary element method (BEM), or alternatively also called the boundary integral equation (BIE) method, has now been developed into an efficient tool for numerical stress analysis since it was first applied to treating potential problems by Jaswon (1963). Rizzo (1967) extended the formulation to two-dimensional elasticity and the method was subsequently used for solving crack problems by Cruse (1971,1974). Since then, crack problems in homogeneous bodies have been actively investigated using BEM by various researchers, see, e.g., Besuner (1977), Bui (1977), Cruse (1978,1979), Tan and Fenner (1979,1980), Smith and Mason (1982), Mukherjee and Banthia (1984), Cruse and Polch (1986), etc.

The use of the boundary element method to solve bimaterial interface crack problems has however been a more recent development due largely to the increasing use of composite materials in structural applications. The numerical treatment of such problems is relatively more difficult because of the highly oscillatory behaviour in the vicinity of the interface crack-tip and reported works using BEM remain fairly

limited in number. In this regard, Lee and Choi (1988) employed the conventional multi-region BEM formulation with extremely refined elements near the crack-tip. Yuuki et al (1987,1988) and Hasegawa (1988) used a special fundamental solution (Hetenyi's solution) in their BIE formulations. To obtain the fracture characterising parameters, extrapolation techniques were employed. Using a different approach, Tan and Gao (1990a,1990b,1991) carried out a series of investigations employing quarter-point crack-tip elements in conjunction with conventional multi-region BEM to calculate these parameters in a direct manner. Accurate results were shown to be obtained for a number of test problems even with relatively coarse meshes.

In this chapter, the direct formulation of boundary element method is first reviewed. Its application to linear elastic fracture mechanics, in which quarter-point crack-tip elements are introduced to simulate the stress fields near the crack-tip, is then introduced. The accuracy and efficiency of the BEM technique with quarter-point crack-tip elements are demonstrated by five examples, three of which involve bimaterial interface cracks. The indicial notation is employed throughout this and later chapters for convenience; where it is not employed, it will be indicated.

3.2 The Boundary Integral Equation for Elastostatics

The theoretical foundation of boundary integral equation (BIE) for elasticity is Betti's reciprocal work theorem, from which the BIE can be derived using the appropriate limiting process with some fundamental solutions. Considering an elastic body with shear modulus μ and Poisson's ratio ν as shown in Figure 3.1, the two dimensional BIE relating the displacements u_i and tractions t_i ($i = 1, 2$) on the boundary S can be written, using indicial notation, as:

$$\begin{aligned}
& C_{ji}(P)u_i(P) + \int_S u_i(Q)T_{ji}(P, Q)dS(Q) \\
= & \int_S [t_i(Q) - n_i(Q)\phi(Q)]U_{ji}(P, Q)dS(Q) \\
& - \int_S \mu_0[n_j(2 \ln r - 1) + 2r_{,j} \frac{dr}{dn}] \phi(Q)dS(Q) \\
& + \int_S \mu_0[r r_{,j} (2 \ln r - 1)] \frac{d\phi(Q)}{dn} dS(Q) \\
& - \int_S \mu_0 k_0 n_j(Q) [r^2 (\ln r - 1)] dS(Q)
\end{aligned} \tag{3.1}$$

where r is the distance between point P and Q on the boundary; n_i ($i = 1, 2$) are the components of the outward normal at point Q ; and $U_{ji}(P, Q)$ and $T_{ji}(P, Q)$ ($i, j = 1, 2$) are the Kelvin fundamental solutions. They may be expressed as:

$$U_{ji}(P, Q) = \frac{1}{8\pi\mu(1-\nu)} [(3-4\nu)\delta_{ij} \ln \frac{1}{r} + r_{,i} r_{,j}] \tag{3.2}$$

$$T_{ji}(P, Q) = -\frac{(1-2\nu)}{4\pi(1-\nu)} \frac{1}{r} \left\{ \frac{dr}{dn} [\delta_{ij} + \frac{2}{1-2\nu} r_{,i} r_{,j}] - r_{,i} n_j + r_{,j} n_i \right\} \tag{3.3}$$

respectively, where δ_{ij} is the Kronecker delta. The coefficient in Eq. (3.1) is

$$C_{ij}(P) = \lim_{\epsilon \rightarrow 0} \int_{S_\epsilon} T_{ij}(P, Q)dS(Q) \tag{3.4}$$

which, in the case of the point P lying on a smooth part of the surface S , becomes

$$C_{ij}(P) = \frac{1}{2} \delta_{ij} \tag{3.5}$$

Also in Eq. (3.1)

$$\mu_0 = \frac{(1-2\nu)}{16\pi(1-\nu)\mu} \tag{3.6}$$

and $\phi(Q)$ is a potential satisfying

$$f_i - \frac{2\mu}{1-2\nu} \alpha' \theta_{,i} = -\phi_{,i} \quad (3.7)$$

such that

$$\phi_{,jj} = k_0, \text{ a constant} \quad (3.8)$$

with f_i and θ in Eq. (3.7) being the body force and temperature change respectively. Further more,

$$\alpha' = \begin{cases} \alpha, & \text{for plane stress} \\ \alpha(1+\nu), & \text{for plane strain} \end{cases} \quad (3.9)$$

where α is the coefficient of thermal expansion. If the body force is due to the gravity in the x_2 -direction, ϕ and k_0 can be explicitly expressed as (see, e.g. Tan(1987))

$$\phi = -\rho g x_2 + \frac{2\mu}{1-2\nu} \alpha' \theta \quad (3.10)$$

$$k_0 = 0 \quad (3.11)$$

where ρ is the density of the material. For a rotating elastic body with angular velocity ω , then

$$\phi = -\frac{1}{2} \rho \omega^2 x_i x_i + \frac{2\mu}{1-2\nu} \alpha' \theta \quad (3.12)$$

$$k_0 = -2\rho\omega^2 \quad (3.13)$$

For the expressions of k_0 in (3.11) and (3.13), steady state of temperature distribution has been assumed so that $\theta_{,jj} = 0$.

Once Eq. (3.1) has been solved, all the boundary values of displacements and tractions will be known. If the displacements and stresses at any particular point at the interior of the domain are required, use may then be made of Somigliana's identities which relate them to the boundary values. Details of this will not be discussed here; for them the reader is referred to, e.g. Tan (1987).

3.3 Numerical Solution of the BIE

To solve Eq. (3.1), the boundary is divided into elements, each having a number of nodal points. The variations of the displacements and tractions on these boundary elements may then be approximated by interpolation of their nodal values. The present work employs the isoparametric representations of geometry, displacements and tractions, using quadratic shape functions. Therefore, each element has three nodal points (see Figure 3.2) and

$$x_i(\xi) = \sum_{c=1}^3 N^c(\xi) x_i^c \quad (3.14)$$

$$u_i(\xi) = \sum_{c=1}^3 N^c(\xi) u_i^c \quad (3.15)$$

$$t_i(\xi) = \sum_{c=1}^3 N^c(\xi) t_i^c \quad (3.16)$$

where ξ is the local or intrinsic coordinate; the superscript c represents a specific node in each element ($c = 1, 3$); and $N_i^c(\xi)$ are the shape functions defined as

$$\begin{cases} N^1(\xi) = -\xi(1 - \xi)/2 \\ N^2(\xi) = 1 - \xi^2 \\ N^3(\xi) = \xi(1 + \xi)/2 \end{cases} \quad (3.17)$$

Employing M elements to approximate the boundary, the BIE, Eq. (3.1), can then be discretized into the following set of algebraic equations:

$$\begin{aligned}
& C_{ji}(P^a)u_i(P^a) + \sum_{b=1}^M \sum_{c=1}^3 u_i(P^{d(b,c)}) \int_{-1}^1 T_{ji}(P^a, Q(\xi)) N^c(\xi) |J(\xi)| d\xi \\
= & \sum_{b=1}^M \sum_{c=1}^3 \{ \Phi_i(P^{d(b,c)}) \int_{-1}^1 U_{ji}(P^a, Q(\xi)) N^c(\xi) |J(\xi)| d\xi \\
& - \phi(P^{d(b,c)}) \int_{-1}^1 A_j(P^a, Q(\xi)) N^c(\xi) |J(\xi)| d\xi \\
& + \Omega(P^{d(b,c)}) \int_{-1}^1 B_j(P^a, Q(\xi)) N^c(\xi) |J(\xi)| d\xi \} \\
& - \sum_{b=1}^M \int_{-1}^1 H_j(P^a, Q(\xi)) |J(\xi)| d\xi; \\
& P^a = 1, N
\end{aligned} \tag{3.18}$$

where N is the total number of the nodes on the boundary S ; $J(\xi)$ is the Jacobian of transformation; P^a is the a -th node of the mesh, and $P^{d(b,c)}$ denotes the c -th node of the b -th element. Also,

$$\Omega(Q) = \frac{d\phi(Q)}{dn} \tag{3.19}$$

$$\Phi_j(Q) = t_j(Q) - n_j(Q)\phi(Q) \tag{3.20}$$

$$A_j(P, Q) = \mu_0[n_j(2 \ln r - 1) + 2r_{,j} \frac{dr}{dn}] \tag{3.21}$$

$$B_j(P, Q) = \mu_0[r r_{,j} (2 \ln r - 1)] \tag{3.22}$$

$$H_j(P, Q) = \mu_0 k_0 n_j(Q) [r^2 (\ln r - 1)] \tag{3.23}$$

The integrations in Eq. (3.18) are numerically evaluated by Gaussian quadrature, and the resultant linear algebraic equations can be solved using Gaussian elimination.

When applying Eq. (3.18) to solve crack problems, the BIE will degenerate if the crack surfaces are treated as internal boundaries, so that no unique solution to the problems can be obtained, see Cruse (1978,1988). In cases where the load and geometry are symmetric about the crack, this problem can be resolved by considering only one-half or one-quarter of the domain with the crack lying along one of the modelled boundaries (see Figure 3.3). For a general crack problem, however, the multi-region BIE technique has to be employed; this will now be briefly discussed.

Consider two elastic bodies ($\omega_1 = 1, 2$) joined along mutual surfaces $\bar{S}$ with zero body force(s) and thermal effects. The BIE for each region is given by

$$C_{ij}^{\omega_1}(P)u_j^{\omega_1}(P) + \int_{S^{\omega_1}} T_{ij}^{\omega_1}(P, Q)u_j^{\omega_1}(Q)dS = \int_{S^{\omega_1}} U_{ij}^{\omega_1}(P, Q)t_j^{\omega_1}(Q)dS \quad (3.24)$$

where the superscript ω_1 here does not imply summation. The boundary conditions are applied separately on $S^{\omega_1} - \bar{S}$. At the interface which joins the two subregions together, additional conditions are imposed as

$$\begin{cases} u_j^1(Q) = u_j^2(Q) \\ t_j^1(Q) = -t_j^2(Q) \end{cases} \quad (3.25)$$

Equation (3.24), the multi-region BIE, can be solved numerically in conjunction with Eq. (3.25) after discretization. The above discussion about multi-region BIE can be generalized to treat problems with more than two subregions, with or without body force(s).

When modelling a general crack problem by multi-region BIE, a line or surface passing through the crack is chosen to divide the solution domain into two subregions, see Figure 3.4. The crack faces are then treated as free boundaries in the two subregions. An additional advantage of the multi-region BIE method is that problems with several different material regions may now be solved, with or without cracks.

C-

ck-
ilts
on-
ity
po-
To
ints
ical
line

ints
i, as
The
see,
it of
ions
-1/2
tion
c-tip
ll be

the

3.4 Application of BEM to Linear Elastic Fracture Mechanics

3.4.1 Quarter-point Element

Once the nodal displacements and tractions are obtained in the vicinity of the crack-tip, the stress intensity factor(s) can be obtained by comparing these numerical results with those predicted by the near-tip field theory discussed in Chapter 2. In the conventional BIE method, the classical stress and displacement variations in the vicinity of the crack-tip are not directly introduced in the numerical treatment and extrapolation techniques have to be employed to determine the stress intensity factor(s). To do this, numerical results for the displacements (or stresses) at several nodal points close to the crack-tip are fitted into a straight line with correlation to the classical field solution. The stress intensity factor is then obtained by extrapolation of the line to $r=0$, see Figure 3.5.

To achieve better accuracy of the stress intensity factor solution, the mid-points of the elements adjoining the crack-tip node may be shifted to the quarter-points, as shown in Figure 3.6. This follows the development in the finite element method. The change introduces the proper variation of the displacements along the element, see, e.g., Henshell and Shaw (1975), that is, they are proportional to the square root of the distance from the crack-tip. However, because the displacements and tractions are independently represented in BEM, the tractions are not of the proper $r^{-1/2}$ singularity at the crack-tip. But this can be easily rectified by a simple modification of the shape functions associated with the tractions for the quarter-point crack-tip element (see, Cruse and Wilson (1978), Martinez and Dominguez (1984)) as will be shown below.

With respect to Figure 3.6, the geometry, displacements and tractions of the

quarter-point crack-tip elements can be represented by

$$r = \sum_{c=1}^3 N^c(\xi) r^c \quad (3.26)$$

$$u_i = \sum_{c=1}^3 N^c(\xi) u_i^c \quad (3.27)$$

$$t_i = \sum_{c=1}^3 N^c(\xi) t_i^c \quad (3.28)$$

where $i = 1, 2$ and $c = 1, 3$. $N^c(\xi)$ are quadratic shape functions expressed in (3.17), and

$$\begin{cases} r^1 = 0 \\ r^2 = l/4 \\ r^3 = l \end{cases} \quad (3.29)$$

Substitution of (3.17) and (3.29) into (3.26) results in

$$r = \frac{1}{4}(\xi + 1)^2 l \quad (3.30)$$

or

$$\xi = 2\sqrt{\frac{r}{l}} - 1 \quad (3.31)$$

Substituting these into (3.27) and (3.28), leads to

$$u_i = A_i^1 + A_i^2 \sqrt{\frac{r}{l}} + A_i^3 \left(\frac{r}{l}\right) \quad (3.32)$$

$$t_i = B_i^1 + B_i^2 \sqrt{\frac{r}{l}} + B_i^3 \left(\frac{r}{l}\right) \quad (3.33)$$

where

$$\begin{cases} A_i^1 &= u_i^1 \\ A_i^2 &= (-3u_i^3 + 4u_i^2 - u_i^3) \\ A_i^3 &= (2u_i^1 - 4u_i^2 + 2u_i^3) \end{cases} \quad (3.34)$$

and

$$\begin{cases} B_i^1 &= t_i^1 \\ B_i^2 &= (-3t_i^1 + 4t_i^2 - t_i^3) \\ B_i^3 &= (2t_i^1 - 4t_i^2 + 2t_i^3) \end{cases} \quad (3.35)$$

It is evident from (3.32) that the proper displacement variations in the vicinity of the crack-tip are already achieved. To achieve the proper traction singularity of order $r^{-1/2}$ at the crack-tip, a simple way is to introduce the special shape functions, defined as

$$\bar{N}^c(\xi) = N^c(\xi) \sqrt{\frac{l}{r}} \quad (3.36)$$

for the traction variations on the crack-tip element. Thus (3.28) changes into

$$\begin{aligned} t_i &= \sum_{c=1}^3 \bar{N}^c(\xi) \bar{t}_i^c \\ &= \sum_{c=1}^3 N^c(\xi) \sqrt{\frac{l}{r}} \bar{t}_i^c \end{aligned} \quad (3.37)$$

where the traction coefficients $\bar{t}_i^c$ can be related to the nodal tractions t_i^c as

$$\begin{cases} \bar{t}_i^3 &= t_i^3 \\ \bar{t}_i^2 &= \frac{1}{2} t_i^2 \\ \bar{t}_i^1 &= \lim_{r \rightarrow 0} t_i^1 \sqrt{r/l} \end{cases} \quad (3.38)$$

It can be shown from (3.31) and (3.37) that

$$\begin{aligned} t_i &= [\bar{B}_i^1 + \bar{B}_i^2 \sqrt{\frac{r}{l}} + \bar{B}_i^3 (\frac{r}{l})] / \sqrt{\frac{r}{l}} \\ &= \bar{B}_i^1 \sqrt{\frac{l}{r}} + \bar{B}_i^2 + \bar{B}_i^3 \sqrt{\frac{r}{l}} \end{aligned} \quad (3.39)$$

where

$$\begin{cases} \bar{B}_i^1 = \bar{t}_i^1 \\ \bar{B}_i^2 = (-3\bar{t}_i^1 + 4\bar{t}_i^2 - \bar{t}_i^3) \\ \bar{B}_i^3 = (2\bar{t}_i^1 - 4\bar{t}_i^2 + 2\bar{t}_i^3) \end{cases} \quad (3.40)$$

Considering that r/l is small in value, (3.32) and (3.39) can be reduced by neglecting terms of higher order. Therefore,

$$\begin{aligned} u_i &= A_i^1 + A_i^2 \sqrt{\frac{r}{l}} \\ &= A_i^1 + (-3u_i^1 + 4u_i^2 - u_i^3) \sqrt{\frac{r}{l}} \end{aligned} \quad (3.41)$$

$$t_i = \bar{B}_i^1 \sqrt{\frac{l}{r}} = \bar{t}_i^1 \sqrt{\frac{l}{r}} \quad (3.42)$$

where the displacements and tractions are then both properly represented.

3.4.2 Determination of Fracture Characterising Parameters

Cracks Embedded in Homogeneous Bodies

The stress intensity factors for cracks embedded in homogeneous bodies can be obtained by equating the displacements expressed in (3.41) with the corresponding

analytical variations presented in (2.4) and (2.5), respectively. In this way, a *displacement formula* for calculating the stress intensity factors from the nodal values of the displacements at the crack-tip element can be derived. Similarly, if the computed tractions are equated to the classical stress distributions, a *traction formula* can also be obtained. Details of these have been presented by Martinez and Dominguez (1984) for cracks in homogeneous bodies. With the reference to Figure 3.7, these formulae may be expressed as follows with respect to the local crack-tip co-ordinate system.

Displacement Formula

$$K_I = \frac{\mu}{k+1} \sqrt{\frac{2\pi}{l}} [4(u_2^B - u_2^D) + (u_2^E - u_2^C)] \quad (3.43)$$

$$K_{II} = \frac{\mu}{k+1} \sqrt{\frac{2\pi}{l}} [4(u_1^B - u_1^D) + (u_1^E - u_1^C)] \quad (3.44)$$

Traction Formula

$$K_I = \bar{t}_2^A \sqrt{2\pi l} \quad (3.45)$$

$$K_{II} = \bar{t}_1^A \sqrt{2\pi l} \quad (3.46)$$

Bimaterial Interface Crack

The treatment of bimaterial interface cracks using BEM is a very recent development. More details of the derivation of the corresponding formulae for the fracture characterising parameters are thus provided here, following Tan and Gao (1990a, 1990b).

In the previous chapter, the formula to calculate the overall stress intensity factor K_0 from the crack face displacements $v_{\alpha r}$ and $v_{\alpha \theta}$ ($\alpha = 1, 2$) has been provided, i.e. Eq. (2.39). Using Eq. (3.41), these displacements can be expressed in terms of the nodal displacements of the quarter-point crack-tip elements at the crack surfaces, see Figure 3.7. Considering only the characteristic $\sqrt{r/l}$ term in (3.41), they are

$$v_{1r} = (-3u_1^A + 4u_1^D - u_1^E)\sqrt{\frac{r}{l}} \quad (3.47)$$

$$v_{2r} = (-3u_1^A + 4u_1^B - u_1^C)\sqrt{\frac{r}{l}} \quad (3.48)$$

$$v_{1\theta} = (-3u_2^A + 4u_2^D - u_2^E)\sqrt{\frac{r}{l}} \quad (3.49)$$

$$v_{2\theta} = (-3u_2^A + 4u_2^B - u_2^C)\sqrt{\frac{r}{l}} \quad (3.50)$$

Substitution of the above expressions for the crack face displacements into Eq. (2.39) may lead to the *displacement formula* for calculating the overall stress intensity factors K_0 from the nodal crack face displacements. Similarly, the *traction formula* for calculating K_0 can be obtained if the traction representation over the quarter-point element ahead of the crack-tip, Eq. (3.42), are equated to Eq. (2.35). They are presented as follows:

Displacement Formula

$$K_0 = \sqrt{\frac{2\pi}{l}}(W^2 + V^2)^{\frac{1}{2}} \quad (3.51)$$

where

$$W = D_1[-u_1^E + 4u_1^D - 3u_1^A] - D_2[-u_1^C + 4u_1^B - 3u_1^A] \quad (3.52)$$

$$V = D_1[-u_2^E + 4u_2^D - 3u_2^A] - D_2[-u_2^C + 4u_2^B - 3u_2^A] \quad (3.53)$$

D_1 and D_2 being constants (see (2.40) and (2.41)).

Traction Formula

$$K_0 = \frac{\sqrt{2\pi l}}{\cosh(\pi\epsilon)} [(\bar{t}_1^A)^2 + (\bar{t}_2^A)^2]^{\frac{1}{2}} \quad (3.54)$$

Note that in the above equations the stress intensity factors are expressed in terms of the computed nodal displacements or traction coefficients $\bar{t}_i^A$.

To determine the characteristic phase angle ψ^* for bimaterial interface crack Eq. (2.48) is used. Numerical experiments by Tan and Gao (1990a,1990b, 1991) have shown that good estimates of solutions can be obtained if it is calculated using (2.48) at $r/l = 0.5$ in two dimensions, and $r/l = 0.09$ in axisymmetry. Thus in the present work ψ^* is calculated at these locations in the respective analyses.

3.5 Examples

Five problems were treated to demonstrate the efficiency of the boundary element method and the veracity of the computer program for the BEM computations. They are relatively simple problems with available analytical solutions, among which three involve bimaterial interface cracks.

In the numerical treatment of all these test problems, only three elements were used to model the crack face, whereby the elements adjacent to the quarter-point crack-tip elements had length $2l$, l being the length of the crack-tip elements. The stress intensity factors were computed from the nodal values of the crack-tip elements using both displacement and traction formulae, i.e. Eqs. (3.43)-(3.44) and

Eqs. (3.45)-(3.46) respectively for cracks in homogeneous bodies, or Eqs. (3.51) and (3.54) respectively for bimaterial interface cracks. The effects of the crack-tip element length l to the accuracy of the stress intensity factor results were investigated. For the bimaterial interface crack problems, the variation of the shear modulus ratios of material 2 to material 1 were also considered. Plane strain conditions were assumed throughout.

3.5.1 Infinite Plate with a Central Crack

Figure 3.8 shows an infinite plate with centrally located crack of length $2a$, subject to remote tension σ . The analytical solution of the stress intensity factor is $K_I = \sigma\sqrt{\pi a}$, or $K_I/\bar{K} = 1$ in non-dimensional form, where $\bar{K} = \sigma\sqrt{\pi a}$. For the numerical analysis a plate of finite width was considered instead, with the width and height both being 40 times the crack length $2a$. Only one quarter of the plate was treated, advantage being taken of symmetry. Figure 3.9 shows the typical boundary element mesh. The numerical results of the normalised stress intensity factor $K_I/\bar{K}$ are listed in Table 3.1, in which the l/a ratio was taken to be from 0.03 to 0.3. It is seen that the results obtained using the traction formula are more accurate, within 2% in error for all l/a ratios. Their accuracy is also less sensitive to the relative length of the crack-tip element.

3.5.2 Plate of Finite Width with a Single Edge Crack

The crack of length a is located at the edge of a plate with width W , and the plate is subject to vertical uniform loading σ at its remote ends, as shown in Figure 3.10. The analytical solution of the stress intensity factor to this problem has been presented by Brown and Srawley (1966) who used a modified mapping collocation (MMC) technique, as

$$\frac{K_I}{\bar{K}} = 1.12 - 0.23\left(\frac{a}{W}\right) + 10.6\left(\frac{a}{W}\right)^2 - 21.7\left(\frac{a}{W}\right)^3 + 30.4\left(\frac{a}{W}\right)^4 \quad (3.55)$$

where $\bar{K} = \sigma\sqrt{\pi a}$. For the BIE analysis of this problem the width W was taken to be $4a$ and the length of the plate was taken to be $10a$. The normalised stress intensity factor, according to (3.55), is then

$$\frac{K_I}{\bar{K}} = 1.5047 \quad (3.56)$$

By virtue of symmetry, only half of the physical domain was treated, and the boundary element mesh is as shown in Figure 3.11. The numerical solution of the normalised stress intensity factor $K_I/\bar{K}$ are listed in Table 3.2 with the various l/a ratios considered. They are in excellent agreement with the MMC solutions above, with errors of less than 1% generally.

3.5.3 Infinite Plate with an Interface Straight Crack

The physical problem is shown in Figure 3.12, where an interface straight crack of length $2a$ is lodged between two semi-infinite dissimilar materials subject to remote normal stresses. The applied horizontal stress $(\sigma_x)_{II}^\infty$ is related to $(\sigma_x)_I^\infty$ and $(\sigma_y)^\infty$ by:

$$(\sigma_x)_{II}^\infty = \frac{E_2}{E_1}(\sigma_x)_I^\infty + \left[\nu_2 - \frac{E_2}{E_1}\nu_1\right](\sigma_y)^\infty \quad (3.57)$$

that strain continuity can be satisfied along the bimaterial interface. The analytical solution for the complex stress intensity factor is as follows (Rice and Sih (1965)):

$$K = (\sigma_y)^\infty \sqrt{\pi a} \{ [\cos(\epsilon \ln 2a) + 2\epsilon \sin(\epsilon \ln 2a)] + i[\sin(\epsilon \ln 2a) - 2\epsilon \cos(\epsilon \ln 2a)] \} / \cosh(\pi\epsilon) \quad (3.58)$$

where ϵ is the bimaterial constant defined in Eq. (2.26). From (3.58), it can be shown that

$$K_0 = |K| = \frac{(\sigma_y)^\infty}{\cosh(\pi\epsilon)} \sqrt{\pi a(1 + 4\epsilon^2)} \quad (3.59)$$

and

$$\psi = \arctan\left(\frac{K_{II}}{K_I}\right) = \epsilon \ln 2a - \arctan(2\epsilon) \quad (3.60)$$

or in a non-dimensional form

$$\psi^* = \psi - \epsilon \ln a = \epsilon \ln 2 - \arctan(2\epsilon) \quad (3.61)$$

with a being the characteristic length for the problem.

In the numerical treatment, a bimaterial plate of finite dimensions was considered instead, both the width and height being 30 times the crack length $2a$. By virtue of symmetry, only half of the physical domain was modelled, and a typical BIE mesh is shown in Figure 3.13. A range of shear modulus ratio, μ_2/μ_1 , was considered; they were 1, 5, 20, 100. The results in terms of the normalised stress intensity factor $K_0/\bar{K}$, where $\bar{K} = (\sigma_y)^\infty \sqrt{\pi a}$, and the characteristic phase angle ψ^* are listed in Table 3.3a and Table 3.3b, respectively, together with the corresponding analytical results. All numerical results of the stress intensity factor were accurate to within 5%, but with the results obtained using traction formula having higher solution accuracy generally. It can also be seen in Table 3.3a that the l/a ratio which would give a given accuracy of the stress intensity factor solution decreased with the increase of the μ_2/μ_1 ratio. As for the numerical results of the phase angle ψ^* they were all within 5% error for all the l/a and μ_2/μ_1 ratios considered (Table 3.3b).

3.5.4 Inclusion Problem with an Interface Arc Crack

Figure 3.14 shows a circular inclusion of radius a embedded in an infinite body which is subjected to uniform tension σ at remote ends, with a bimaterial interface arc crack that spans an angle of 2θ . The analytical solution for the complex stress intensity factor has been given by Perlman and Sih (1967), and it may be expressed as

$$K = \frac{2i\sigma\sqrt{\pi a \sin \theta} a^{i\epsilon} F_1(i + 2\epsilon) e^{i(\theta+\pi)} e^{i\epsilon \ln 2 \sin \theta} e^{-i\theta/2}}{(1 + \gamma) (F_2 - F_3 N_1 e^{-2\epsilon\theta})} \quad (3.62)$$

in which γ and ϵ are the bimaterial constants introduced in (2.27) and (2.26) respectively, and

$$F_1 = \mu_1(1 + k_2)[\mu_1(1 + k_2) + \mu_2(1 + k_1)] \quad (3.63)$$

$$F_2 = (\mu_1 + \mu_2 k_1)[\mu_2(1 + k_1) + 2\mu_1(1 + k_2)] \quad (3.64)$$

$$F_3 = \mu_2(1 + k_1)(\mu_2 + \mu_1 k_2) \quad (3.65)$$

$$N_1 = \cos \theta - 2\epsilon \sin \theta \quad (3.66)$$

From (3.62) the overall stress intensity factor K_0 and the characteristic phase angle ψ^* can be obtained as

$$K_0 = \frac{2\sigma\sqrt{\pi a \sin \theta} F_1 \sqrt{1 + 4\epsilon^2} e^{i(\theta+\pi)}}{(1 + \gamma) (F_2 - F_3 N_1 e^{-2\epsilon\theta})} \quad (3.67)$$

$$\psi^* = \frac{\pi}{2} + \arctan\left(\frac{1}{2\epsilon}\right) + \epsilon \ln(2 \sin \theta) - \frac{\theta}{2} \quad (3.68)$$

In the BIE analysis, the plate treated was a square with the width and height 20 times the diameter $2a$, and θ was taken to be 30° . Only one-half of the plate was

considered, taking advantage of symmetry. The boundary element mesh is shown in Figure 3.15, where a total number of 36 elements was employed.

The numerical results are listed in Table 3.4a and Table 3.4b for the stress intensity factors and the phase angle respectively, together with the corresponding analytical solutions and the percentage errors. The relative crack size θ_c/θ , where θ_c is the angular span of the crack-tip element, was taken to be 0.025, 0.05 and 0.10. The normalised stress intensity factors, $K_0/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi a}$, obtained from the BIE analysis can be seen to be in good agreement with the analytical prediction when the μ_2/μ_1 ratios are greater than 1, the errors being limited to within about 3%, irrespective of which formula (traction or displacement) was used. For the μ_2/μ_1 ratios less than 1, however, it seems difficult to obtain numerical results with reasonable accuracy, the error reaching as high as 24.3% when $\mu_2/\mu_1 = 1/100$. This is due largely to the small absolute values of K_0 when μ_2/μ_1 becomes smaller and smaller. However, the numerical results of the phase angle ψ^* remained in good agreement with the analytical prediction even when $\mu_2/\mu_1 < 1$, and they were found to be relatively more insensitive to the relative size of the crack-tip element θ_c/θ than when $\mu_2/\mu_1 > 1$, as shown in Table 3.4b.

3.5.5 Infinite Body with a Penny-shaped Interface Crack

Figure 3.16 shows the diametrical plane of the axisymmetric problem, where the penny-shaped crack of diameter $2a$ is located between two semi-infinite dissimilar materials and is subject to internal pressure p . The analytical solution to the complex stress intensity factor has been provided by Kassir and Bregman (1972), which may be written as follows:

$$K = 2p\sqrt{a}(2a)^{i\epsilon} \frac{\Gamma(2 + i\epsilon)}{\Gamma(\frac{1}{2} + i\epsilon)} \quad (3.69)$$

where Γ is the special Gamma function and ϵ is the bimaterial constant described previously. The overall stress intensity factor K_0 and the characteristic phase angle ψ^* can be determined easily to be

$$K_0 = 2p\sqrt{a} \left| \frac{\Gamma(2 + i\epsilon)}{\Gamma(\frac{1}{2} + i\epsilon)} \right| \quad (3.70)$$

and

$$\psi^* = \arg(K) - \epsilon \ln a \quad (3.71)$$

respectively.

For the BIE calculation a finite cylinder was considered, with both the radius of the cylinder and the height of each material being twenty times the radius of the penny-shaped crack. Figure 3.17 shows the typical mesh discretisation with a total of 32 boundary elements employed. The numerical results of the normalised overall stress intensity factors $K_0/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi a}$, and the phase angle ψ^* are listed in Table 3.5a and Table 3.5b, respectively. It can be seen that the numerical results are in good agreement with the analytical prediction, the percentage error being limited to within 4% for the stress intensity factor, and 3% for the characteristic phase angle, for all the l/a and μ_2/μ_1 ratios considered. The effect of the shear modulus ratio μ_2/μ_1 to the solution accuracy is found to be insignificant in this case, and, once again, the results obtained using traction formula are more insensitive to the relative crack size.

3.5.6 Further Remarks

In this section, five test problems have been treated using the BEM with quarter-point crack-tip elements. The stress intensity factors have been calculated from the nodal

displacement or traction values. They have been found to be very accurate even with relatively coarse mesh designs. The traction formulae have been found generally to provide more accurate numerical results and also to be more insensitive to the size of the crack-tip elements. All the results presented have been obtained with three crack face elements in the BEM mesh. Meshes with four crack face elements have also been used, but the accuracies of the numerical results were very close to those shown.

3.6 Closing Remarks

In this chapter a review of the conventional multi-region BEM with quarter-point crack-tip elements has been presented. The displacement and traction formulae used for calculating the fracture characterising parameters directly from the numerical BEM results on the crack-tip elements have also been introduced. The accuracy and efficiency of the technique have been tested with five examples, including three bimaterial interface crack problems.

Chapter 4

Two Dimensional Fracture Analysis for Cracks at Inclusions

Fiber and particulate reinforced composite materials are increasingly being used for structural applications. In the micromechanics of these materials, they may often be modelled as two dimensional and axisymmetric inclusion problems, respectively, in simple geometric and load conditions. To this end, the mismatch of mechanical properties between the inclusion and the matrix plays a key role in influencing the overall material toughness of the composite structure, see, e.g., Evans and Faber (1984), Bao and Hui (1989). Also, if a difference in the thermal expansion coefficients of the two materials exists, it may lead to the formation of microcracks at, for example, the interface between the inclusion and the matrix. This can happen when the composite is expected to work in a environment of thermal cycling, or during thermal processing of the material. In both cases, the temperature change results in high residual stresses at locations around the interface, with implications for crack growth there if flaws or imperfect bonding exists. In the analysis of these inclusion crack problems, the boundary element method has been shown to be an efficient and suitable numerical tool, see, e.g. Tan and Gao (1990b), Gao and Tan (1991).

In this chapter three two-dimensional elliptical inclusion crack problems subjected to either mechanical or thermal load are considered using the boundary element method discussed previously. The shape of the elliptical inclusion is characterized by the ratio of the two semi-axis, c/a , which was taken to range from 1/3 to 3. A range of crack sizes was studied and, for a given crack configuration, the effects of the mismatch of material properties between the inclusion (material 2) and the matrix (material 1) were also investigated. To this end, the ratios of the shear modulus of the inclusion to that of the matrix, μ_2/μ_1 , were taken to be 1/100, 1/20, 1/10, 1/5, 1, 5, 10, 20, 100, for both load cases. Poisson's ratio was taken to be 0.3 throughout however, and plane strain conditions were assumed. In cases where thermal cooling was involved, the ratio of thermal expansion coefficient between the inclusion and the matrix, α_2/α_1 , was taken to be 10.0. The results of the stress intensity factors for other thermal ratios can be obtained by simple linear interpolation between zero values when the ratio is unity, and the corresponding values obtained here.

In the numerical models employed, the infinite matrix was represented as a square domain with side lengths twenty times the length of the horizontal axis of the inclusion, as will be shown later. Quarter-point crack-tip elements were used in all the analysis, and both the displacement and traction formulae presented in the previous chapter were used for evaluating the stress intensity factors. It was found that the deviations of the stress intensity factors produced by these formulae were generally less than 2 percent, and hence only the traction formula results are presented.

For all the problems considered, the stress intensity factor results of mechanical loading are shown plotted while those for thermal loading are tabulated. It should also be mentioned that some of the numerical results for shear modulus ratios of the inclusion to the matrix greater than 1, have been presented by Gao and Tan (1990) for mechanical loading. But for completeness, their results are plotted together with those obtained from the present investigation.

4.1 2D Problem I: Crack which has completely penetrated an inclusion

Figure 4.1 shows a crack of length $2b$ which has completely penetrated the elliptical inclusion along its axis, with the two crack-tips located in the matrix, symmetric about the inclusion. A range of crack sizes was treated, namely, $b/c = 1.05$ to 1.8 . For the BEM analysis of this problem, only one quarter of the physical solution domain was modelled, advantage being taken of the planes of symmetry. A typical BIE mesh is shown in Figure 4.2, where a total of 30 elements were used.

4.1.1 Mechanical Load

The matrix is subjected to remote uniform tension σ in the direction perpendicular to the plane of the crack. The results of the normalised stress intensity factors at the crack-tip $K_I/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi b}$, are plotted in Figs. 4.3-4.7 against the shear modulus ratio μ_2/μ_1 , for the different relative crack sizes, b/c , and the elliptical inclusion semi-axis ratios c/a , treated. It can be seen that given a c/a ratio, the numerical stress intensity factors increase fairly rapidly with the shear modulus ratio μ_2/μ_1 , particularly for smaller relative crack sizes b/c , reflecting the stronger influence of the inclusion. For larger b/c ratios, however, the results are not as sensitive to the change in the μ_2/μ_1 ratio, being close to unity for all the c/a ratios considered. Also, for this problem with a completely penetrating crack, the problem reduces to that of a crack in an infinite homogeneous body when materials 1 and 2 are taken to be identical. Under the remote tension load, the accuracy of the numerical stress intensity factor solutions obtained was checked and found to be in excellent agreement with the analytical prediction, with error of less than one percent in general. There are also obvious differences in the numerical results of the normalised stress intensity

factor for different c/a ratios. For example, the variations of the stress intensity factor results with b/c and μ_2/μ_1 ratios are limited to an increasingly smaller range as the ratio c/a gets larger. As for the effects of the relative crack size b/c , the stress intensity factors increase with it when the shear modulus ratio μ_2/μ_1 is less than 1; but the reverse is true when μ_2/μ_1 is greater than 1. For the limiting case when the shear modulus ratio approaches zero, this problem reduces to that of symmetric smaller cracks emanating from an elliptical hole. It can be expected that in this case, the stress intensity factor will increase with the relative crack size, b/c .

Also of interest to note in Figs. 4.3 to 4.7 is that all the curves pass through one point when $\mu_2/\mu_1 = 1$, as expected when the two materials become identical. The normalised stress intensity factor for this case is, within the realms of numerical error, unity, the analytically predicted result for a centrally located crack embedded in homogeneous materials.

4.1.2 Thermal Cooling

When the composite is uniformly cooled, as is the case considered throughout the present work, thermal stresses will result because of the mismatch of material properties. The numerical results of the normalised stress intensity factors, $K_I/\bar{K}$, where $\bar{K} = E_1\alpha_1\Delta T\sqrt{\pi b}$, for Problem I are presented in Tables 4.1-4.5, ΔT being the temperature change. Each table shows the results for a specific c/a and the various μ_2/μ_1 ratios and b/c values considered. The results of the normalised stress intensity factor can be shown to increase monotonically with the μ_2/μ_1 ratio, for each of the b/c and c/a ratios treated. Increasing the relative crack size b/c , on the other hand, has the effect of reducing the results for a given combination of c/a and μ_2/μ_1 ratios. Also, the numerical stress intensity factor decreases significantly with the increase in c/a ratio, if μ_2/μ_1 and b/c ratios are specified.

4.2 2D Problem II: Partially penetrating crack

In this problem, see Fig. 4.8, the crack has partially penetrated the elliptical inclusion along its axis to a length of b , while the remaining part of the crack lies in the matrix with length d , which is taken to be equal to the semi-axis, c , of the ellipse. The relative crack size, $b/2c$, considered ranged from 0.20 to 0.80. By virtue of symmetry only one half of the domain was modelled, and the typical BIE mesh is shown in Figure 4.9 with 42 boundary elements employed.

4.2.1 Mechanical Load

The composite is subjected to remote tension σ in the direction perpendicular to the plane of the crack. The numerical results of the normalised stress intensity factors, $K_I/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi(b+d)/2}$, for crack-tip A in the matrix (see Figure 4.8) are shown in Figs. 4.10-4.14 for the different relative crack size $b/2c$ and various c/a ratios. In these figures it is seen that given the $b/2c$ and c/a ratios, the value of $K_I/\bar{K}$ decreases monotonically with the increase of the shear modulus ratio, μ_2/μ_1 , in general. This trend is expected because, with the increase of μ_2/μ_1 , the matrix becomes relatively less stiff and thus is expected to be subjected to weaker stress distributions around the crack-tip A. For μ_2/μ_1 ratios less than 1, the normalised stress intensity factor decreases with the relative crack size $b/2c$. The c/a ratio also has some effect on the numerical results, with smaller c/a ratios generally resulting in more rapid variations in the stress intensity factor with the shear modulus ratio.

The numerical results of the normalised stress intensity factor, $K_I/\bar{K}$, for crack-tip B located in the inclusion are shown in Figs. 4.15-4.19; they have been plotted separately for $\mu_2/\mu_1 \leq 1$ and $\mu_2/\mu_1 \geq 1$ for the sake of clarity. The value of $K_I/\bar{K}$ is found to increase significantly with the shear modulus ratio μ_2/μ_1 in each figure.

Again this is anticipated because with the increase in the value of μ_2/μ_1 , the inclusion becomes relatively stiffer resulting in stress distributions of greater magnitude about the crack-tip, and hence higher stress intensity factors. Also, increasing the relative crack length $b/2c$ has the effect of decreasing the stress intensity factor when μ_2/μ_1 is less than 1, while opposite trend is found for the cases when μ_2/μ_1 ratios are greater than 1.

When the shear modulus ratio becomes 1 this problem again reduces to that of a centrally located crack in homogeneous material. In this case the numerical results for all the $b/2c$ and c/a ratios converge to unity, the theoretically predicted result of the normalised stress intensity factor, for both crack-tip A and crack-tip B; the BEM numerical errors of the results are always limited to well within 2%.

4.2.2 Thermal Cooling

The numerical results of the normalised stress intensity factors, $K_I/\bar{K}$, where $\bar{K} = E_1\alpha_1\Delta T\sqrt{\pi(b+d)}$, at crack-tip A are listed in Tables 4.6-4.10 for the load case when the composite is subject to uniform cooling by temperature ΔT . In each table the results for a specific c/a ratio and the various relative crack sizes $b/2c$ and the shear modulus ratios μ_2/μ_1 are presented. Of importance to note from these tables is that some of the numerical results of $K_I/\bar{K}$ are negative in value, implying that the crack faces will close at the crack-tip in this case instead of opening it. This is particularly so when $\mu_2/\mu_1 > 1$. This can be explained by the combined result of two opposite effects; one trying to open the crack within the inclusion which will be in a tensile stress state, while the other trying to close it in the matrix which will be in a state of compression (see Fig. 4.20). The normalised stress intensity factor is seen to increase with the relative crack size $b/2c$, while decreasing with the shear modulus ratio μ_2/μ_1 in general. Also, the larger the c/a ratio, the smaller is the range of variation in $K_I/\bar{K}$ with the μ_2/μ_1 ratio, for a given $b/2c$ value.

The results of the normalised stress intensity factor, $K_I/\bar{K}$, at crack-tip B are listed in Tables 4.11-4.15. It can be seen that given μ_2/μ_1 and $b/2c$ values, numerical stress intensity factor decreases significantly as the c/a ratio increases from 1/3 to 3. This is especially true when the μ_2/μ_1 ratio becomes very large. It is also found that at relatively large μ_2/μ_1 ratios the effects of the relative crack size $b/2c$ on the normalised stress intensity factor results are much more evident than those at smaller μ_2/μ_1 ratios, given the c/a ratio; the larger the $b/2c$ ratio, the larger the $K_I/\bar{K}$ values. However, these effects become rather insignificant when the μ_2/μ_1 ratio decreases to be less than 1. Also, the numerical results can be seen to increase markedly with the shear modulus ratio μ_2/μ_1 for almost all $b/2c$ and c/a ratios, except at $b/2c = 0.20$ and $c/a = 2$ and 3. The numerical values at $\mu_2/\mu_1 = 100$, $b/2c = 0.20$, $c/a = 2$ and 3, are seen to be negative. This can be again explained with reference to Fig. 4.20 where the compressive stress in the matrix predominates over the tensile stress in the inclusion.

4.3 2D Problem III: Y-shaped crack

Figure 4.21 shows the geometry of the problem, in which a crack spans an angle 2β along the elliptical interface and is symmetric about the horizontal axis, continuing into the matrix along the plane of this axis. For the BIE analysis, the length of the straight part of the crack in the matrix, d , was taken to be equal to the length of the semi-axis c , and stress intensity factors were calculated for four different values of β , namely, $30^\circ, 60^\circ, 90^\circ, 120^\circ$. By the virtue of symmetry, only one-half of the physical domain is represented for the BEM calculation, and a typical BEM mesh is shown in Fig. 4.22, where 44 elements were employed.

4.3.1 Mechanical Load

The infinite body is subjected to vertical and horizontal uniform remote tension σ . The normalised results of $K_I/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi d}$, for the point A are plotted in Figs. 4.23-4.27. Each figure is for a specific c/a ratio, and shows four curves for the four different crack sizes β treated. The normalised stress intensity factor is seen to decrease with the shear modulus ratio μ_2/μ_1 in general for all β angles and c/a ratios; the smaller the β value and the closer the μ_2/μ_1 ratio to 1, the larger the rate of decrease. Also can be seen from these figures is that as μ_2/μ_1 becomes smaller and smaller, all four curves in each figure approach one value. This trend is to be expected, for in the limiting case of $\mu_2/\mu_1 = 0$, the elliptical inclusion becomes an elliptical hole and effect of the β angle then vanishes. Except for the case of $c/a = 1/3$, all the results indicate that the larger the interface crack size as measured by β , the higher the value of $K_I/\bar{K}$.

The BEM results of the normalised *overall stress intensity factor* $K_0/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi d}$, for the crack-tips B are shown in Figs. 4.28-4.32 for the β angles and c/a and μ_2/μ_1 ratios considered. It can be seen from each figure that the $K_0/\bar{K}$ value increases monotonically with the shear modulus ratio μ_2/μ_1 for all the β values analyzed. The curves of the stress intensity factor have the general trend that as the μ_2/μ_1 ratio approaches zero the numerical results approach zero too. Again this is to be expected if the limiting case of elliptical hole is considered, where the stress intensity factor is obviously zero regardless of the β value.

The computed results of the non-dimensionalised phase angle ψ^* are shown in Figs. 4.33-4.37. When the c/a ratio is less than unity, the effect of the shear modulus ratio μ_2/μ_1 on ψ^* appears not to be as significant as when $c/a \geq 1$.

4.3.2 Thermal Cooling

The BEM results of the normalised stress intensity factor, $K_I/\bar{K}$, where $\bar{K} = E_1\alpha_1\Delta T\sqrt{\pi d}$, for point A are listed in Tables 4.16-4.20. Each table shows the results for a specific c/a ratio, and the range of β values and the μ_2/μ_1 ratios treated. They are all negative in value, implying that to open the crack faces at A, external loads which give positive stress intensity factor values of at least the same magnitude, when considered separately, are required. It is seen from these tables that the negative stress intensity factor solution increases in value with the shear modulus ratio μ_2/μ_1 in general, for a set of c/a and β values. This is expected because the larger the value μ_2/μ_1 , the greater will be the compressive stresses at A resulting from the thermal cooling.

The normalised results of the overall stress intensity factor $K_0/\bar{K}$, where $\bar{K} = E_1\alpha_1\Delta T\sqrt{\pi d}$, for the crack-tip B are listed in Tables 4.21-4.25. The corresponding solutions obtained for the phase angle ψ^* are listed in Tables 4.26-4.30. The qualitative trends of these results are again as expected.

4.4 Conclusion

In this chapter three two-dimensional crack problems involving an elliptical inclusion in a matrix have been investigated using the BEM. For each problem, both mechanical and thermal loading have been considered. The effects of the inclusion geometry and the crack size have also been studied, and, for a given cracked configuration, various shear modulus ratios of the inclusion to the matrix were also treated in the analysis. The numerical results were compared with the corresponding analytical solution where possible, and they were found to be in very good agreement.

Chapter 5

Axisymmetric Fracture Analysis for Cracks at Inclusions

In particulate-reinforced composite materials cracks often initiate at inclusions due to high localised applied or residual stresses. These stresses can arise from the mismatch of the shear modulus or the thermal expansion coefficient between the inclusion and the matrix. Microcracking in such components may have deleterious effects on their fracture strength, although a limited amount of microcracking have been found to enhance the fracture toughness of a number of ceramics, see, e.g. Evans and Faber (1984). In the study of such problems using the concepts of linear fracture mechanics, the particulate inclusions may be considered as spherical or ellipsoidal so that the problems can be simplified to axisymmetric ones.

In this chapter three crack configurations at a spherical or an ellipsoidal inclusion, namely, (a) the penny-shaped crack, (b) the Y-shaped crack (in the diametrical plane) and (c) the circumferential crack, are studied using the BIE method for axisymmetry. Both mechanical and thermal loads are considered in the analysis for a range of crack sizes. As before in the two-dimensional study, the ratio of the shear modulus of the inclusion (material 2) to that of the matrix (material 1), μ_2/μ_1 , was taken to range from 1/100 to 100 for both load cases, unless otherwise specified. Poisson's ratio was assumed to be 0.25 throughout. As for the thermal load case, the ratio of the thermal

expansion coefficient between the inclusion and the matrix, α_2/α_1 , was taken to be 10; the stress intensity factor results for other thermal ratios may be obtained by simple linear interpolation between zero values at $\alpha_2/\alpha_1 = 1$, and the corresponding values obtained here.

In the numerical treatment of the above-mentioned problems, the infinite matrix was modelled as a finite cylinder with radius and half-length both twenty times that of the radius of the spherical inclusion or of the horizontal semi-axis of the ellipsoidal inclusion. Quarter-point crack-tip elements were once again used in all the analysis, and both the displacement and traction formulas presented previously were used for evaluating the stress intensity factors. The differences in the numerical stress intensity factors obtained from using these formulas were found to be generally less than 2 percent, and thus only the traction formula results are presented here.

For all the problems considered, the numerical results are shown plotted for remote tension case and tabulated for the thermal loading case. It should also be mentioned that some of the results for the μ_2/μ_1 ratios greater than unity have been presented by Tan and Gao (1990b). Their results are presented together with those obtained here for completeness.

5.1 Axisymmetric Problem I: Penny-shaped crack

Figure 5.1 shows a penny-shaped crack of radius b located in the equatorial plane of a spherical inclusion of radius c , and perpendicular to the axis of symmetry. The relative crack sizes considered were from $b/c = 0.5$ to $b/c = 1.5$. Obviously, when the b/c ratio is less than unity, the crack is completely embedded in the inclusion, while $b/c > 1$ indicates its extension into the matrix. For the BIE analysis, only one-quarter of the cylinder was considered, by virtue of symmetry. A typical boundary element

mesh is shown in Fig. 5.2.

5.1.1 Mechanical Load

For the physical problem subject to remote axial tension σ , the BEM results of the normalised stress intensity factor, $K_I/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi b}$, at the crack-periphery in the case when $b/c < 1$, are as shown in Fig. 5.3a and Fig. 5.3b. The results for $\mu_2/\mu_1 \leq 1$ and for $\mu_2/\mu_1 \geq 1$ have been plotted separately for the sake of clarity here. It can be seen that, given a relative crack size, the shear modulus ratio μ_2/μ_1 has a significant effect on the stress intensity factor. That the $K_I/\bar{K}$ value increases monotonically with μ_2/μ_1 in this case when the crack is completely lodged in the inclusion is also to be expected. This is because a larger μ_2/μ_1 ratio means a stiffer inclusion, and hence a higher normal stress in the inclusion. Also, as the μ_2/μ_1 ratio becomes smaller and smaller, as can be seen, $K_I/\bar{K}$ decreases towards zero for all the b/c ratios treated, as it should be.

The numerical results of $K_I/\bar{K}$ for the cases when the crack-periphery is located in the matrix, i.e. $b/c > 1$, are shown in Fig. 5.4. It can be seen that the value of $K_I/\bar{K}$ increases fairly rapidly with the shear modulus ratio μ_2/μ_1 , particularly for the smaller b/c ratios. In this case, the crack-periphery is closer to the interface and is thus expected to be subject to a greater influence of the inclusion. As b/c gets relatively large in value, however, the solution is rather insensitive to the variation of μ_2/μ_1 , as seen in Fig. 5.4.

When $\mu_2/\mu_1 = 1$, the physical problem reduces to that of a penny-shaped crack embedded in a homogeneous body. The analytical solution of the stress intensity factor to this problem can be written as $K_I = 2\sigma\sqrt{b/\pi}$, or in non-dimensionalised form $K_I/\bar{K} = 2/\pi$, where $\bar{K} = \sigma\sqrt{\pi b}$. Numerical results obtained here for this case was found to be within 1.5 percent error from this analytical solution.

5.1.2 Thermal Cooling

The computed results of the normalised stress intensity factor, $K_I/\bar{K}$, where $\bar{K} = E_1\alpha_1\Delta T\sqrt{\pi c}$, for $b/c < 1$ are listed in Table 5.1, ΔT being the change in temperature. It is seen that the $K_I/\bar{K}$ value increases significantly with the shear modulus ratio μ_2/μ_1 . Also seen in the table is that increasing the relative crack size b/c would increase the normalised stress intensity factor for $\mu_2/\mu_1 > 1$. However, when the μ_2/μ_1 ratio is less than unity this trend does not hold true. In this situation of $\mu_2/\mu_1 < 1$, the spherical boundary of the stiffer matrix is expected to resist the crack opening in the inclusion. The larger the b/c value, i.e. the closer the crack-periphery to the interface, the stronger will be the effect.

The results of $K_I/\bar{K}$ for the crack-periphery located in the matrix are listed in Table 5.2. It can be seen from this Table that the $K_I/\bar{K}$ value increases significantly with the μ_2/μ_1 ratio for a given b/c value. This is due to the increasing magnitude of the thermal stresses, both the tensile stresses in the inclusion and the compressive stresses in the matrix (the effect of the former being larger on crack opening), with the increase in μ_2/μ_1 . Also indicated in the Table is that increasing the relative crack size has the effect of reducing the stress intensity factors for all the μ_2/μ_1 ratios treated. This is expected, because of the increasing effect of the compressive thermal stresses in the matrix at the crack-periphery with the increase in b/c .

5.2 Problem II: Y-shaped crack

Figure 5.5 shows the diametrical plane of the physical problem considered, where a crack has grown radially in the matrix from its interface with the inclusion; the circumferential interface crack spans an angle of 2β , symmetric about the plane of the radial crack. For the BIE analysis, the b/c ratio was taken to be 2, and the angle

β was varied from 15° to 75° . By virtue of symmetry, only one-half of the radial plane was modelled, and the typical boundary element mesh is shown in Fig. 5.6.

5.2.1 Mechanical Load

Figure 5.7 shows the normalised stress intensity factors $K_I/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi c}$ here, for the crack periphery A in the matrix when the cylinder matrix is subjected to remote tension σ in the axial direction. The $K_I/\bar{K}$ solution is seen to decrease with the increase in μ_2/μ_1 ratio for a given β angle. As expected, all five curves for the different β angles converge to one value as the μ_2/μ_1 ratio approaches zero, when the inclusion becomes a hollow sphere. Also, the stress intensity factor at A increases with the extent of the circumferential debonding, as measured by β , at the inclusion-matrix interface. The effect of the value β on the $K_I/\bar{K}$ results is more evident as the μ_2/μ_1 ratio becomes greater. Figure 5.8 shows the variation of the normalised overall stress intensity factor, $K_0/\bar{K}$, for the debond crack periphery B, with the shear modulus ratio μ_2/μ_1 . The value of $K_0/\bar{K}$ is seen to increase fairly rapidly with the shear modulus ratio μ_2/μ_1 for a given extent of debonding as measured by β . When μ_2/μ_1 approaches zero, the stress intensity factors for all the β values considered approach zero as well, as should be the case. This is because the inclusion becomes a spherical cavity at $\mu_2/\mu_1 = 0$.

The corresponding variations for the normalised phase angle $\psi^* = \arg(Kc^{-1/2})$ with μ_2/μ_1 are shown in Figure 5.9 for the different crack sizes. It can be seen that for a given crack size, ψ^* remains fairly constant for most part of the range of μ_2/μ_1 , except when $0.1 \leq \mu_2/\mu_1 \leq 10$, indicating the relatively significant variations of coupled shear and tensile mode deformation in this shear modulus ratio range.

5.2.2 Thermal Cooling

Table 5.3 lists the results of the normalised stress intensity factors for the periphery of A, $K_I/\bar{K}$, when the composite is uniformly cooled by a temperature ΔT . $\bar{K}$ is as before, equal to $E_1\alpha_1\Delta T\sqrt{\pi c}$. Note that the mode I stress intensity factor at A is negative throughout for all the angles of β and the μ_2/μ_1 ratios treated. This implies that for the geometric and material property parameters analyzed, the compressive axial stress in the matrix always tends to close the crack at the periphery A and it must be overcome by, say, an axial tensile stress due to mechanical loads for the crack to open there. The magnitude of the (negative) stress intensity factor is seen to increase markedly with increasing μ_2/μ_1 for a given extent of debonding. However, increasing the β angle would decrease the value of $K_I/\bar{K}$.

The BEM results for the normalised overall stress intensity factor at the crack periphery B are listed in Table 5.4. It was found that the effect of the β angle on the stress intensity result here does not appear to be very significant, as can be seen in the Table. The corresponding results of the non-dimensionalised phase angle ψ^* are listed in Table 5.5.

5.3 Problem III: Circumferential interface crack

5.3.1 Mechanical Load

Figure 5.10 shows the diametrical plane of the third problem analyzed, where an axisymmetric debond crack spans an angle 2β along the interface between the ellipsoidal inclusion and the matrix. Three semi-axis ratio, c/a , were considered, namely, 1, 2, and 3. For each c/a ratio, four debond crack sizes were treated in this study, namely, $\beta = 22.5^\circ, 45^\circ, 67.5^\circ$, and 75° , and the shear modulus ratio, μ_2/μ_1 , was varied from

1/100 to 20. Note that the case of $\mu_2/\mu_1 = 100$ was not included. This is because in this case, the BIE analysis indicated that the debond crack surfaces would overlap one another at $\beta = 75^\circ$, which is physically inadmissible. The problem then becomes that of contact mechanics and is beyond the scope of the present study. For the numerical treatment of this problem, the entire radial plane of the physical problem was modelled because there is no symmetry about any axial plane here, and the typical BEM mesh is shown in Fig. 5.11.

The composite cylinder is subject to remote axial tension σ . The variations of the normalised overall stress intensity factors $K_0/\bar{K}$, where $\bar{K} = \sigma\sqrt{\pi c}$, with the shear modulus ratio μ_2/μ_1 , are shown in Figs. 5.12-5.14 for the three c/a ratios and various β angles considered. The numerical stress intensity factors are seen to increase monotonically with the shear modulus ratio μ_2/μ_1 for a given c/a ratio and β angle. The β angle also affects quite significantly the stress intensity factor results; the larger the c/a ratio, the more significant the role of β value would be, as seen in Figs. 5.12-5.14. The corresponding results of the non-dimensionalised phase angle, ψ^* , are plotted the Figs. 5.15-5.17, where the ψ^* value is seen to decrease with increasing μ_2/μ_1 ratio.

5.3.2 Thermal Cooling

For this load case, only a spherical inclusion was treated and three axisymmetric interface crack sizes, as measured by the angle 2β , were analyzed. The β angles were taken to be $22.5^\circ, 45^\circ, 67.5^\circ$ and, for a given β value, the shear modulus ratio was varied to range from 1/100 to 100. The reason that the crack-sizes of up to only $\beta = 67.5^\circ$ were treated is because the BIE analysis indicated that beyond this angle the debond crack faces would overlap with each other at $\mu_2/\mu_1 = 100$.

Table 5.6 lists the BEM results of the overall stress intensity factor $K_0/\bar{K}$, where

$\bar{K} = E_1 \alpha_1 \Delta T \sqrt{\pi c}$, for the case when the composite is uniformly cooled by temperature ΔT . It can be seen that the $K_0/\bar{K}$ value increases significantly with the shear modulus ratio μ_2/μ_1 for a given β angle, as expected. The effect of the β value on the stress intensity factor solution is, however, not very significant, although the latter still increases with it to a certain degree, as indicated in Table 5.6. The computed results of the non-dimensionalised phase angle, ψ^* , are shown in Table 5.7, where it can be seen that the ψ^* value decreases with increasing μ_2/μ_1 ratio. Increasing the β angle, on the other hand, has the effect of increasing ψ^* , as it was found.

5.4 Conclusions

In this chapter the multi-region boundary element method with quadratic quarter-point crack-tip elements has been used to investigate axisymmetric inclusion crack problems. Three problems have been treated here, among which two involve a bi-material interface crack. Stress intensity factors have been obtained for both remote tension and thermal cooling. The effects of crack size and the shear modulus ratio of the inclusion to the matrix have also been investigated. The results presented would be of interest to the study of, for example, microcracking in particulate composites.

Chapter 6

Summary and Conclusions

In this study, the theory of linear elastic fracture mechanics (LEFM) has been reviewed, in which the near-tip fields for a crack embedded in a homogeneous material, as well as those for a bimaterial interface crack, are presented. For the latter type of crack the stresses in the vicinity of the crack-tip are oscillatorily singular in nature, when treated by the traditional LEFM approach. For full characterisation of these oscillatory fields, the concepts of the overall stress intensity factor and the characteristic phase angle have been introduced.

The formulation of the multi-region boundary element method (BEM) has also been reviewed. The use of the quadratic quarter-point crack-tip elements has been introduced to accurately represent the displacement variation and stress singularity in the vicinity of the crack-tip according to LEFM theory. The procedures for obtaining the formulae for evaluating the stress intensity factors directly from the computed nodal values of the displacements, or from those of the nodal tractions at these quarter-point crack-tip elements have also been described. They may be used to treat problems with crack-tip(s) located in a homogeneous body, as well as those involving bimaterial interface crack(s). The accuracy and efficiency of the boundary element method have been illustrated by five test problems, of which three involve bimaterial interface cracks.

The multi-region BEM with quarter-point crack-tip elements has then been used to investigate cracks at elliptical inclusions in two dimensions. These problems are of importance in, for example, the micromechanics of composite materials which are increasingly being employed for structural applications. Both mechanical and thermal loading have been considered. Three crack configurations have been studied here. For a given crack problem, different elliptical semi-axis ratios and several crack sizes were treated and the effects of the shear modulus ratio of the inclusion to the matrix were also investigated. Stress intensity factor results have been presented and discussed, and where possible they were compared to analytical solutions.

The boundary element method has further been applied to treating three axisymmetric problems with cracks occurring at spherical and ellipsoidal inclusions. Again, both cases of mechanical loading and thermal loading have been considered. Several crack sizes have been treated for each problem, and as before, the numerical results have been obtained for a range of shear modulus ratios.

The current study has demonstrated that the multi-region BEM with quarter-point crack-tip elements is an efficient numerical tool for fracture analysis of cracks at inclusions. The results obtained here may be applied to, for example, the study of microcracking in composite materials.

References

- Bao, G. and Hui, C. Y. (1989), *Effects of Interface Debonding on the Toughness of Ductile-Particle Reinforced Ceramics*, Int. J Solids Struct., Vol. 26, No. 5/6, 631-642, 1990.
- Besuner, P. M. (1977), *The Application of the Boundary-Integral Equation Method to the Solution of Engineering Stress Analysis and Fracture Mechanics Problems*, Nuclear Engng. Design 43, 161-173.
- Brown, W. S. and Strawley, J. E. (1966), *Plane Strain Crack Toughness Testing of High Strength Metallic Materials*, ASTM STP No. 410.
- Bui, H. D. (1977), *An Integral Equations Method for Solving the Problem of a Plane Crack of Arbitrary Shape*, J. Mech. and Physics of Solids 25, 29-39.
- Charalambides, P. G., Lund, J., Evans, A. G. and McMeeking, R. M. (1989), *A test specimen for determining the fracture resistance of bimaterial interfaces*, J. Appl. Mech. 56, 77-82.
- Comninou, M. (1977), *The interface crack*, J. Appl. Mech. 44, 631-636.
- Comninou, M. (1990), *An Overview of Interface Cracks*, Engng. Fracture Mech. 37, 1, 197-208.
- Cruse, T. A. and Buren, W. V. (1971), *Three-Dimensional Elastic Stress Analysis of a Fracture Specimen with an Edge Crack*, Int. J. Fracture Mech., 7, No. 1, 1-15.
- Cruse, T. A. (1974), *An Improved Boundary-Integral Equation Method for Three*

Dimensional Elastic Stress Analysis, Computers & Struct., **4**, 741-754.

Cruse, T. A. and Wilson, R. B. (1978), *Advanced Applications of Boundary Integral Equation Methods*, Nuclear Engng. Design, **46**, 223-234.

Cruse, T. A. (1978), *Two Dimensional BIE Fracture Analysis*, Appl. Math. Modelling **2**, 287-293.

Cruse, T. A. (1979), *Two- and Three-Dimensional Problems of Fracture Mechanics*, in: *Developments in Boundary Element Methods-1*, P. K. Banerjee and R. Butterfield, Eds., 97-119.

Cruse, T. A. and Polch, E. Z. (1986), *Elastoplastic BIE analysis of Cracked Plates and Related Problems, Part 1: Formulation, Part 2: Numerical Results*, Int. J. Numer. Methods Engng. **23**, 429-437, 439-452.

Cruse, T. A. (1988), " *Boundary Element Analysis in Computational Fracture Mechanics* ". Kluwer Academic Publishers.

England, A. H. (1965), *A crack between dissimilar media*, J. Appl. Mech. **32**, 400-402.

Erdogan, F. (1963), *Stress distribution in a nonhomogeneous elastic plane with cracks*, J. Appl. Mech. **30**, 232-237.

Evans, A. G. and Faber, K. T. (1984), *Crack-growth resistance of microcracking in brittle materials*, J. Amer. Ceram. Soc., **67**, 255-260.

Gao, Y. L., Tan, C. L. and Selvadurai, A. P. S. (1991), *Stress intensity factors for cracks around or penetrating an elliptic inclusion using the boundary element method*, Computational Mech. (in press)

Hasegawa, H. (1988), *A fundamental solution and boundary element method for torsion problems of a bonded dissimilar elastic solid*, in: Boundary Element Methods in Applied Mechanics, Edited by M. Tanaka and T. A. Cruse, Pergamon Press, Oxford, 179-190.

Henshell, R. D. and Shaw, K. G. (1975), *Crack tip elements are unnecessary*, Int. J. Numer. Methods Engng. **9**, 495-509.

Hong, C. C. and Stern, M. (1978), *The computation of stress intensity factors in dissimilar materials*, J. Elasticity **8**, 21-34.

Hutchinson, J. W. and Evans, A. G. (1989), *On the Mixed Mode Fracture Resistance of Interfaces*, Acta Metall. **37**, 3, 909-916.

Jaswon, M. A. (1963), *Integral Equation Methods in Potential Theory*, Proc. Royal Soc. London, **A275**, 23-32.

Kassir, M. K. and Bregman, A. M. (1972), *The Stress-Intensity Factor for a Penny-Shaped Crack Between Two Dissimilar Materials*, J. Appl. Mech., **36**, 308-310.

Lee, K. Y. and Choi, H. J. (1988), *Boundary element analysis of stress intensity factors for bimaterial interface cracks*, Engng. Fracture Mech. **29**, 461-472.

Malyshev, B. M. and Salganik, R. L. (1965), *The strength of Adhesive Joints Using the Theory of Crack*, Int. J. Fracture Mech., **1**, 114-128.

Martinez, J. and Dominguez, J. (1984), *On the use of quarter-point boundary elements for stress intensity factor computations*, Int. J. Numer. Methods Engng. **20**, 1941-1950.

Mukherjee, S. and Banthia, V. (1984), *Non-Linear Problems of Fracture Mechanics*, in: Developments in Boundary Element Methods-3, P.K. Banerjee and S. Mukherjee,

Eds. (Elsevier Applied Science Publishers, London), 87-114.

Mulville, D. R. and Mast, P. W. (1976), *Strain energy release rate of interfacial cracks between dissimilar materials*, Engng. Fracture Mech., **8**, 555-565.

Muskhelishvili, N. I. (1953), *"Some Basic Problems of Mathematical Theory of Elasticity"*, Noordhoff, Groningen, Holland.

Owen, D. R. J. and Fawkes, A. J. (1983), *"Engineering Fracture Mechanics: Numerical Methods and Applications"*, Pineridge Press, Swansea, U.K.

Perlman, A. B. and Sih, G. C. (1967), *Elastostatic Problems of Curvilinear Cracks in Bonded Dissimilar Materials*, Int. J. Engng Sci. Vol. **5**, 845-867.

Rice, J. R. and Sih, G. C. (1965), *Plane problems of cracks in dissimilar media*, J. Appl. Mech. **32**, 418.

Rice, J. R. (1988), *Elastic fracture mechanics concepts for interfacial cracks*, J. Appl. Mech. **55**, 98-103.

Rizzo, F. J. (1967), *An Integral Equation Approach to Boundary Value Problems of Classical Elastostatics*, Quar. Appl. Mech., **25**, 83-95.

Sih, G. C. and Rice J. R. (1964), *The bending of plates of dissimilar materials with cracks*, J. Appl. Mech. **31**, 477.

Smelser, R. E. (1979), *Evaluation of stress intensity factors for bimaterial bodies using crack flank displacement data*, Int. J. Fracture **32**, 169-183.

Smith, R. N. L. and Mason, J. C. (1982), *A Boundary Element Method for Curved Crack Problems in Two Dimensions*, in: Boundary Element Methods in Engineering, C. A. Brebbia, Ed. (Springer-Verlag, Berlin), 472-484.

Tan, C. L. and Fenner, R. T. (1979), *Elastic Fracture Mechanics Analysis by the Boundary-Integral Equation Method*, Proc. Royal Soc. London, **A369**, 243-260.

Tan, C. L. and Fenner, R. T. (1980), *Stress Intensity Factors for Semi-Elliptical Surface Cracks in Pressurized Cylinders Using the Boundary Integral Equation Method*, Int. J. Fracture **16**, 223-245.

Tan, C. L. (1987), "*The Boundary Element Method: A Short Course*", Monograph, Carleton Univ.

Tan, C. L. and Gao, Y. L. (1990a), *Treatment of bimaterial interface crack problems using the boundary element method*, Eng. Fracture Mech. **36**, 6, 919-932.

Tan, C. L. and Gao, Y. L. (1990b), *Stress intensity factors for cracks at spherical inclusions by the boundary integral equation method*, J. Strain Analysis **25**, 4, 197-206.

Tan, C. L. and Gao, Y. L. (1991), *Axisymmetric boundary integral equation analysis of interface cracks between dissimilar materials*, Computational Mech. **7**, 381-396.

Yuuki, R., Cho, S. B., Matsumoto, T. and Kisu, H. (1987), *Usefulness of Hetenyi's solution for boundary element analysis of crack problems in dissimilar materials*, in: Role of Fracture Mechanics in Modern Technology, Edited by G. C. Sih, H. Nisitani and T. Ishihara, 823-834, Elsevier, Amsterdam.

Yuuki, R. and Cho, S. B. (1988), *Boundary element analysis of the stress intensity factors for an interface crack in dissimilar materials*, in: Boundary Element Methods in Applied Mechanics, Edited by M. Tanaka and T. A. Cruse, 179-190, Pergamon Press, Oxford.

Williams, M. L. (1959), *The stresses around a fault or crack in dissimilar media*, Bull. Seismol. Soc. Am. **49**, 199-204.

Table 3.1 Percentage Error in the Stress Intensity Factor for Plate with a Central Crack: $\bar{K} = \sigma \sqrt{(\pi a)}$; $(K_I)_t$ - Traction Formula Result; $(K_I)_d$ - Displacement Formula Result. $(K_I/\bar{K})_{\text{exact}} = 1$

l/a	$(K_I)_t/\bar{K}$	Error %	$(K_I)_d/\bar{K}$	Error %
0.30	1.0170	1.70	1.0430	4.30
0.20	1.0147	1.47	1.0293	2.93
0.10	1.0119	1.19	1.0168	1.68
0.05	1.0065	0.65	1.0080	0.80
0.03	0.9968	-0.32	0.9974	-0.26

Table 3.2 Percentage Error in the Stress Intensity Factor for Finite Plate with a Edge Crack: $\bar{K} = \sigma \sqrt{(\pi a)}$; $(K_I)_t$ - Traction Formula Result; $(K_I)_d$ - Displacement Formula Result. $(K_I/\bar{K})_{\text{exact}} = 1.5047$

l/a	$(K_I)_t/\bar{K}$	Error %	$(K_I)_d/\bar{K}$	Error %
0.30	1.5129	0.55	1.5116	0.46
0.20	1.5124	0.51	1.5093	0.30
0.10	1.5109	0.40	1.5065	0.12
0.05	1.5039	-0.075	1.5001	-0.30
0.03	1.4868	-1.19	1.4844	-1.35

Table 3.3a Percentage Error in the Normalised Overall Stress Intensity Factor for Infinite Plate with a Bimaterial Central Crack: $\bar{K} = (\sigma_y)^{-1} \sqrt{\pi a}$; $(K_0)_t$ - Traction Formula Result; $(K_0)_d$ - Displacement Formula Result.

μ_2/μ_1	$(K_0/\bar{K})_{\text{exact}}$	l/a	$(K_0)_d/\bar{K}$	Error %	$(K_0)_t/\bar{K}$	Error %
1	1	0.30	1.0229	2.3	1.0003	0.03
		0.20	1.0074	0.7	0.9965	-0.3
		0.10	0.9943	-0.6	0.9984	-0.5
		0.05	0.9850	-1.5	0.9910	-0.9
		0.03	0.9738	-2.6	0.9817	-1.8
5	0.989	0.30	1.0202	3.1	0.9934	0.4
		0.20	1.0050	1.6	0.9895	0.05
		0.10	0.9925	0.4	0.9869	-0.2
		0.05	0.9834	-0.6	0.9820	-0.7
		0.03	0.9723	-1.7	0.9726	-1.7
20	0.980	0.30	1.0187	4.0	0.9914	1.2
		0.20	1.0028	2.3	0.9880	0.8
		0.10	0.9899	1.0	0.9860	0.6
		0.05	0.9872	-0.2	0.9817	0.2
		0.03	0.9652	-1.5	0.9926	-0.8
100	0.976	0.30	1.0107	4.0	0.9915	1.6
		0.20	0.9917	1.6	0.9880	1.2
		0.10	0.9720	-0.4	0.9860	1.0
		0.05	0.9483	-2.8	0.9817	0.6
		0.03	0.9318	-4.5	0.9722	-0.4

Table 3.3b Percentage Error in the Phase Angle for Infinite Plate with a Bimaterial Central Crack: $\psi^* = \text{Arg}(Ka^{-1/2})$.

μ_2/μ_1	$(\psi^*)_{\text{exact}}$	l/a	ψ^* (deg.)	Error (%)
1	0.00°	0.30	-0.22	/
		0.20	-0.21	/
		0.10	-0.22	/
		0.05	-0.21	/
		0.03	-0.21	/
5	7.00°	0.30	6.86	-2.0
		0.20	6.74	-3.8
		0.10	6.63	-5.2
		0.05	6.67	-4.7
		0.03	6.84	-2.2
20	9.56°	0.30	9.43	-1.3
		0.20	9.27	-3.0
		0.10	9.13	-4.5
		0.05	9.17	-4.0
		0.03	9.42	-1.5
100	10.23°	0.30	10.2	-1.3
		0.20	10.1	-3.0
		0.10	9.92	-4.5
		0.05	9.96	-4.0
		0.03	10.2	-1.4

Table 3.4a Percentage Error in the Normalised Stress Intensity Factor for the Bimaterial Interface Arc Crack: $\bar{K} = \sigma \sqrt{\pi a}$; $(K_0)_t$ - Traction Formula Result; $(K_0)_d$ - Displacement Formula Result.

μ_2/μ_1	$(K_0/\bar{K})_{\text{exact}}$	θ_c/θ	$(K_0)_d/\bar{K}$	Error %	$(K_0)_t/\bar{K}$	Error %
1/100	0.0181	.025	0.0223	23.1	0.0217	19.6
		0.05	0.0223	23.1	0.0220	21.5
		0.10	0.0225	24.3	0.0222	22.7
1/20	0.0848	.025	0.1021	20.3	0.0994	17.2
		0.05	0.1020	20.3	0.1007	18.8
		0.10	0.1029	21.3	0.1017	20.0
1/5	0.2736	.025	0.3139	14.7	0.3025	10.6
		0.05	0.3119	14.0	0.3066	12.1
		0.10	0.3137	14.7	0.3095	13.3
1	0.6626	.025	0.6692	1.0	0.6568	-0.8
		0.05	0.6704	1.2	0.6652	0.4
		0.10	0.6737	1.7	0.6707	1.1
5	0.8763	.025	0.8705	-0.7	0.8806	-1.5
		0.05	0.8805	0.5	0.8738	-0.3
		0.10	0.8844	0.9	0.8790	0.3
20	0.9111	.025	0.8982	-1.4	0.9185	0.8
		0.05	0.9315	2.2	0.9289	2.0
		0.10	0.9399	3.2	0.9337	2.5
100	0.9175	.025	0.9377	2.2	0.9349	1.9
		0.05	0.9196	0.2	0.9448	3.0
		0.10	0.9443	2.8	0.9495	3.5

Table 3.4b Percentage Error in the Phase Angle for the Bimaterial Interface Arc Crack: $\Psi' = \text{Arg}(Ka^{-1/2})$

μ_2/μ_1	$(\Psi')_{\text{exact}}$	θ_c/θ	Ψ' (deg.)	Error (%)
1/100	25.4°	0.025	25.50	0.4
		0.05	25.48	0.3
		0.10	25.68	1.1
1/20	24.6°	0.025	24.63	0.1
		0.05	24.66	0.2
		0.10	24.88	1.1
1/5	22.0°	0.025	21.91	-0.1
		0.05	22.11	0.5
		0.10	22.37	1.7
1	15.0°	0.025	14.44	-3.7
		0.05	15.08	0.5
		0.10	15.44	2.9
5	8.0°	0.025	6.90	-13.8
		0.05	7.95	-0.6
		0.10	8.33	4.1
20	5.4°	0.025	4.14	-23.3
		0.05	5.33	-1.3
		0.10	5.74	6.3
100	4.6°	0.025	3.26	-29.1
		0.05	4.49	-2.4
		0.10	4.90	6.5

Table 3.5a Percentage Error in the Normalised Stress Intensity Factor for the Penny-shaped Bimaterial Interface Crack:
 $\bar{K} = p \sqrt{(\pi a)}$; $(K_I)_t$ - Traction Formula Result; $(K_I)_d$ - Displacement Formula Result.

μ_2/μ_1	$(K_I/\bar{K})_{\text{exact}}$	l/a	$(K_I)_d/\bar{K}$	Error %	$(K_I)_t/\bar{K}$	Error %
1	0.6364	.03	0.6295	-1.1	0.6435	1.1
		.05	0.6365	0.02	0.6490	2.0
		.10	0.6511	2.3	0.6427	1.0
		.20	0.6514	2.4	0.6511	2.3
		.30	0.6603	3.8	0.6506	2.2
5	0.6420	.03	0.6357	-1.0	0.6484	1.0
		.05	0.6426	0.1	0.6539	1.9
		.10	0.6487	1.0	0.6561	2.2
		.20	0.6574	2.4	0.6562	2.2
		.30	0.6662	3.8	0.6557	2.1
20	0.6460	.03	0.6410	-0.8	0.6517	0.9
		.05	0.6479	0.3	0.6572	1.7
		.10	0.6539	1.2	0.6594	2.1
		.20	0.6625	2.6	0.6596	2.1
		.30	0.6674	3.3	0.6591	2.0
100	0.6482	.03	0.6430	-0.8	0.6527	0.7
		.05	0.6499	0.3	0.6583	1.6
		.10	0.6559	1.2	0.6605	1.9
		.20	0.6625	2.5	0.6606	1.9
		.30	0.6733	3.9	0.6602	1.9

Table 3.5b Percentage Error in the Phase Angle for the Penny-shaped Bimaterial Interface Crack: $\Psi^* = \text{Arg}(Ka^{-1/2})$

μ_2/μ_1	$(\Psi^*)_{\text{exact}}$	l/a	Ψ^* (deg.)	Error (%)
1	0.00°	0.03	0	0
		0.05	0	0
		0.10	0	0
		0.20	0	0
		0.30	0	0
5	-8.36°	0.03	-8.52	1.9
		0.05	-8.33	-0.4
		0.10	-8.26	-1.2
		0.20	-8.31	-0.6
		0.30	-8.38	0.2
20	-11.42°	0.03	-11.62	1.8
		0.05	-11.35	-0.6
		0.10	-11.25	-1.5
		0.20	-11.33	-0.8
		0.30	-11.42	0
100	-12.40°	0.03	-12.61	1.7
		0.05	-12.32	-0.7
		0.10	-12.21	-1.5
		0.20	-12.29	-0.9
		0.30	-12.39	-0.1

Table 4.1 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{(\pi b)}$; $c/a = 1/3$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	b/c						
	1.05	1.10	1.20	1.40	1.50	1.60	1.80
0.01	0.240	0.232	0.215	0.169	0.153	0.138	0.111
0.05	1.061	1.010	0.914	0.703	0.630	0.564	0.450
0.10	1.859	1.749	1.539	1.164	1.036	0.921	0.728
0.20	3.043	2.811	2.381	1.763	1.555	1.372	1.070
1	7.193	6.223	4.867	3.410	2.940	2.542	1.912
5	12.00	9.626	7.437	4.992	4.239	3.620	2.668
10	13.66	10.67	8.440	5.621	4.768	4.071	3.006
20	14.81	11.35	9.512	6.358	5.414	4.645	3.471
100	15.77	11.84	10.99	10.50	9.229	8.171	6.520

Table 4.2 Normalised Stress Intensity Factors, $K_I/\bar{K}$, for 2D Inclusion Problem with Completely Penetrating Crack Subject to Thermal Cooling: $\bar{K} = E_1\alpha_1\Delta T \sqrt{(\pi b)}$; $c/a = 1/2$; $\alpha_2/\alpha_1 = 10$.

μ_2/μ_1	b/c						
	1.05	1.10	1.20	1.40	1.50	1.60	1.80
0.01	0.205	0.190	0.169	0.119	0.102	0.088	0.065
0.05	0.925	0.850	0.740	0.515	0.441	0.378	0.280
0.10	1.638	1.489	1.270	0.875	0.747	0.639	0.471
0.20	2.688	2.406	1.993	1.336	1.152	0.981	0.718
1	6.078	5.125	3.930	2.584	2.167	1.826	1.311
5	9.714	7.638	5.563	3.550	2.948	2.467	1.752
10	11.07	8.505	6.127	3.885	3.223	2.696	1.917
20	12.23	9.249	6.658	4.228	3.516	2.950	2.114
100	15.38	11.58	8.789	5.856	4.997	4.306	3.263

3

A resolution test chart featuring various patterns of vertical and horizontal lines. Each pattern is accompanied by a numerical label indicating its resolution. The labels include 1.0, 1.1, 1.25, 1.4, 1.6, 1.8, 2.0, 2.2, 2.5, 2.8, 3.2, 3.6, 4.0, 4.5, 5.0, 5.6, 6.3, 7.1, and 8.0. The patterns become progressively smaller and more densely packed as the numerical value increases.

PIONEERS IN METHYLENE BLUE TESTING SINCE 1974

Micro-D
in 22 New Editions

19000 COUNTY ROAD 5, BLANDVILLE, MN 55007 USA
TEL 612 435 7767 FAX 612 435 7767 T.E. & M. HARRISON

Figure 5.16 Characteristic Phase Angles
for Axisymmetric Problem III; $c/a=2$

Figure 5.17 Characteristic Phase Angles
for Axisymmetric Problem III; $c/a=3$

END

2|3·12·92

FIN