INFORMATION TO USERS

This manuscript has been reproduced from the microfilm master. UMI films the text directly from the original or copy submitted. Thus, some thesis and dissertation copies are in typewriter face, while others may be from any type of computer printer.

The quality of this reproduction is dependent upon the quality of the copy submitted. Broken or indistinct print, colored or poor quality illustrations and photographs, print bleedthrough, substandard margins, and improper alignment can adversely affect reproduction.

In the unlikely event that the author did not send UMI a complete manuscript and there are missing pages, these will be noted. Also, if unauthorized copyright material had to be removed, a note will indicate the deletion.

Oversize materials (e.g., maps, drawings, charts) are reproduced by sectioning the original, beginning at the upper left-hand corner and continuing from left to right in equal sections with small overlaps.

ProQuest Information and Learning
300 North Zeeb Road, Ann Arbor, MI 48106-1346 USA
800-521-0600

UMI[®]

Flexural and In-Plane Compressive Behaviour of Composite Structure Laminate Plates

by

Scott E. Funnell

**A thesis submitted to the
Faculty of Graduate Studies and Research
in partial fulfilment of the requirements
for the degree of
Master of Engineering**

**Department of Civil and Environmental Engineering
Carleton University
Ottawa, Ontario
May, 2000**

**The Master of Engineering in Civil and Environmental Engineering
is a joint program with the University of Ottawa,
administered by the Ottawa-Carleton Institute for Civil Engineering**

**© 2000
S. E. Funnell**

**National Library
of Canada**

**Acquisitions and
Bibliographic Services**

**395 Wellington Street
Ottawa ON K1A 0N4
Canada**

**Bibliothèque nationale
du Canada**

**Acquisitions et
services bibliographiques**

**395, rue Wellington
Ottawa ON K1A 0N4
Canada**

Your file Votre référence

Our file Notre référence

The author has granted a non-exclusive licence allowing the National Library of Canada to reproduce, loan, distribute or sell copies of this thesis in microform, paper or electronic formats.

The author retains ownership of the copyright in this thesis. Neither the thesis nor substantial extracts from it may be printed or otherwise reproduced without the author's permission.

L'auteur a accordé une licence non exclusive permettant à la Bibliothèque nationale du Canada de reproduire, prêter, distribuer ou vendre des copies de cette thèse sous la forme de microfiche/film, de reproduction sur papier ou sur format électronique.

L'auteur conserve la propriété du droit d'auteur qui protège cette thèse. Ni la thèse ni des extraits substantiels de celle-ci ne doivent être imprimés ou autrement reproduits sans son autorisation.

0-612-72084-5

Canada

Department of Civil and Environmental Engineering

The Undersigned recommend to the Faculty of Graduate Studies
and Research acceptance of the thesis

**Flexural and In-Plane Compressive Behaviour of Composite
Structural Laminate Plates**

submitted by

Scott E. Funnell, B.Eng.

in partial fulfilment of the requirements for the degree of
Master of Engineering

J. L. Humar, Chair, Department of Civil and Environmental Engineering

S. J. Kennedy, Thesis Supervisor

Carleton University
Ottawa, Ontario, Canada

May, 2000

Abstract

A composite structural laminate was developed to provide an impact resistant hull structure for double hull product oil tankers to resist extreme loads like collisions and groundings and to minimize the probability of rupture and oil outflow. The composite structural laminate plate provides the strength and stiffness of traditional stiffened steel plates for normal operating loads without the primary stiffening. This construction allows significant simplification and the elimination of all the corresponding intersections, which are a major source of corrosion and fatigue problems. The engineered structural polyurethane elastomer core is an energy absorptive, puncture resistant layer that provides thermal insulation, additional dampening and an effective crack arrest layer.

To effectively integrate this type of construction into practice requires the development of simple design equations that will accurately predict the behaviour of the CSL members subject to flexure, compression, or both. The design equations were verified experimentally through large scale testing of CSL beams and columns, which represent the full range of anticipated behaviour, and was further supported and extended with analytical evidence. A series of bond strength tests for varying temperatures were conducted to obtain data to set limits for the maximum design shear stress at the interface to preclude one possible local failure mode. It was concluded that the strength and stiffness of this type of construction can be described using existing design equations for steel considering the steel faceplates only (the core contribution is negligible). The core with the specified minimum modulus of elasticity stabilizes the steel faceplates and prevents all probable local buckling failure modes.

Acknowledgements

I would like to offer my thanks to the following people who made my studies at Carleton tolerable.

My supervisor, Dr. Stephen Kennedy, for supporting me financially and academically, supplying me with the right tools, and putting in the time to get the job done. I appreciate it.

The boyz at ie, Angelo and Dale. Thanks for your help guys. All I had to do was pick up that phone.

Pierre Trudel, Stan Conley and Ken McMartin of the Civil Laboratory staff. Between Pierre's wizardry and Stan's mastery of the testing machine arts, it was a wonder I wasn't out of there in a matter of days.

The previous graduate students, the Fuller and Raby show and Bobby Han, who imparted their knowledge and got me started.

Finally, my family and friends who provided a sounding board for my occasional ranting and an encouraging note at the end of a long day.

Table of Contents

Abstract	i
Acknowledgements	ii
Table of Contents	iii
List of Figures	vii
List of Tables	xii
List of Symbols	xiv
1. Introduction	
1.1 General	1
1.2 Composite Structural Laminate Plates	4
1.3 Finite Element Modelling	8
1.4 Objectives and Scope	10
1.5 Thesis Outline	11
2. Experimental Programme	
2.1 General	12
2.2 Material Characterization	13
2.2.1 Steel Characterization Tests	13
Tension Coupon Tests	13
2.2.2 Elastomer Characterization Tests	14
Tension Coupon Tests	15
Compression Disc Tests	15

2.2.3	Bond Capacity	16
2.3	Flexural Behaviour	21
2.3.1	Specimen Preparation	23
2.3.2	Instrumentation	25
2.3.3	Test Procedure	27
	Static Tests	27
	Fatigue Tests	28
2.4	In-Plane Behaviour	30
2.4.1	Stub Column and Component Parts	31
2.4.1.1	Specimen Preparation	32
2.4.1.2	Instrumentation	32
2.4.1.3	Test Procedure	32
2.4.2	Pin-Ended Columns	34
2.4.2.1	Specimen Preparation	37
2.4.2.2	Instrumentation	37
2.4.2.3	Test Procedure	43
3.	Material Characterization of Steel, Elastomer, and Interface Bond Strength	
3.1	General	45
3.2	Steel Stress-Strain Characteristics	45
3.3	Elastomer Stress-Strain Characteristics	47
3.3.1	Tension	47
3.3.2	Compression	47
3.3.3	Determination of Bond Strength	52

4.	Flexural Results, Finite Element Analyses and Fatigue Resistance	
4.1	General	58
4.2	Geometry	58
4.3	Flexure Behaviour and Test Results	60
4.4	Finite Element Analyses and Comparison	74
4.4.1	General	74
4.4.2	Analysis Assumptions and Modelling Notes	74
4.4.3	Material Characterization	75
4.4.4	Geometry, Boundary Conditions and Loading	76
4.4.5	Discussion	78
4.5	Fatigue	84
4.6	Limit States Design	86
5.	Flexural Test Results and Finite Element Analyses	
5.1	General	90
5.2	Geometry	91
5.3	Cross-sectional Strength	95
5.4	Overall Member Stability	103

5.5	Finite Element Analyses and Comparison	120
5.5.1	General	120
5.5.2	Analysis Assumptions and Modeling Techniques	121
5.5.3	Material Characterization	121
5.5.4	Geometry, Boundary Conditions and Loading	122
5.5.5	Discussion	126
5.5.6	Limit States Design	141
6.	Summary, Conclusions, Recommendations and Future Work	
6.1	Summary	146
6.2	Conclusions	148
6.3	Recommendations and Future Work	150
	References	152

List of Figures

1.1	Components of a Typical 40,000 DWT Product Oil Tanker Tank Section ..	3
1.2	Failure Modes and Limit States for CSL Beams (after Braun, 1999)	7
1.3	Failure Modes and Limit States for CSL Columns (after Braun, 1999)	7
1.4	Typical ANSYS Solid Element Results.....	9
2.1	Tension Coupon	13
2.2	Elastomer Ancillary Test Specimens	15
2.3	Bond Specimen Apparatus (after Braun, 1999)	18
2.4	Direct Tension Bond Test Specimen and Apparatus Definition	19
2.5	Shear Bond Test Specimen and Apparatus Definition	19
2.6	Typical Locations of Temperature Measurements for Bond Specimens	20
2.7	Large Scale Specimen Cross-section	21
2.8	Schematic Diagram of Flexure Test Set-up	22
2.9	Knife Edge Roller Reaction Assembly	23
2.10	4000mm SPS Casting Apparatus	24
2.11	Instrumentation for Flexure Test Specimens	26
2.12	Typical Strain Gauge Arrangements for Flexure Tests	27
2.13	Typical LVDT Arrangements for Flexure Tests	27
2.14	Fatigue Resistances for Categories A to F (after CAN/CSA-S16.1-94)	29
2.15	Methods for Restraining Top Loading Plate	30
2.16	Stub Column Test Set-up	31

2.17	Instrumentation for Stub Column and Components	33
2.18	Pin-Ended Column Test Set-up	35
2.19	Knife Edge Load Assembly	36
2.20	Knife Edge Reaction Assembly	36
2.21	Out-of-Straightness Measuring Device and Locations	38
2.22	Instrumentation Arrangement for Column Test Specimens	39
2.23	Typical Strain Gauge Arrangement for Column Tests	43
2.24	Typical LVDT Arrangement for Column Tests	43
3.1	Typical Stress-Strain Curve, Steel Tension Coupon F3-4	46
3.2	Typical Tensile Stress-Strain Curves for Core-Removed and Thin-Plaque Elastomer	49
3.3	Typical Compressive Stress-Strain Curves for Core-Removed and Thin-Plaque Elastomer	49
3.4	Typical Bond Stress-Relative Displacement Curves	54
3.5	Shear Stresses in Direct Tension Bond Test Specimen	56
3.6	Bond Stress vs. Temperature Comparison	57
3.7	Relative Displacement vs. Temperature Comparison	57
4.1	Measurement Locations	59
4.2	Flexure Test Set-up	61
4.3	Typical Moment versus Mid-span Deflection Relationships for Flexure Specimens	61

4.4	Flexure Test Results – FS7-1	63
4.5	Flexure Test Results – FS7-2	64
4.6	Flexure Test Results – FS6-3	65
4.7	Flexure Test Results – FS5-5	66
4.8	Flexure Test Results – FS5-6	67
4.9	Flexure Test Results – FSR-7	68
4.10	Uneven Loading of Flexure Specimen	70
4.11	Delaminated Flexural Specimens	71
4.12	Ductility of FS5-6 at $\delta_{max} = 127\text{mm}$	73
4.13	Mooney-Rivlin Stress-Strain Comparison	76
4.14	Finite Element Geometry and Boundary Conditions for Flexure Model	77
4.15	Analytical Results – FS7-2	79
4.16	Deflected Shape Comparison at Plastic Moment Capacity, M_p	80
4.17	Von Mises Stresses at Plastic Moment Capacity, M_p	81
4.18	Interface Shear Stresses at Plastic Moment Capacity, M_p	82
4.19	Fatigue Test Results	85
4.20	Failure Mode of Specimen FF6-4	85
4.21	Failure Modes and Limit States for CSL Beams (after Braun, 1999)	87
4.22	Stiffness Approximation Factor, D_{comp}/D_s	89
5.1	Measurement Locations	92
5.2	Initial Out-of-Straightness of Columns	94

5.3	Eccentric Loading of Knife Edge	95
5.4	Stub Column Set-up	96
5.5	Typical Compressive Test Results, 300mm SPS	
	Stub Column, IS3-0b	97
5.6	Typical Compressive Test Results, 300mm Steel Faceplate	98
5.7	Compressive Test Results, 300mm Elastomer Core	99
5.8	Failure Modes of Stub Column and Components	102
5.9	In-Plane Compression Set-up	103
5.10	Characteristic Load versus Lateral Mid-height	
	Deflection Curves	104
5.11	Compression Test Results – IS31-b (500mm)	106
5.12	Compression Test Results – IS4-2 (1000mm)	108
5.13	Typical Compression Test Results – IS4-3 (1500mm)	110
5.14	Compression Test Results – IS2-4 (2000mm)	112
5.15	Compression Test Results – IS3-5 (2500mm)	114
5.16	Specimen IS3-1b (500mm)	117
5.17	Specimen IS4-2 (1000mm)	118
5.18	Specimen IS4-3 (1500mm)	118
5.19	Specimen IS2-4 (2000mm)	119
5.20	Specimen IS3-5 (2500mm)	119
5.21	Finite Element Geometry and Boundary Conditions	
	for Stub Column Model, 300mm	122

5.22	Finite Element Geometry and Boundary Conditions	
	for Compression Model, 1500mm	124
5.23	Initial Out-of-Straightness Approximation Methods	125
5.24	Finite Element Model for Eccentrically Applied Load	125
5.25	Analytical Results – IS3-0b (300mm Stub Column)	128
5.26	Analytical Results – IS3-1b (500mm)	129
5.27	Analytical Results – IS4-2 (1000mm)	130
5.28	Analytical Results – IS4-3 (1500mm)	132
5.29	Analytical Results – IS2-4 (2000mm)	134
5.30	Analytical Results – IS3-5 (2500mm)	137
5.31	Failure Modes and Limit States for CSL Columns (after Braun, 1999)	141
5.32	C_r/C_y versus Slenderness Ratio for SPS 10-50-10 Columns	145

List of Tables

1.1	Elastomer Core Material Specifications for Maritime Applications (after Braun, 1999)	5
2.1	Specified Mechanical Properties of Polyurethane EC-609-002/18 (after Elastogran, 1999)	14
2.2	Bond Test Schedule	17
2.3	Stress Ranges for Fatigue Tests	29
3.1	Characteristic Material Properties Determined from Uniaxial Tension Coupon Tests: Elastic Range	46
3.2	Characteristic Material Properties Determined from Uniaxial Tension Coupon Tests: Inelastic Range	46
3.3	Characteristic Material Properties of Elastomer Tension Coupons Cast as Thin Plaques and Post-Cured	50
3.4	Characteristic Material Properties of Elastomer Tension Coupons Removed from Cast Specimen Core	50
3.5	Characteristic Material Properties of Elastomer Compression Discs Cast as Thin Plaques and Post-Cured	51
3.6	Characteristic Material Properties of Elastomer Compression Discs Removed from Cast Specimen Core	51
3.7	Estimated Test Temperatures for Bond Specimens	53

3.8	Bond Strength Summary	55
3.9	Proposed Bond Strength as a Function of Temperature	57
4.1	Total Measured Thicknesses, δ	59
4.2	Constant Moment Region Geometric Properties	60
4.3	Flexure Test Results	69
4.4	Finite Element Results and Comparison	78
4.5	Fatigue Test Results	85
4.6	Test-to-Predicted Moment Capacities	87
4.7	Calculated Flexural Stiffness Factors, D_{comp}/D_s	89
5.1	Total Thicknesses, δ	92
5.2	Geometric Properties of Compressive Specimens	93
5.3	Results Summary for Stub Column and Components	101
5.4	Axial Strains through Thickness of Typical Length Specimens	116
5.5	Compression Test Results	117
5.6	Analytically Determined Ultimate Compression Capacities and Test-to-Predicted Ratios	140
5.7	Test-to-Predicted Compressive Strengths	145

List of Symbols

A	Area of steel cross-section
ASTM	American Society for Testing and Materials
b	Specimen width
C_e	Euler buckling capacity of steel cross-section
C_r	Applied axial load
COV	Coefficient of Variation
C_r	Ultimate compressive capacity
CSL	Composite Structure Laminate
C_y	Compressive yield load
d_2	Total specimen thickness, side 2
d_4	Total specimen thickness, side 4
d_c	Thickness of the core
D_{comp}	Experimental flexural stiffness of composite
D_p	Predicted flexural stiffness
D_s	Flexural stiffness of the steel section alone
DT	Direct tension bond action
$d\theta$	Change in end rotation, degrees
$d\theta'$	Change in end rotation, radians
E	Modulus of elasticity
e	Eccentricity
e_1	Eccentricity subsequent to rotation

E_c	Compressive modulus of elastomer
E_{core}	Average modulus of elasticity of the core
E_s	Strain-hardening modulus
E_t	Tensile modulus of elastomer
F_s	Steel stress range
F_y	Yield strength
I	Moment of Inertia
K	Effective length factor
L	Length of column
LVDT	Linear Variance Differential Transformer
M_e	Moment at proportional limit
M_d	Moment at premature (debonding) failure
MDI	Diphenylmethane-diisocyanate
M_p	Plastic moment capacity
MTS	Material testing system
M_y	Elastic moment capacity
N	Number of cycles
n	Compressive resistance parameter
R	Radius of curvature
r	Radius of gyration
S	Elastic Section Modulus
s	Point of contact between knife edge and knife edge plate
Sh	Shear bond action

S-N	Stress range versus number of cycles
SPS	Sandwich Plate System
t	Faceplate thickness
t/p	Test-to-predicted ratio
U_{1x}	Magnification factor for applied moment
x	Location of projected end of the column
x_0	Initial distance along slope from contact surface to plate edge
x_c	Distance along slope from projected centre of column to plate edge
Z	Plastic Section Modulus
Φ	Resistance factor
δ	Mid-span or mid-height deflection
δ_A	Axial displacement
δ_d	Deflection at failure
ϵ_f	Strain at failure
ϵ_{π}	Strain-hardening strain
ϵ_u	Ultimate strain
ϵ_y	Yield strain
λ	Stiffness factor
λ_{exp}	Stiffness factor derived experimentally
μ	Mean
ν	Poisson's ratio
θ_0	Initial slope of knife edge

σ_f	Stress at failure
σ_{sy}	Static yield
σ_u	Ultimate stress
σ_y	Yield stress
τ_b	Ultimate bond stress
τ_{br}	Bond stress range
ω_1	Uniform bending effect coefficient

Chapter 1

Introduction

1.1 General

The grounding of the Exxon Valdez in 1989 prompted legislation by the United States Government in the form of the Oil Pollution Act of 1990 to specify minimum requirements with regards to navigation safety and manning standards, and oil tanker structural requirements for all oil carriers accessing United States coastal or inland waters in an attempt to minimize environmental damage in the event of an accident. Despite legislation and continued advancements in navigational technology, environmental and economical disasters persist as exemplified by the following headline which appeared in the New York Times December 13, 1999 following the grounding of the oil tanker, Erika and an estimated 8000 tonnes of heavy crude oil following it into the surrounding waters off the Brittany Coast. "Tanker Sinks, Spilling Oil off the French Coast."

Unforeseen and unavoidable mechanical and human error coupled with an aging fleet and amplified by the inconsistencies of nature will always be a factor in open water transport. Accidents or extreme load events will always occur. To achieve the objective of minimizing environmental damage (zero oil outflow), ship structures must be designed to produce a "crashworthy" vessel that anticipates these conditions. Provisions for this design case are not explicitly given in current Classification Society rules and regulations for the design of ships and need to be developed.

Existing all-steel double hull technology has several identified structural problems associated with its design, including; structural complexity (as illustrated in Figure 1.1(a)), a proliferation of corrosion and fatigue prone details, and a construction that is susceptible to crack propagation that limits its "crashworthiness" or impact resistance and its ability to achieve the objective of zero oil outflow. New designs, design philosophies and innovative structural systems must be developed to resolve these problems.

A composite structure laminate (CSL) technology has been developed to resolve the problems associated with all steel construction and in conjunction with consistent design philosophies for extreme load events provides an enhanced impact resistance structure. The stiffened plates used for the double bottom structure, bilge, side structure, gunwale and deck are replaced with CSL panels constructed of steel-polyurethane elastomer-steel with equivalent strength and stiffness for normal operating loads to produce the simplified sections illustrated in Figure 1.1(b). The construction eliminates the stiffeners, the corresponding intersections, welding and fabrication. Increased simplicity results in a preferred geometry for coating application, reduced surface area requiring coating protection, and less congestion and details making inspection easier. Additional benefits resulting from the composite structural laminate system include reduced assembly and maintenance costs, reduced weight, better vibration control, crack arrest in the polyurethane core and the reduction or elimination of contaminant spillage subsequent to high impact loading.

The introduction of composite structural laminate plates into the maritime and civil structures requires substantial research and development work to provide the technical data (experimental evidence and analytical verification), design data, design

Figure 1.1 Components of a Typical 40,000 DWT Product Oil Tanker Tank Section

equations, and data or information on all aspects of the use of this type of construction over the life of the structures in which it will be incorporated. Broad categories of work include: development of the technical specifications and formulation for the polyurethane elastomer core: characterization of bond strength; behaviour when subjected to fire load; development and verification of member resistance formulations; determination of fatigue capacity, impact resistance, vibration and acoustic characteristics; methods of fabrication and repair; developments of inspections methods and procedures for quality control. This thesis focuses on the development and verification of member resistance formulations for composite structural laminate members subject to flexure, compression or both and on the determination of design values like bond strength which can only be determined by test.

1.2 Composite Structural Laminate Plates

A composite structural laminate plate consists of two steel faceplates fully bonded to a structural polyurethane elastomer core of constant or varying thickness. The core material is an engineered structural plastic that has been specifically developed to meet the conditions associated with its fabrication and use in maritime applications. The corresponding material specification is given in Table 1.1, (Braun, 1999).

The failure modes and limit states associated with the composite structural laminate members subject to flexure and compression are listed under the categories of strength, local buckling stability or overall member stability, fatigue, and serviceability in Figures 1.2 and 1.3, respectively. All of the local buckling failure modes have been precluded through the specification of a minimum core modulus which when fully

**Table 1.1 Elastomer Core Material Specifications for Maritime Applications
(after Braun, 1999)**

Normal Operating Conditions	
Condition	Description
Normal Operating Loads	<p>The predominant load case is a combination of hydrostatic and in-plane compressive loads due to the hogging and sagging moments as specified by the appropriate classification society.</p> <p>The material properties of the plastic should include:</p> <ul style="list-style-type: none"> • A modulus of elasticity greater than 275 MPa at the maximum operating temperature (100°C). • Sufficient bond strength to provide the required shear transfer between the steel plates and the tensile strength across the interface for transverse forces (negative hydrostatic pressure and delaminating forces from steel connections). • Fatigue strength to provide composite sandwich behaviour throughout the life of the vessel. • Minimum elongation of 20% at -45°C.
Ambient Temperature	<p>The normal operating temperature range as specified by Lloyd's Rules and Regulations (1994) Part 3, Chapter 3 is from -45°C to approximately 100°C (the maximum deck temperature for ships operating in the Gulf Region).</p>
Corrosion	<p>Corrosion may expose the plastic to seawater and possible harmful products carried by the vessel. It should have hydrolytic stability for both fresh water and seawater, and to a lesser extent chemical resistance to oils.</p>
Modification and Repair	<p>The plastic must provide sufficient resistance to heat induced by welding and must restrict the changes in material characteristics and bond to the region local to the weld.</p> <p>The plastic should have chemical characteristics and properties so that the damaged section could be cold cut (sawn) or flame cut from existing structure and removed.</p> <p>The characteristics of the off-gases in an oxygen and non-oxygen environment, and the resistance to heat and flame must be known.</p>

**Table 1.1 Elastomer Core Material Specifications for Maritime Applications
(Continued)**

Accidental or Extreme Load Events	
Condition	Description
Fire and Explosion	The sandwich plate system and plastic core must meet the requirements of SOLAS (1974) and subsequent amendments.
Collision and Grounding	<p>The plastic must provide the appropriate rebound resilience to be compatible with the steel faceplate tear strength, compressive strength, tensile strength and elongation such that the energy absorption of the sandwich plate system is maximized.</p> <p>The compressive and tensile strengths of the plastic should be greater than 20 MPa with ductility equal to or greater than that of steel.</p> <p>The plastic should have sufficient bond strength to maintain the composite behaviour of the sandwich plate system outside the damaged region so that the ship structure has sufficient residual strength to be rescued and repaired.</p>
Fabrication	
Condition	Description
Reaction Injection Moulding (RIM)	<p>The plastic material must be cast under shipyard conditions (temperatures and humidity ranges similar to those for applying epoxy-based paints).</p> <p>The plastic must be castable to precast plastic spacers and provide a homogeneous intermediate layer.</p> <p>Pumping equipment should have the capacity to pump at a rate of between 0.5 to 1.0 kg per second in a manner that prevents splash and air entrainment.</p> <p>Pumping equipment should have the ability to inject the plastic at any angle with a reach of 20 m.</p> <p>The pumping process may provide quick release ports that mitigate overflow problems and a monitoring system to ensure that the cavities are properly filled and not pressurized.</p> <p>On-site quality control tests to be established.</p>
Polymerization Shrinkage	<p>The degree of polymerization shrinkage must be minimized such that the integrity of the bond between core and faceplate is maintained.</p> <p>The addition of flocculates such as calcium carbonate or an acceptable amount of air entrainment (approximately 5% to 10%) to control the shrinkage must not significantly alter the strength and ductility of the plastic.</p>

Figure 1.2 Failure Modes and Limit States for CSL Beams (after Braun, 1999)

Figure 1.3 Failure Modes and Limit States for CSL Columns (after Braun, 1999)

bonded stabilizes the steel faceplates so that the yield strength can be obtained. This concept is analogous to the philosophy of and requirements given in CAN/CSA-S16.1-94 that specify maximum slenderness ratios for plate elements so that the plates achieve Class 3 behaviour and member resistance equations need only describe overall member behaviour for different actions.

1.3 Finite Element Modelling

Finite element modelling of the behaviour of composite structural laminate structures required experimental verification of:

- material modelling of hyper-elastic material in both tension and compression including the effects of using higher order polynomial Mooney-Rivlin curves, Ferro(1998),
- modelling assumptions and solution strategies, Braun (1999), Ferro (1998),
- modelling laminates with shell or solid elements (including optimizing of mesh density and aspect ratios), Braun (1999), Ferro (1998) and Bennett (1998)
- modelling of complex plate structures with perpendicular intersections subject to large strains, deflections and inelastic buckling, Ferro (1998) and Bennett (1998)

Based on this body of work finite element models were developed (with both shell and solid elements) for composite structural laminate members subject to flexure and compression with varying imperfections (initial out-of-straightness), cross-sectional properties, geometry, boundary conditions and material properties to determine the full

range of behaviour so that the experimental programs required for development of the corresponding member resistance equations could be defined, Braun (1999).

Given the breadth of experimental data to be verified and the detailed behaviour descriptions (shear distortions within the core and distributions of interface shear stresses as those illustrated in Figure 1.4) required to develop comprehensive design rules for strength, stability and serviceability, all finite element models used in this thesis were constructed with SOLID45 and HYPER58 solid elements for the steel faceplates and elastomer, respectively. The elements along the interfaces were assumed to be fully bonded. Proven solution strategies, material models and mesh densities were used.

Figure 1.4 Typical ANSYS Solid Element Results

1.4 Objectives and Scope

The main objectives of this thesis were:

- to conduct material tests to characterize the tensile and compressive behaviour of both the steel faceplates and polyurethane elastomer core to generate the data required for finite element modelling,
- to conduct a series of bond strength tests in direct tension and shear as a function of ambient temperature at the interface to determine minimum design values associated with the anticipated operating conditions for maritime applications,
- to conduct a series of flexural tests to generate the experimental data associated with the relevant strength and serviceability limit states to be used to verify solid element modelling techniques,
- to conduct a series of fatigue tests for varying bond stress levels (expressed as a function of ultimate bond capacity) to establish fatigue life,
- to conduct a series of stub column tests to establish the cross-sectional strength of the SPS,
- to conduct a series of pinned-ended column tests for varying slenderness to generate the experimental data associated with the limit state of overall member stability to be used to verify solid element modelling techniques,
- based on both experimental and analytical data, to develop appropriate design equations which describe the applicable limit states.

1.5 Thesis Outline

Chapter 1 simply describes the current state-of-the-art in performance and design for all-steel stiffened ship construction with respect to extreme loading events resulting in environmentally hazardous leaks, such as collisions or grounding. Also described is a new construction technology comprising of two plates and a structural polyurethane core which addresses the problems of all steel construction, provides an equivalent structure for operating loads and a superior impact structure for extreme load events. Material specifications for the elastomer core and limit states for flexure and in-plane compression are defined. Proven finite element techniques are summarized.

Chapter 2 describes the experimental programme, (ancillary tests, large scale tests for flexure and in-plane compression, instrumentation, boundary conditions, loading and scope).

Chapter 3 describes the results of all ancillary tests including the characterization of both the steel and elastomer and the shear and tension bond tests.

Chapters 4 and 5 describe the general behaviour of CSL members subjected to flexure and compression and give details of load-deflection behaviour and internal strain distributions. Comparative finite element analyses and discussions are given. The typical bond fatigue life is presented as a function of the applied stress range. Relevant design equations for these failure modes are presented along with statistical comparisons with experimental data.

Chapter 6 concludes the thesis with a brief overview of the experimental work conducted, the general behaviour observed, results of comparisons with numerical analysis and proposed design equations.

Chapter 2

Experimental Programme

2.1 General

The objectives of the experimental programme were:

- to conduct large scale tests which will describe fundamental behaviour such as flexure and in-plane stability,
- to generate design data which can only be obtained by test (bond strength), and
- to provide experimental data which will then be used to verify numerical models.

The basic sandwich section consists of two 10mm faceplates and a 50mm elastomer core and is referred to as SPS 10-50-10. All the bond specimens, large scale specimens, (flexure and in-plane compression), and fatigue specimens were machine cast by Elastogran, GmbH in Olching, Germany in molds specific to each specimen. These were then shipped to Canada , cut and machined to the appropriate sizes, instrumented, and subsequently tested according to the descriptions provided in the following sections.

2.2 Material Characterization

The compressive and tensile stress-strain characteristics were determined for both the steel and the polyurethane elastomer from tests on representative samples taken from cast specimens from flexural and column series.

2.2.1 Steel Characterization Tests

Tension Coupon Tests

Four steel plates, measuring 600 mm x 50 mm aligned with the longitudinal direction of the specimen, were cold cut from a cast section. These were machined to give the appropriate tension coupon geometry, instrumented and tested in accordance with ASTM E8M-88. The basic dimensions and instrumentation for a typical coupon is given in Figure 2.1.

Figure 2.1 Tension Coupon

Both the width and thickness of the reduced cross-section were measured for each specimen. Load was applied via an MTS controller which was integrated with a 1780 kN

Tinius Olsen testing machine. Strains and loads were measured and recorded, and the characteristic material properties determined subsequently.

2.2.2 Elastomer Characterization Tests

The structural polyurethane core, EC-609-002/18, was developed by Elastogran to meet the specifications outlined in Chapter 1. The material consists of two principle components, a polyol and catalyst mix, and a prepolymer containing diphenylmethane-diisocyanate (MDI). The specified mechanical properties cited by Elastogran for machine cast specimens, stored for seven days under standard climatic conditions with the polyol loaded with 9% air, according to the DIN standards are listed in Table 2.1.

The material characteristics of the EC-609-002/18 elastomer were determined from tests on elastomer samples, in accordance with the appropriate ASTM standards, taken from post-cured plaques and from the elastomer core of large scale cast specimens.

Post-curing of the plaques (thin plate samples) simulates the curing conditions of the large scale specimens which result from the exothermic reaction as the elastomer sets. Comparison of this data provides a correlation between thin, post-cured samples and large scale cast sections which may be useful in determining the material characteristics of in-situ samples that are not accessible.

**Table 2.1 Specified Mechanical Properties of Elastomer EC-609-002/18
(after Elastogran, 1999)**

Mechanical Properties	Measurements	Units	Test Procedure
Hardness	70	Shore D	DIN 53 505
Tensile Strength	22.7	N/mm ²	DIN 53 504
Elongation at break	26	%	DIN 53 504
E-modulus	517	N/mm ²	DIN 53 497

Tension Coupon Tests

Two sets of tension coupons with the nominal dimensions given in Figure 2.2(a) were tested in accordance with ASTM D412-83 Method A to obtain tensile stress-strain characteristics. The first set of eight coupons were taken from a 3 mm thick A4-sized plaque, and the second set of eight from the core of a cast specimen.

The width and thickness of the reduced sectional area were measured for each specimen. Tests were conducted in a 90 kN Instron testing machine at a load rate of 5.1mm/s. Engineering strains were obtained from displacement measurements made with a clip extensometer (50 mm gauge length), attached to the reduced area. The appropriate loads and displacements (strains) were recorded until failure occurred.

Compression Disc Tests

Two sets of compression discs, with nominal dimensions given in Figure 2.3(b) were tested in accordance with ASTM D575-83 Method A to obtain compressive stress-strain characteristics. The first set of nine discs were machined from a 12.7 mm plaque, and the second set of eleven discs were from the core of a cast specimen.

Figure 2.2 Elastomer Ancillary Test Specimens

The diameter and thickness were measured for each specimen. Testing was conducted in a 90 kN Instron testing machine at a load rate of 5.1 mm/s. Compressive engineering strains were determined from displacement measurements of the load platens recorded during the test. The specimen was monotonically loaded in compression until the capacity of the machine was reached.

2.2.3 Bond Capacity

The maximum design value for bond strength is equal to a statistically evaluated minimum based on tests conducted under conditions associated with the service life of the structure. This value can only be determined by experimental tests on representative samples that have been constructed under conditions similar to those anticipated. The bond strength is a function of load action across the interface, number of load cycles, surface preparation, type of primer or bonding agent used, temperature, casting conditions and exposure of the elastomer core to either sea water or oil for sections where the steel faceplates have corroded through.

Forty-seven direct tension and shear bond tests, (23 and 24, respectively), have been conducted on SPS 10-50-10 samples measuring approximately 100 mm x 100 mm in plan to determine the bond strength for varying temperatures associated with the specified operating range, (-45 to +100 °C). The bond test specimen designations associated with the particular test conditions, (bond action, (loading direction across interface), target core temperature and duration of time to stabilize test specimen temperature, (conditioning)), are listed in Table 2.2.

Table 2.2 Bond Test Schedule

Batch	No. of Direct Tension Samples	No. of Shear Samples	Target Temp (C)	Conditioning Time (days)
B	3	0	23	2
S	0	3	23	1
A	2	3	-40	1
B	3	3	60	1
C	3	3	23	1
D	3	3	-35	2
E	3	3	-35	7
F	3	3	40	2
G	3	3	100	2

The specimens were milled from machine-cast A4-sized plates and have nominal bonded surface areas of 4000 mm² and 6400 mm² for shear and direct tension, as illustrated in Figure 2.4(a) and Figure 2.5(a), respectively. The test specimens were fitted into a shear/tension bond test apparatus which was loaded by a 1780 kN Tinius Olsen testing machine via articulating, self-aligning load arms. An expanded isometric view of the test apparatus, views of the specimens within the apparatus and corresponding photographs are shown in Figures 2.3, 2.4 and 2.5. Figure 2.4(b) and 2.5(b) show the line of action to be along the interface for shear and perpendicular to the interface through the centre of the bonded area for direct tension.

Figure 2.3 Bond Specimen Apparatus (after Braun, 1999)

Figure 2.4 Direct Tension Bond Test Specimen and Apparatus Definition

Figure 2.5 Shear Bond Test Specimen and Apparatus Definition

All bond test specimens were temperature conditioned, either in an oven or freezer, for a period ranging from two to seven days at their target temperatures as given in Table 2.2. Each was removed, dimensioned, fitted into the test apparatus and loaded monotonically at a rate of 0.1 kN/s until debonding occurred. Both load and relative displacement between points *a* and *b*, shown in Figures 2.4 and 2.5, were measured and recorded throughout each test.

To determine the approximate temperature of the specimen at the time of failure, temperature measurements were made at varying combinations of points *a*, (steel), *b*, (core), *c*, (interface), and *d*, (internal core) as illustrated in Figure 2.6 for the different test series. All measurements were taken prior to, (~10 sec), and/or subsequent to (~15 sec), each test with either a Raytek non-contact thermometer or thermocouple. The temperature at the time of failure was calculated by linear interpolation of the temperatures recorded at the interface at the respective times.

Figure 2.6 Typical Locations of Temperature Measurements for Bond Specimens

2.3 Flexural Behaviour

Six 2000 mm long, simply supported SPS 10-50-10 beams with the nominal cross-section and proportions shown in Figure 2.7 were tested in the set-up depicted in Figure 2.8 to determine the flexural behaviour and ultimate moment capacity of the sections. One of these was intentionally cold cut in half and welded with a typical butt weld seam. As part of the repair procedure, the existing elastomer was cut back to provide a weld margin and recast after the weld was completed. Four additional flexure specimens were subjected to cyclic loading to obtain the fatigue capacity of the steel-elastomer bond interface at varying load levels.

Load was applied via a 670 kN MTS actuator through a distributing beam to provide a two-point load system and a constant moment region of 595 mm on the specimen. Knife-edge roller assemblies were used at both the load and reaction points to provide the appropriate translational and rotational degrees of freedom associated with a simply supported beam.

The reaction assemblies, as typically illustrated in Figure 2.9, are integrated with alignment sleeves that house the beam ends. The sleeves provide capacity to center the

Figure 2.7 Large Scale Specimen Cross-section

Figure 2.8 Schematic Diagram of Flexure Test Set-up

beam over the reaction point, and to fix it to the knife edge plate. Two 25mm diameter shear pins pass through each end of the specimen and the corresponding alignment sleeves providing shear restraint between the two steel faceplates, simulating continuous construction.

Figure 2.9 Knife Edge Roller Reaction Assembly

2.3.1 Specimen Preparation

All SPS 10-50-10 samples were constructed of primed and shot-blasted cold rolled steel, (of the same heat), and the EC-609-002/18 elastomer. Four-metre long plates were attached to and properly positioned by the mould shown in Figure 2.10. The mould was closed and the elastomer injected into the cavity through the lower end. Once the cavity was filled, the vent port was closed and the test specimen was cured by ambient heat given off by the chemical reaction. All specimens were cast by Elastogran GmbH in Olching, Germany and shipped to Canada. Two-metre long beam samples were cold-cut from these initial sections and prepared for testing, (installation of instrumentation and insertion of shear pins). The through thickness was measured at every 200mm along their length on either side.

Figure 2.10 4000mm SPS Casting Apparatus

2.3.2 Instrumentation

Strain and displacement data were measured by a series of strain gauges and LVDTs as illustrated in Figure 2.11. Only one half of the flexural specimen was instrumented since it was symmetrically loaded and restrained.

Twenty-one strain gauges with the orientation and positions shown in Figures 2.11 and 2.12 were used to measure flexural strains on both the steel faceplates and the core and through thickness strains in the core directly underneath the load plate. The numbering system was consistent for each test. Numbers that are outlined represent strain gauges located on the face opposite to that shown. All dimensions are given in millimetres.

LVDTs were used to measure characteristic displacements which include vertical deflections at midspan, directly under the load and mid-shear span, and horizontal displacements at both ends. End rotations were calculated from the horizontal displacement at the ends measured by LVDT pairs 1 and 2, and 9 and 10, which were separated by an approximate distance of 80mm and in contact with the rigidly attached alignment sleeve.

LVDTs for vertical deflection were located on either side of the specimen to give sufficient data to eliminate discrepancies due to twist that may result from misalignment. The LVDT numbering and symbols used in the figures are similar to those for the strain gauges.

Figure 2.11 Instrumentation for Flexure Test Specimens

Figure 2.12 Typical Strain Gauge Arrangements for Flexure Tests

Figure 2.13 Typical LVDT Arrangements for Flexure Tests

2.3.3 Test Procedure

Static Tests

Each prepared test specimen was installed and aligned in the test apparatus. Moulding plaster and steel shims were used at both the load and reaction points to ensure horizontal alignment and uniform bearing surfaces. Instrumentation was connected to the data acquisition system and tested to ensure it was functioning properly. A small load

was applied to seat the specimen, which was then removed and all instrumentation zeroed. Load was applied monotonically until failure with electronic readings taken every 10 kN up to the proportional limit, and then as required to describe the load-deflection curve.

Fatigue Tests

Four flexure specimens were subjected to cyclic loading to characterize the fatigue strength of the steel-elastomer bond and develop an S-N curve for the SPS for comparison with those existing for all-steel parent plates and standardized steel details given in Appendix K of CAN/CSA-S16.1-94 and as shown in Figure 2.14. S-N curves are generally illustrated on a log-log graph with number of cycles and stress range plotted on the x- and y-axis, respectively. Curves labeled A-E1 in Figure 2.14 represent the fatigue life of common, steel details described in Appendix K. Curve A corresponds to the parent plate material without fabrication details and represents the maximum possible fatigue life.

A comparable S-N curve for SPS without steel detailing would be illustrated on a log-log curve with number of cycles and bond stress range on the x- and y-axis, respectively. Ideally the fatigue capacity would be governed by steel details and not by bond, hence three of the tests are being conducted without details and one with a simple hole in the fatigue critical zone.

Table 2.3 gives the tensile stress ranges and the corresponding bond stress ranges for the four CSL beams with and without details.

Figure 2.14 Fatigue Resistances for Categories A to F (after CAN/CSA-S16.1-94)

Table 2.3 Stress Ranges for Fatigue Tests

Tensile Stress Range, F_w (MPa)	F_w/F_y	Bond Stress Range, τ_{br} (MPa)	τ_{br}/τ_b	Details
211	0.65	2.83	0.35	small hole
210	0.64	2.83	0.35	none
268	0.82	3.62	0.45	none
155	0.48	2.09	0.26	none

note: maximum bond stress = 8.0 MPa, taken from shear bond tests

The fatigue test specimens were prepared, instrumented and loaded in a similar manner to the flexural specimens with the appropriate load level. Due to the cyclic nature of the load, alignment pins and alignment pins with clip angles were used to prevent the load plates from moving, as shown in Figure 2.15. Note the alignment pins are located on the compression faceplate and do not present fatigue critical details.

Figure 2.15 Methods for Restraining Top Loading Plate

2.4 In-Plane Behaviour

A series of ten SPS 10-50-10 columns with the same cross-sectional properties and surface preparation as the flexure test specimens were tested to establish the compressive capacity of the composite cross-section, as well as the compressive resistance of sections with varying slenderness ratios and known boundary conditions. The resulting experimental data could then be used for the verification of numerical modelling techniques. The following sections describe tests associated with determining the cross-sectional strength of the SPS and its component parts, and the elastic and inelastic buckling strength of SPS pin-ended columns.

2.4.1 Stub Columns and Component Parts

Two stub columns, 300mm in length, were tested in a 1780 kN Tinius Olsen testing machine, as shown in the schematic diagram in Figure 2.16, to determine the compressive resistance of the composite cross-section. Two steel faceplates and one elastomer core of equal length were also tested to obtain the compressive strength of the individual components of the SPS. The specimens were raised off the load platens with a bearing column to allow clearance for the instrumentation.

Figure 2.16 Stub Column Test Set-up

2.4.1.1 Specimen Preparation

The 300mm SPS columns were cold-cut from a four-metre sample, constructed and cast in a similar manner to those described in Section 2.3.1. 300mm lengths of steel faceplate and elastomer core were taken from the central portion of a 500mm length of SPS. The ends of the stub columns and components were milled square to ensure uniform bearing, (parallel loading and reaction surfaces). All thicknesses and widths were dimensioned and recorded prior to instrumentation.

2.4.1.2 Instrumentation

The orientation, location and identification numbers for the strain gauges and LVDTs used to obtain the data for stub columns, steel faceplates and elastomer core are shown in Figure 2.17(a), (b) and (c), respectively. Numbers that are outlined indicate strain gauges and LVDTs located on the face opposite to that illustrated. All dimensions are in millimetres. In addition to the instrumentation shown, two LVDTs were positioned to measure the relative displacement between the load and reaction platens.

2.4.1.3 Test Procedure

Each prepared 300mm specimen was placed between and aligned with the centre of the load platens. Instrumentation was connected and tested, and pre-loads were applied to each sample. The position of the test specimen was adjusted to give a uniform strain distribution across the thickness and width. The specimen was then loaded monotonically until failure, with electronic readings taken every 10 kN until the proportional limit was reached, and then as required to describe the load-deflection curve.

Figure 2.17 Instrumentation for Stub Column and Components

2.4.2 Pinned-Ended Columns

Eight columns, with nominal lengths and corresponding slenderness ratios, (given in brackets), of 500mm, (21), 1000mm, (38), 1500mm, (55), 2000mm, (71), and 2500mm (88), were tested as pinned-ended columns in the set-up shown in Figure 2.18 to determine the compressive resistance and buckling behaviour of SPS columns.

Load was applied via a 4500 kN Enerpac actuator. Knife edge assemblies were used at the load and reaction points at either end of the column to provide the rotational degrees of freedom associated with pinned-pinned conditions. This method introduced a small, constant eccentricity of the axial load with respect to the column's centroid.

The ends of the column were fixed to their respective knife edge plates with alignment sleeves and constrained against twisting and translation with set screws. Hinged-mechanisms were used to secure, without restraint, the alignment sleeve and knife edge plate to the corresponding knife edge at the top end.

Detailed elevations and isometric views of the knife edge load and reaction assemblies shown in Figures 2.18 are illustrated in Figures 2.19(a) and (b), and 2.20(a) and (b), respectively. The set screws were used to centre and fix the end of the column within the alignment sleeve.

Figure 2.18 Pinned-Ended Column Test Set-up

Figure 2.19 Knife Edge Load Assembly

Figure 2.20 Knife Edge Reaction Assembly

2.4.2.1 Preparation

The columns were cut to the required lengths from the 4000mm sections cast by Elastogran. The ends of the columns were milled square to provide uniform and parallel bearing surfaces. The length of the column and through thickness, (at every 200mm along its length), were measured and recorded. The initial out-of-straightness was determined from the average of the dial gauge measurements taken on both sides of the column with the measuring device shown schematically in Figure 2.21(a). The dial gauges measure the relative position of their plungers, along the centre of the column, with respect to the contact points located at either end of the device, off-centre, as illustrated in Figures 2.21(b) and (c). A Precision Granite Surface was used to zero the device prior to measuring each column. Note the length of the measuring device and number and position of dial gauges was tailored to the column lengths being measured, (1500mm set-up shown in figure).

2.4.2.2 Instrumentation

The instrumentation, (strain gauge and LVDT), arrangement for the 500mm, 1000mm, 1500mm, 2000mm and 2500mm specimens are illustrated in Figures 2.22(a), (b), (c), (d) and (e), respectively.

Strain gauges were placed on the steel faceplates and exposed surfaces of the elastomer core at the quarter-points of the column lengths to determine principal strains at the cross-sections. Additional strain gauges were placed on the core about mid-height to determine through thickness strains in that region. The position and orientation of these gauges are illustrated in the details given in Figure 2.23.

Figure 2.21 Out-of-Straightness Measuring Device and Locations

The LVDTs required for measuring out-of-plane displacements were attached to a frame fastened to each alignment sleeve at a height corresponding to the interface between the knife edge plate and the end of the column, as shown in Figure 2.24(a). The frame allowed for relative end rotations and displacements. LVDTs attached to the actuator and alignment sleeves, as shown in Figures 2.24(b) and (c) respectively, measured actuator displacements and vertical displacements from which the end rotations could be calculated.

Figure 2.22(a) Instrumentation Arrangement for 500mm Column Specimens IS2-1 and IS3-1b

Figure 2.22(b) Instrumentation Arrangement for 1000mm Column Specimen IS4-2

**Figure 2.22(c) Instrumentation Arrangement for 1500mm Column
Specimens IS4-3, IF2-6 and IF4-7**

Figure 2.22(d) Instrumentation Arrangement for 2000mm Column Specimen IS2-4

Figure 2.22(e) Instrumentation Arrangement for 2500mm Column Specimen IS3-5

Figure 2.23 Typical Strain Gauge Arrangement for Column Tests

Figure 2.24 Typical LVDT Arrangement for Column Tests

2.4.2.3 Test Procedure

The prepared test specimens were positioned and aligned within the test set-up illustrated in Figure 2.18. Electronic instrumentation was connected to the data acquisition system and tested. A 50 kN preload was applied to each column to seat the specimen and to centrally locate it across its width. The preload was removed, and the

instrumentation was zeroed. Each column was then loaded monotonically, under displacement control, up to and past its ultimate compressive resistance until debonding occurred or the lateral deflections became excessive. Measurements were taken and recorded at every 20 kN, or as the load-deflection curve dictated.

Chapter 3

Material Characterization of Steel, Elastomer, and Interface Bond Strength

3.1 General

This chapter gives the compressive and tensile characteristics of both the steel and elastomer material used in the construction of the CSL plate test specimens for the flexural and in-plane compression test programmes. Also given are the test results for the bond strength between the elastomer and the unprimed, shot blasted steel as a function of temperature and direction of interface loading, (shear or direct tension).

3.2 Steel Stress-Strain Characteristics

Figure 3.1 illustrates a typical stress-strain curve for a steel tension coupon, F3-4, which was tested in accordance to ASTM E8M-88. Points 1 through 16 give the stress-strain data pairs used to define the multi-linear curve (for both tension and compression) that was used in subsequent finite element analysis predictions. The elastic and strain-hardening moduli, E and E_s , Poisson's ratio, ν , static yield, σ_y , strain at which strain-hardening begins, ϵ_s , and stress and strain at yield, σ_y and ϵ_y , ultimate, σ_u and ϵ_u , and failure, σ_f and ϵ_f are listed for each of the four coupons tested in Tables 3.1 and 3.2 along with the corresponding means, standard deviations and coefficients of variation.

Figure 3.1 Typical Stress-Strain Curve, Steel Tension Coupon F3-4

Table 3.1 Characteristic Material Properties Determined from Uniaxial Tension Coupon Tests: Elastic Range

	E (MPa)	ν	σ_y (MPa)	ϵ_y	$\sigma_{0.2}$ (MPa)
F3-1	200000	0.287	334.0	0.001700	302.5
F3-2	206000	0.292	335.0	0.001500	268.5
F3-3	205000	0.323	310.0	0.001500	307.2
F3-4	194000	0.273	324.0	0.001800	282.8
μ	201250	0.294	325.8	0.001625	290.3
Std. Dev.	5500	0.021	11.6	0.000150	17.9
COV	0.027	0.072	0.036	0.092308	0.062

Table 3.2 Characteristic Material Properties Determined from Uniaxial Tension Coupon Tests: Inelastic Range

	E_{pl} (MPa)	ϵ_{pl}	$\sigma_{0.2}$ (MPa)	$\epsilon_{0.2}$	σ_r (MPa)	ϵ_r
F3-1	1700.0	0.017400	441.0	0.150000	404.0	0.197000
F3-2	1906.0	0.016600	442.5	0.151000	380.1	0.200000
F3-3	2381.0	0.015000	431.0	0.150000	384.0	0.185800
F3-4	2150.5	0.014000	436.0	0.148000	389.5	0.200000
μ	2034.4	0.015750	437.6	0.149750	389.4	0.195700
Std. Dev.	295.5	0.001535	5.2	0.001258	10.5	0.006750
COV	0.145	0.097469	0.012	0.008403	0.027	0.034491

3.3 Elastomer Stress-Strain Characteristics

3.3.1 Tension

Typical tensile stress-strain relationships for elastomer cast as thin-plaques and post-cured, and for elastomer removed from the core of a cast specimen were obtained from tension coupon tests conducted in accordance with ASTM D412-83 and are illustrated in Figure 3.2. Tables 3.3 and 3.4 list the corresponding values of the elastic tensile modulus, E_t , and the stress and strain values at a 0.2% offset, (as illustrated in Figure 3.2), and ultimate, (σ_y and ϵ_y , and σ_u and ϵ_u , respectively), for each group of tests.

The material strengths and stiffnesses determined for elastomer removed from the cast specimen core were significantly higher than those taken from the post-cured thin plaques, with ratios of 1.66 and 3.75 for modulus of elasticity and yield stress, respectively. Note, the standard deviation and coefficient of variation for the core-cast values are considerably less. Considering that the test specimen, procedure, temperature, rate of loading and instrumentation were the same for both sets, it can only be concluded that material characterization samples must be taken from large sections cast and cured in the same manner as those being investigated. The appropriate properties were used for subsequent finite element analyses.

3.3.2 Compression

Typical compressive stress-strain relationships for elastomer cast as thin-plaques and post-cured, and for elastomer removed from the core of a cast specimen were obtained from compression disc tests conducted in accordance with ASTM D575-83 Method A and are illustrated in Figure 3.3. Tables 3.5 and 3.6 list the corresponding

values of the elastic compressive modulus, E_c , and the stress and strain values at a 0.2% offset, (as illustrated in Figure 3.3), and ultimate, (σ_y and ϵ_y , and σ_u and ϵ_u , respectively), for each group of tests. Note, the ultimate stress and strain of the compressive discs were governed by the capacity of the testing apparatus and not the material.

Similar to the tension coupon results, the material strengths and stiffnesses determined for elastomer removed from the cast specimen core were significantly higher than those taken from the post-cured thin plaques, with ratios of 1.73 and 2.50 for modulus of elasticity and yield stress, respectively. As per the conclusions drawn from the tensile data, material characterization samples must be taken from large sections cast and cured in the same manner as those being investigated. The appropriate properties were used for subsequent finite element analyses.

Figure 3.2 Typical Tensile Stress-Strain Curves for Core-Removed and Thin-Plaque Elastomer

Figure 3.3 Typical Compressive Stress-Strain Curves for Core-Removed and Thin-Plaque Elastomer

Table 3.3 Characteristic Material Properties of Elastomer Tension Coupons Cast as Thin Plaques and Post-Cured

Specimen	E_p MPa	σ_y MPa	ϵ_y mm/mm	σ_w MPa	ϵ_w mm/mm
Zt1	625.0	5.25	0.011	8.42	0.286
Zt2	255.0	5.25	0.012	14.60	0.358
Zt3	336.5	7.25	0.014	16.51	0.378
Zt4	410.7	3.00	0.010	15.13	0.381
Zt5	359.4	5.38	0.018	14.75	0.411
Zt6	312.5	4.70	0.020	12.82	0.417
Zt7	365.4	3.25	0.012	7.60	0.456
Zt8	395.8	3.85	0.014	14.30	0.412
μ	383	4.74	0.014	13.02	0.387
Std Dev	109.5	1.38	0.004	3.26	0.051
cov	0.29	0.29	0.26	0.25	0.13

Table 3.4 Characteristic Material Properties of Elastomer Tension Coupons Removed from Cast Specimen Core

Specimen	E_p MPa	σ_y MPa	ϵ_y mm/mm	σ_w MPa	ϵ_w mm/mm
F3-1	*				
F3-2	640.0	18.50	0.033	24.60	0.353
F3-3	680.0	19.00	0.035	24.75	0.320
F3-4	600.0	18.00	0.033	25.30	0.365
F3-5	572.0	16.75	0.028	24.75	0.325
F3-6	667.0	16.00	0.025	27.00	0.380
F3-7	*				
F3-8	700.0	19.50	0.030	26.00	0.362
μ	643	17.96	0.031	25.40	0.351
Std Dev	49.2	1.35	0.004	0.94	0.024
cov	0.08	0.07	0.12	0.04	0.07

note: data for F3-1 and F3-8 omitted due to equipment malfunction

Table 3.4 Characteristic Material Properties of Elastomer Compression Discs Cast as Thin Plaques and Post-Cured

Specimen	E_p MPa	σ_y MPa	ϵ_y mm/mm	σ_w MPa	ϵ_w mm/mm
Zc1	200.0	8.3	0.039	77.2	0.610
Zc2	225.0	10.2	0.049	70.0	0.618
Zc3	200.0	9.9	0.048	66.0	0.615
Zc4	233.3	10.5	0.049	69.0	0.602
Zc6	220.0	9.5	0.044	69.5	0.612
Zc7	212.5	8.5	0.042	75.5	0.640
Zc8	228.1	9.8	0.044	70.0	0.620
Zc9	228.1	10.5	0.041	72.5	0.635
μ	218.4	9.6	0.045	71.2	0.619
Std Dev	12.91	0.84	0.004	3.66	0.013
cov	0.06	0.09	0.09	0.05	0.021

Table 3.5 Characteristic Material Properties of Elastomer Compression Discs Removed from Cast Specimen Core

Specimen	E_p MPa	σ_y MPa	ϵ_y mm/mm	σ_w MPa	ϵ_w mm/mm
F3-1	302.6	23.5	0.09	89.5	0.544
F3-2	396.2	25.00	0.069	102.00	0.590
F3-3	413.8	23.00	0.057	68.50	0.471
F3-4	409.1	24.00	0.061	91.50	0.553
F3-5	404.3	25.50	0.068	94.00	0.556
F3-6	384.6	22.00	0.057	95.50	0.558
F3-7	375.0	26.50	0.072	87.00	0.527
F3-8	395.3	26.00	0.069	73.00	0.476
F3-9	379.3	24.00	0.065	91.50	0.541
F3-10	385.7	24.00	0.058	88.50	0.538
F3-11	312.5	21.00	0.069	86.50	0.541
μ	378	24.05	0.067	87.95	0.536
Std Dev	37.0	1.67	0.009	9.61	0.035
cov	0.10	0.07	0.14	0.11	0.06

3.4 Determination of Bond Strength

Forty-seven tests were conducted to determine the characteristic bond strength between the polyurethane elastomer core and the shot-blasted steel as a function of bond action across the interface (shear (Sh) or direct tension (DT)) and ambient temperature. Three series of test samples (T and S; A, B and C; and D, E, F and G highlighted in blue, green and yellow in Table 3.7) were cast by Elastogran in three corresponding A4-sized sections, shipped to Canada, machined and tested at Carleton. The test specimen designations identify the test series and successive test number. Table 3.7 also identifies with each test specimen the bond action, target temperature, temperature of the specimen prior to the test and after the test, and an estimated interface temperature at failure.

Test series T, S and C were tested at a measured room temperature of 23°C. A series of temperatures were taken with the Raytek non-contact thermometer immediately prior to each test (~10 seconds) and averaged for test series A and B. For series E, F and G, two sets of temperature measurements were taken immediately prior to and subsequent to each test, (~10 and ~15 seconds, respectively), to estimate the temperature at failure. Accurate temperature measurements were not obtained for series D. Estimated test temperatures were calculated on the assumption that variations in temperature with respect to time would be similar to those from test series E, which was conducted under identical conditions.

Controlling and maintaining the target temperature at the bond interface was difficult, if not impossible. Ideally, these tests should be conducted in a temperature chamber with a constant ambient temperature equal to the target temperature.

Table 3.7 Estimated Test Temperatures for Bond Specimens

Test Specimen Designation	Bond Action	Test Target	Temperature (°C)				
			Prior to Test	Subsequent to Test	Estimated Value		
T	DT	23	-	-	23.0		
S	Sh		-	-	23.0		
A1	DT		-40	~ -15	-	-15.0	
A2		-			-15.0		
A3		-			-15.0		
A4		-			-15.0		
A5	Sh	-			-15.0		
A6		-			-15.0		
B1		-			-15.0		
B2	DT	60	~ 43	-	43.0		
B3				-	43.0		
B4				-	43.0		
B5	Sh			-	43.0		
B6				-	43.0		
C				DT/Sh	23	-	-
D1	DT			-35	-	-	-7.0
D2		-	-		-7.0		
D3		-	-		-7.0		
D4	Sh	-	-		-7.0		
D5		-	-		-7.0		
D6		-	-		-7.0		
E1	DT	-19	-1		-11.8		
E2		-5	2		-2.2		
E3		-14	5		-6.4		
E4	Sh	-15	10		-5.0		
E5		-19	5		-9.4		
E6		-6	13		1.6		
F1	DT	40	35	34	34.6		
F2			37	35	36.2		
F3			37	37	37.0		
F4	Sh		36	29	33.2		
F5			41	39	40.2		
F6			-	-	36.2		
G1	DT	100	69	55	63.4		
G2			75	62	69.8		
G3			78	65	72.8		
G4	Sh		74	55	66.4		
G5			78	68	74.0		
G6			77	61	70.6		

Figure 3.4 illustrates the typical bond stress-relative displacement curves for direct tension and shear bond action across the interface at a test temperature of 23 °C. The bond stress is simply calculated by dividing the applied load by the bonded area. Table 3.8 summarizes the bond strength values obtained for each test series, the corresponding target temperature and bond action. The mean values and coefficients of variation are also listed.

Figure 3.4 Typical Bond Stress-Relative Displacement Curves

Table 3.8 Bond Strength Summary

Series Designation	Target Test Temp (degrees)	Bond Action	Number of tests	Bond Stress (MPa)	Standard Deviation	Coefficient of Variation
T	23	DT	3	3.60	0.858	0.240
S		Sh	3	8.33	1.458	0.175
A	-40	DT	2	6.06	0.146	0.025
		Sh	3	7.24	2.204	0.304
B	60	DT	3	3.72	0.115	0.031
		Sh	3	6.45	0.204	0.032
C	23	DT	3	4.16	0.407	0.098
		Sh	3	7.68	0.747	0.097
D	-35	DT	3	1.46	0.658	0.450
		Sh	3	6.76	0.804	0.120
E	-35	DT	3	1.86	0.565	0.303
		Sh	3	5.81	1.167	0.201
F	40	DT	3	1.62	0.160	0.099
		Sh	3	5.94	1.070	0.180
G	100	DT	3	1.95	0.345	0.177
		Sh	3	3.25	0.738	0.227

The bond strength for direct tension samples are lower than those tested in shear. The 50mm thick core of the specimen has sufficient length that necking due to Poisson's effect, as illustrated in Figure 3.5, introduces additional shear stresses at the corners, peeling the elastomer away from the interface surface, reducing the bonded area and yielding a sudden debonding failure with an apparent reduced average bond strength. This was verified by Braun (1999) with finite element modelling of a typical tension bond test. Bond stress values obtained from shear tests give a better representation of the bond strength for continuous CSL plate sections as localized deformations associated with the isolated sample that cause premature failure are essentially eliminated. The remaining discussion will pertain to the results of the bond tests conducted in shear.

Figure 3.5 Shear Stresses in Direct Tension Bond Test Specimen

Figure 3.6 illustrates the relationship between ultimate shear bond stress (MPa) and estimated test temperature ($^{\circ}\text{C}$) for all bond series tested in shear. Figure 3.7 illustrates the maximum relative displacement as a function of temperature for the same series of tests.

Based on this limited data set it can be concluded that;

- the bond strength has temperature dependent characteristics that are similar to other elastomer material properties, and
- relative displacement is independent of temperature.

The dashed line illustrated in Figure 3.6 represents a lower bound to all bond strength values and could serve as a limit to the maximum shear stress along the elastomer-steel interface to be used in design. Proposed bond strength equations corresponding to the experimental data are given in Table 3.9.

Figure 3.6 Bond Stress vs. Temperature Comparison

Figure 3.7 Relative Displacement vs. Temperature Comparison

Table 3.9 Proposed Bond Strength as a Function of Temperature

$(\tau_b)_{max}$ (MPa)	Temperature Range (°C)
6	< 55
$17 - 0.2T(^{\circ}C)$	$55 < T < 75$
2	> 75

Chapter 4

Flexural Results, Finite Element Analyses and Fatigue Resistance

4.1 General

This chapter describes the characteristic flexural behaviour of SPS 10-50-10 beams, details representative strain distributions, gives a description of the finite element model developed to verify the application of finite element modelling and compares the analytical and experimental results. Existing, rational mathematical design equations have been applied to describe the flexural capacity of the SPS beams. The fatigue resistance of the steel-elastomer bond interface has also been determined from a series of four fatigue tests.

4.2 Geometry

Based on measurements of the rolled steel faceplates, the width was determined to be 200mm, and the average thickness 9.93mm with a coefficient of variation of 0.011. Prior to each test, the total thickness (two faceplates and core) was measured on both sides 2 and 4 at 200mm increments along the length of each specimen as illustrated in Figure 4.1, and are listed in Table 4.1. Based on the measurements made within the constant moment region, relevant geometric properties; average core depth, moment of inertia, and elastic and plastic section moduli were calculated. These are listed in Table 4.2. These geometric properties were based on the steel sections alone as the contribution

Figure 4.1 Measurement Locations

Table 4.1 Total Thicknesses, d

Specimen Designations	side	Measured Thickness along Specimen Length, mm										
		a	b	c	d	e	f	g	h	i	j	k
FS7-1	2	67.57	67.84	68.64	68.94	69.58	69.35	69.30	69.88	70.45	70.69	70.99
	4	70.68	71.20	72.44	73.14	73.01	72.50	72.67	72.63	73.81	74.21	74.13
FS7-2	2	70.70	70.85	71.16	71.54	71.60	70.90	70.68	71.11	70.72	70.63	69.70
	4	67.50	68.26	68.41	68.21	67.81	67.17	67.42	68.66	69.26	69.42	68.69
FS6-3	2	68.55	69.76	71.48	72.15	72.54	72.56	72.31	72.33	72.67	73.18	73.43
	4	66.23	67.07	68.31	68.81	68.45	68.55	68.75	70.61	70.32	70.88	70.58
FS5-5	2	73.36	73.06	72.92	72.89	72.66	72.61	72.52	72.13	71.98	71.64	71.41
	4	72.23	71.63	70.90	71.23	70.06	69.87	70.03	69.27	68.26	68.91	68.72
FS5-6	2	68.64	69.12	68.92	69.26	68.83	68.27	67.96	68.73	69.39	68.83	68.48
	4	70.07	70.54	70.68	72.05	71.12	70.07	69.70	70.13	70.82	70.98	70.89
FSR-7	2	68.26	67.61	66.51	65.58	65.35	65.55	65.12	65.40	65.28	65.33	65.58
	4	68.87	67.43	65.77	64.88	64.93	65.43	65.45	66.04	66.15	65.85	66.16

Table 4.2 Constant Moment Region Geometric Properties

$$I = 2 \left[\left(\frac{bt^3}{12} \right) + bt \left(\frac{d-t}{2} \right)^2 \right]$$

$$Z = bt(d-t)$$

$$S = \frac{b(d^3 - d_c^3)}{6d}$$

Specimen Designations	d_c (mm)	I (10^6 mm^4)	S (10^3 mm^3)	Z (10^3 mm^3)
FS7-1	51.24	3.75	105.44	121.48
FS7-2	49.55	3.55	102.17	118.13
FS6-3	50.70	3.68	104.39	120.41
FS5-5	51.45	3.77	105.84	121.90
FS5-6	49.62	3.55	102.30	118.27
FSR-7	45.37	3.07	94.11	109.83

of the transformed core was negligible due to the small modular ratio, approximately 0.0032.

Specimens are designated with an alphanumeric code which identifies the direction and method of loading, the specimen's cast number and the sequenced test number. For example, specimen FS7-2 designates flexure, (F), and static, (S), test conditions, was cut from the seventh cast sample, (7), and was the second specimen tested, (2). Note, for specimen FSR-7, the 'R' indicates that it was the repaired specimen.

4.3 Flexure Behaviour and Test Results

A typical flexural test set-up of a 2000mm long, simply-supported beam subject to two point loads, is illustrated in Figure 4.2. The knife edge roller load and reaction assemblies, linear variable differential transformers (LVDTs), loads and reactions and the shear span are highlighted.

Figure 4.2 Flexure Test Set-up

Figure 4.3 Typical Moment versus Mid-span Deflection Relationships for Flexure Specimens

The flexural behaviour is best described by characteristic moment versus mid-span deflection curves such as those illustrated in Figure 4.3. Points a, b and c on the curve labeled FS7-2 represent the calculated bending moments associated with the onset of non-linear behaviour, yield and full plastic capacity. Point d on FS7-1 represents the calculated bending moment at the load at which premature (debonding) failure occurred. All moments are calculated from measured loads and an initial shear span measuring 629.5mm.

Specific moment versus mid-span deflection curves and flexural strain distributions for mid-shear span, under the load point and at mid-span are given for each of the six tests in Figure 4.4 to 4.9. Strain distributions are illustrated for key behaviour at points a, b, c and d, (where applicable), identified on each moment-deflection curve. Each point on the distribution curves, (solid circle), with the exception of the flexural strains under the load point, is an average of two strain measurements taken across the section at that particular location. Positive and negative values represent tensile and compressive values, respectively. Assuming that the flexural strain distributions through the core are linear, and given that the strains at the interface must be equal for fully bonded surfaces, the flexural strain distributions through the thickness can be drawn as shown. The dotted lines, representing the strain distribution through the steel thicknesses, are based on these assumptions. The yield strain ($1619 \mu\text{s}$) as determined from the tension coupon tests is shown on the applicable strain distribution graphs.

The flexural stiffness and characteristic moment values calculated from measured data from each test and the corresponding failure modes are summarized for the flexure test series in Table 4.3.

(a) Moment versus Mid-span Deflection Curve

(b) Strain Gauge Locations

(c) Flexure Strains within Shear Span

(d) Flexure Strains at Mid-span

Figure 4.4 Flexural Test Results - FS7-1

(a) Moment versus Mid-span Deflection Curve

(b) Strain Gauge Locations

(c) Flexure Strains within Shear Span

(d) Flexure Strains at Load Point

(e) Flexure Strains at Mid-span

Figure 4.5 Flexure Test Results – FS7-2

(a) Moment versus Mid-span Deflection Curve

(b) Strain Gauge Locations

(c) Flexure Strains within Shear Span

(d) Flexure Strains at Load Point

(e) Flexure Strains at Mid-span

Figure 4.6 Flexure Test Results – FS6-3

(a) Moment versus Mid-span Deflection Curve

(b) Strain Gauge Locations

(c) Flexure Strains within Shear Span

(d) Flexure Strains at Load Point

(e) Flexure Strains at Mid-span

Figure 4.7 Flexure Test Results – FS5-5

(a) Moment versus Mid-span Deflection Curve

(b) Strain Gauge Locations

(c) Flexure Strains within Shear Span

(d) Flexure Strains at Load Point

(e) Flexure Strains at Mid-span

Figure 4.8 Flexure Test Results – FS5-6

(a) Moment versus Mid-span Deflection Curve

(b) Strain Gauge Locations

(c) Flexure Strains within Shear Span

(d) Flexure Strains at Load Point

(e) Flexure Strains at Mid-span

Figure 4.9 Flexure Test Results – FSR-7

Table 4.3 Flexure Test Results

Specimen Designation	EI (10^9 Nmm^2)	Moments, kNm				Failure Mode
		a	b (M_y)	c (M_x)	d	
FS7-1	396.3	29.1	-	-	33.4	delamination of top steel faceplate within shear span
FS7-2	398.8	28.4	34.0	37.4	-	plastic moment capacity was reached
FS6-3	404.3	22.3	-	-	25.1	delamination of top steel faceplate within shear span
FS5-5	405.7	-	-	-	26.7	delamination of both steel faceplates coupled with a brittle fracture through the thickness of the core
FS5-6	401.4	31.3	34.3	38.6	-	plastic moment capacity was reached
FSR-7	332.1	27.1	31.4	34.6	-	plastic moment capacity was reached

The premature debonding failures associated with FS7-1, FS6-3 and FS5-5 were unanticipated and the cause only clearly identified from observations made during several subsequent tests. Measurements of cross-sectional dimensions indicated that the faceplates were not necessarily parallel along the length nor across the width, and in some cases, the latter varied by as much as 4.2mm. When loaded, the flexural specimen twisted until it became fully seated against the load and reaction knife edge plates, as illustrated in Figure 4.10. Twisting introduced additional shear stresses, which when superimposed upon the shear stresses due to flexure within the shear span, exceeded the bond capacity causing delamination prior to the flexural specimen reaching cross-sectional capacity. To avoid the introduction of these unwanted shear stresses, moulding plaster and shims were used at both the load and reaction points to ensure full bearing without twisting.

Figure 4.10 Uneven Loading of Flexure Specimen

Pictures of delaminated flexural specimens FS6-3 and FS5-5 are shown in Figure 4.11(a) and (b), respectively. As a result of sudden debonding, the corresponding shear span assumed a double curvature shape with little or no visible end rotation. The variation in set-up conditions from the first two specimens to the third specimen suggest that the critical interface became that of the tension plate for FS5-5 instead of the top compression plate. This resulted in a delamination of the bottom plate from mid-shear span outward towards the load and reaction points. The sudden release near the load point caused the core, (now shear critical), to fracture through its thickness and further delamination of the top plate to the load point. The flexure specimens were tested in a state of neutral equilibrium without horizontal restraint along their length. Asymmetric failure due to delamination in one shear span led to a sudden translation of the beam, as illustrated by the lateral displacement, δ , given in Figure 4.11(a).

(a) FS6-3

(b) FS5-5

Figure 4.11 Delaminated Flexural Specimens

The remaining test specimens, all properly seated and not shear bond critical within the shear span, reached full cross-sectional strength, the plastic moment capacity of the steel sections alone, including the repaired specimen. Based on the load-deformation response and on measured strains, these flexural specimens showed substantial ductility in the range of 14,000 to 18,000 μs without buckling of the compression steel faceplate in the constant moment region. The ductility is clearly illustrated in Figure 4.12(a) where FS5-6 has been plastically deformed through a radius of curvature of approximately 1370mm. The corresponding strain distributions are illustrated in Figure 4.12(b). Note, the maximum deflection was not limited by the specimen, but by the stroke of the actuator for the given test.

The only other relevant observation is the increased flexibility (reduced flexural stiffness) of the CSL due to the shear deformations of the flexible core. The average ratio of the stiffness determined from the load-deflection curve to the transformed stiffness for the six beams was 0.54.

(a) radius of curvature

(b) flexural strain distribution at mid-span

Figure 4.12 Ductility of FS5-6 at $\delta_{max} = 127\text{mm}$

4.4 Finite Element Analyses and Comparison

Objective:	To model the load-deflection relationships derived experimentally for Specimens FS7-2 and FS5-6 and obtain comparable plastic moment capacities of the sections.
Analysis Type:	Nonlinear, static
Element Types:	Structural solid, SOLID45 Hyperelastic solid, HYPER58 Elastic shell, SHELL63 Target element, TARGE170 Contact element, CONTA173

4.4.1 General

The finite element program ANSYS, version 5.5, was used to model the experimental flexure programme and the specimens which reached plastic moment capacity. Nodal and elemental solutions of the numerical analyses were compared to experimental strains, stresses and deflections to verify the finite element modelling technique. The following sections discuss the solution options used, material characterization of the hyperelastic core and the modeled geometry and boundary conditions. The results of the analyses and their validity are then discussed, concluding with the proposed mathematical models for flexural CSL members.

4.4.2 Analysis Assumptions and Modelling Notes

The Newton-Raphson approach was used for this solution since the flexural specimen is subjected to large deformations and there are significant shear deformations within the flexible core. The stress stiffening option was used in conjunction with the

large strain effects to account for any additional in-plane stiffness resulting from out-of-plane elemental stresses.

4.4.3 Material Characterization

The steel was modeled with a multilinear stress-strain curve that was based on stress-strain data obtained from tension coupon tests on steel plates taken from a section of one of the flexure specimens, and shown on the typical stress-strain plot in Figure 3.1.

The elastomer core material is best modeled using hyperelastic elements and a Mooney-Rivlin elastic potential function (non-linear stress-strain relationship), Ferro (1998) and Braun (1999). The Mooney-Rivlin function can be described by second-, fifth- or ninth-order polynomials in which the corresponding Mooney-Rivlin constants are determined by ANSYS and are based on experimentally obtained uniaxial stress-strain data for both tension and compression. The best Mooney-Rivlin function fit to the maximum anticipated strain range for the large scale flexural and in-plane compressive tests was obtained using the ninth-order polynomial as determined from experimental data between $\pm 50,000 \mu\text{s}$. The corresponding function is illustrated in Figure 4.13 along with the stress-strain data determined experimentally. Variations between the curve fit and experimental data have little or no effect on the member's strength discovered by the steel section and on stiffness as small variations in modulus in this modular range are insignificant, (Braun, 1999).

Figure 4.13 Mooney-Rivlin Stress-Strain Comparison

4.4.4 Geometry, Boundary Conditions and Loading

Given that the flexure test specimen and loading was symmetric, it may be modeled about the plane of symmetry at mid-span as shown in Figure 4.14. Note, all displacements along the length of the specimen are relative to the plane of symmetry which is constrained in that direction, as is the case for the flexure specimen, which is tested in a state of neutral equilibrium.

The knife edge plates and their contact with the steel faceplates were modeled using shell elements, and target and contact elements, respectively. The contact surfaces available in ANSYS allow surface-to-surface contact between the plates, taking into

Figure 4.14 Finite Element Geometry and Boundary Conditions for Flexure Model

consideration the coefficient of friction between the two materials. The contact option selected enforces contact and permits sliding between surfaces if friction is overcome. The coefficient of sliding friction for steel on steel was taken as 0.74, Serway (1990).

The flexural specimen was loaded by prescribing uniform displacements along the centreline of the shell elements on the top steel faceplate, (modeling knife edge loading).

4.4.5 Discussion

The results of the finite element analyses are characterized by the moment versus mid-span deflection curve illustrated along with the corresponding experimental test, FS7-2 in Figure 4.15(a). Points 'b' and 'c' are the same as previously defined, and correspond to the first yield strains in the extreme fibres of the steel faceplates and full-yield through the faceplates and point 'e' is an arbitrary point corresponding to the maximum deflection set for the analysis.

As illustrated by the graph, the strength and stiffness predicted analytically closely match the experimental curve. The stiffness and strength values obtained both experimentally and analytically for each test along with the corresponding test-to-predicted ratios are listed in Table 4.4. The calculated mean values and coefficients of variation for the strength and stiffness are 0.98 and 0.021, and 0.96 and 0.050, respectively.

Given that the characteristic behaviour can accurately be predicted, then there's confidence that the internal behaviour is also accurately predicted. Figure 4.15(b), 4.16, 4.17 and 4.18 illustrate flexural strain distributions at mid-span, deflected shapes and end rotations, Von Mises stresses for both faceplates and elastomer core, and the relevant interface shear stresses at plastic moment capacity.

Table 4.4 Finite Element Results and Comparison

Specimen	Stiffness (10^9 Nmm^2)			Plastic Moment Capacity (kNm)		
Designations	D_{exp}	D_p	t/p	test	predicted	t/p
FS7-2	398.8	395.5	1.01	37.39	38.70	0.97
FS5-6	401.6	439.6	0.91	38.56	38.73	1.00
FSR-7	332.1	350.2	0.95	34.59	35.78	0.96

(a) moment versus mid-span deflection comparison

(b) flexure strain distribution at mid-span

Figure 4.15 Analytical Results - FS7-2

Figure 4.16 Deflected Shape Comparison at Plastic Moment Capacity, M_p

Figure 4.17 Von Mises Stresses at Plastic Moment Capacity, M_p

Figure 4.18 Interface Shear Stresses at Plastic Moment Capacity, M_p

The flexural strain distributions in the analytical model at plastic moment capacity and maximum mid-span deflection are shown in Figure 4.15(b) along with the previously introduced flexural strain distribution of test FS7-2 at the maximum applied load. The results are comparable, with the discrepancy in the tension faceplate due to differing mid-span deflections at the respective test times.

The deflected shapes obtained analytically and experimentally, shown in Figures 4.16(a) and (c), are similar. Note, the additional deflections due to shear deformation of the core are difficult if not impossible to measure in the test, but can be seen on the analytical end rotation figure when magnified 100 times.

The Von Mises stresses given in Figure 4.17 simply confirm that the plastic moment capacity is reached when the faceplates are fully yielded. Note, the maximum Von Mises stress in the core occurs within the shear span and has a value of 9.1 MPa.

The interface shear stresses given on the core face in Figure 4.18 are directly comparable to the interface shear stresses developed for the shear bond test specimens. The maximum value of 5.17 MPa is less than the critical bond stress of 8.0 MPa for a temperature equivalent to that experienced during the flexure test. This corroborates observations from the test in which the specimen remained fully bonded. The shear stresses are essentially uniform throughout the entire shear span region. Note, the maximum interface shear stress was calculated using basic mechanics of materials to be 4.9 MPa which compares well with that determined analytically.

It can be concluded that the solid finite element model provides an excellent predictor of flexural behaviour and can be used with confidence to describe the behaviour of more complex plate systems as long as the maximum shear stresses in the core do not exceed the relevant bond strength for the particular temperature.

4.5 Fatigue

The fatigue capacity of the flexure specimens is best described by the modified S-N curve in Figure 4.19. Points 'a', 'b', 'c' and 'd' represent the four fatigue tests conducted, and are listed with their corresponding specimen designations, flexure and bond stress ranges and number of cycles before test completion, (N), in Table 4.4.

With the exception of specimen FF6-4, (point 'a' on the figure), all fatigue test results lie on the line corresponding to Detail A, associated with plain members, in Figure 4.19. This verifies that for the loading conditions and set-up geometry of the specimens tested, the interface bond capacity does not govern for fatigue. The bond stress ranges developed for the corresponding load levels, shown in Table 4.4, suggest this result, with the highest bond stress reaching only 0.45 of the ultimate bond capacity. FF6-4 failed prior to reaching the specified number of cycles for its applied stress range due to the introduction of simple hole details in the fatigue critical tension faceplate within the constant moment region. This resulted in a fatigue fracture across the plate propagating from each hole as shown in Figure 4.20. Point 'a' on the graph associates the fatigue strength of beam FF6-4 with Detail D, equivalent to the net sectional strength of riveted connections.

Table 4.4 Fatigue Test Results

point	Tensile Stress Range, F_{sr} (MPa)	F_{sr}/F_y	Bond Stress Range, τ_{br} (MPa)	τ_{br}/τ_{ult}	N ($\times 10^3$)	Details
a	211	0.65	2.83	0.35	79.9	small hole
b	210	0.64	2.83	0.35	800	none
c	268	0.82	3.62	0.45	400	none
d	155	0.48	2.09	0.26	3000	none

Figure 4.19 Fatigue Test Results

Figure 4.20 Failure Mode of Specimen FF6-4

4.6 Limit States Design

The development of design equations for this or any other structural element requires an understanding of the behaviour under specific load actions. For flexure, these limit states are associated with flexural strength, load plate stability, fatigue capacity at the interface and serviceability as illustrated in Figure 4.21.

Current steel standards generally eliminate the probability of local plate buckling by specifying that sections must meet Class 3 requirements. For these CSL plates, local plate buckling is advantageously eliminated as a probable failure mode by specifying a minimum core modulus. For flexure members, the symmetric and inherent out-of-plane stability precludes lateral torsion buckling. Based on experimental and analytical evidence, the flexural strengths associated with the CSL beams are equivalent to the elastic and plastic moment capacities of the steel faceplates, which are well described by equations 4.1 and 4.2 from § 13.5(a) and (b) from CAN/CSA-S16.1-94, respectively;

$$M_y = \Phi S F_y \quad (4.1)$$

where, M_y = yield moment capacity
 Φ = resistance factor
 S = elastic section modulus
 F_y = yield strength

$$M_p = \Phi Z F_y \quad (4.2)$$

where, M_p = plastic moment capacity
 Z = plastic section modulus

Figure 4.21 Failure Modes and Limit States for CSL Beams (after Braun, 1999)

Table 4.5 lists the test, predicted, and test-to-predicted ratio (t/p) values for both elastic and plastic moment capacities, (where applicable), for the flexural tests conducted. Φ was taken as 1.0 since all material and geometric properties used in these calculations were based on measurements of each test specimen. The average t/p ratio and coefficient of variation for the plastic moment capacity was 0.98 and 0.019, respectively. Note, there was no local plate buckling for any of the flexure specimens tested as the core modulus was greater than the minimum specified to prevent this failure mode.

Table 4.5 Test-to-Predicted Moment Capacities

Specimen Designation	Elastic Moment Capacity (kNm)			Plastic Moment Capacity (kNm)		
	test, t	predicted, p	t/p	test, t	predicted, p	t/p
FS7-1	na	34.51	na	na	39.81	na
FS7-2	33.96	33.44	1.02	37.39	38.70	0.97
FS6-3	na	34.18	na	na	39.94	na
FS5-5	na	34.65	na	na	39.94	na
FS5-6	34.30	33.45	1.03	38.56	38.73	1.00
FSR-7	27.09	30.80	0.88	34.59	35.98	0.96

The plastic moment capacity can be reached only if composite action is maintained. This implies that the average interface shear stress, which can be calculated by basic mechanics of material, (VQ/It) is less than the minimum specified bond stress, which is achieved through proper material specifications.

Based on a limited series of fatigue tests which varied the ratio of the interface bond stress to the bond strength, (from 0.26 to 0.45), it was determined that the fatigue capacity of the CSL plate would be limited not by bond, but by steel details.

The analytical models accurately predict stiffness and can be used in parametric studies to develop semi-empirical relationships to give flexural stiffnesses of the composite section as a function of the flexural stiffness of the steel alone. Based on the parametric studies done by Braun (1999), the following empirical relationship to calculate the stiffness factor, λ , was developed.

$$\lambda = \frac{D_{comp}}{D_s} = 0.36 + 0.0005E_{core} \quad (4.3)$$

where, D_{comp} = flexural rigidity of composite section
 D_s = flexural rigidity of steel sections
 E_{core} = average modulus of elasticity for core material

This equation along with the data and the probable range of core moduli are illustrated in Figure 4.22. Stiffness factors were calculated for the flexural specimens using the composite stiffnesses obtained experimentally and the stiffnesses of the steel sections alone calculated from measured dimensions and are listed in Table 4.6. The mean value for λ_{exp} , 0.54, has a coefficient of variation of 0.026 and has been plotted on Figure 4.22.

Figure 4.22 Stiffness Approximation Factor, D_{comp}/D_s

Table 4.6 Calculated Flexural Stiffness Factors, D_{comp}/D_s

Specimen Designation	D_s (10^9 Nmm ²)	D_{comp} (10^9 Nmm ²)	Stiffness Factor D_{comp}/D_s
FS7-1	754.7	396.3	0.53
FS7-2	714.4	398.8	0.56
FF6-3	740.6	404.3	0.55
FF5-5	758.7	405.7	0.53
FS5-6	714.4	401.4	0.56
FSR-7	617.8	332.1	0.54

Chapter 5

In-plane Compressive Results and Finite Element Analyses

5.1 General

This chapter describes the characteristic compressive behaviour of SPS 10-50-10 beam-columns with varying slenderness ratios that failed by cross-sectional strength and buckling. Finite element models were developed for each test to verify the application of commercial finite element packages to model SPS. Each column was modeled with solid elements and measured geometric properties, analyzed and compared with the corresponding experimental data. Verification allows additional structural data to be obtained from the analysis such as shear stresses at the interface that can't be obtained experimentally. In addition, verification allows the extrapolation of modelling and analysis techniques for problems with structural configurations and loading that are impractical or difficult to obtain experimentally. Existing, rational mathematical design equations have been applied to describe the compressive capacity of these SPS beam-columns. This comparison identifies the key parameters for predicting the ultimate capacity of these and other elements like CSL plates.

Note, specimen identification codes are designated with an alphanumeric code which identifies the direction and method of loading, the specimen's cast number and the sequenced test number, (starting at zero). For example, specimen IS4-2 designates in-plane compression, (I), and static, (S), test conditions, was cut from the fourth cast sample, (4), and was the second sample tested, (2).

5.2 Geometry

Similar to the flexure test specimens, the rolled steel faceplates of the column specimens had measured widths of 200mm and an average thickness of 9.93mm with a coefficient of variation of 0.011. Prior to each test, measurements of the total thickness (two faceplates and core) were taken along each side of the specimen at intervals of either 200mm or 250mm, as illustrated in Figure 5.1, to give the data from which the cross-sectional geometric properties along the length of the column could be calculated. These are listed in Table 5.1.

Geometric properties related to overall member stability, measured specimen length, slenderness, (L/r), average core depth, moment of inertia, (I), plastic section modulus (Z), and maximum initial out-of-straightness are listed in Table 5.2. With the exception of stub-columns IS3-0a and IS3-0b, all other specimens were tested as pinned-ended columns with knife edge plate assemblies located at either end of the column. The column length for this latter set-up was taken to be the distance between the points of contact the knife edges make with respect to the corresponding plates, (illustrated in Figure 5.2), and includes two 3mm copper plates provided at each end of the column to ensure uniform bearing and a total of 129.3mm for the knife edge plates.

The slenderness values given in the table were calculated for a sandwich plate cross-section with faceplates of equal thickness, (Plantema, 1966).

$$\frac{L}{r} = \frac{2L}{d} \quad (5.1)$$

where, L/r = slenderness ratio
 L = length of column, mm
 d = column thickness, mm, centre-to-centre of faceplates

(a) plan view of 1500mm column

(b) cross section

Figure 5.1 Measurement Locations

Table 5.1 Total Thicknesses, d

Specimen Designations	side	Measured Thickness along Specimen Length, mm									
		a	b	c	d	e	f	g	h	i	j
IS2-1	2	67.33	68.15	67.52							
	4	69.94	70.19	70.23							
IS3-1B	2	68.90	69.06	68.31							
	4	71.71	71.63	71.06							
IS4-2	2	71.60	71.19	70.46	70.83	71.22	71.69				
	4	68.31	68.09	68.60	68.02	67.92	67.76				
IS4-3	2	67.80	67.86	67.71	68.91	68.58	67.60	67.12			
	4	71.56	71.55	70.80	71.05	71.27	70.82	71.54			
IS2-6	2	69.84	69.01	69.06	70.03	70.02	68.65	68.35			
	4	67.27	65.50	65.78	66.46	67.28	66.27	66.20			
IS4-7	2	71.20	71.09	70.30	69.31	69.61	69.66	68.70			
	4	73.60	73.12	73.04	72.76	72.01	72.02	71.45			
IS2-4	2	68.31	69.53	70.41	71.40	70.96	70.32	71.27	72.34	73.47	
	4	66.17	66.39	67.54	68.45	68.33	68.64	69.37	70.19	70.57	
IS3-5	2	71.04	71.30	71.58	71.67	70.38	69.86	70.49	71.27	71.05	70.63
	4	69.68	69.26	69.45	69.05	67.54	69.67	67.48	67.69	67.41	67.62

Table 5.2 Geometric Properties of Compressive Specimens

Specimen Designation	Length (mm)	L/r	d_c (mm)	I (10^6 mm^4)	Z (10^3 mm^3)	Initial Out-of-Straightness (mm)
IS3-0a	302.5	na	49.38	3.53	117.79	na
IS3-0b	298.0	na	49.26	3.51	117.55	na
IS2-1	632.3	21.45	49.03	3.48	117.09	0.65
IS3-1b	631.3	20.98	50.25	3.63	119.52	-0.38
IS4-2	1131.3	37.89	49.78	3.57	118.58	0.56
IS4-3	1633.3	54.76	49.72	3.57	118.46	0.61
IS2-6	1630.5	56.31	47.98	3.36	115.01	1.74
IS4-7	1633.3	53.25	51.42	3.77	121.84	-0.81
IS2-4	2125.3	71.18	49.79	3.57	118.60	0.82
IS3-5	2627.3	87.93	49.83	3.58	118.68	-1.13

The initial out-of-straightness for each column was calculated as the average of the out-of-straightness measurements taken on opposite faces and are illustrated in Figure 5.2. The maximum values for each specimen are listed in Table 5.2 with the negative or positive sign indicating the position relative to the known initial eccentricity of the load for the test set-up, (negative values indicate towards the applied load, and vice-versa).

The knife edges used to simulate pinned-ended conditions introduced an initial eccentricity of the axial loading to the column centroid, (curved knife edge surface in contact with sloped knife edge plate), as illustrated in Figure 5.3. Points 'x' and 's' represent the projected end of the column and the point of contact between the knife edge and the knife edge plate, respectively. The horizontal component of this distance is equivalent to the eccentricity of the load and reaction points, and can be described in terms of end rotation by Equation 5.2.

- the initial location of the eccentric load, $e = 9.83\text{mm}$, is relative to the centroid and measured initial out of straightness of the columns
- point s is the point of contact between the knife edge and knife edge plate

Figure 5.2 Initial Out-of-Straightness of Columns

Figure 5.3 Eccentric Loading of Knife Edge

$$e_1 = (x_0 - rd\theta' - x_c) \cos(\theta_0 - d\theta) \quad (5.2)$$

where,	e_1	= load eccentricity subsequent to rotation, mm
	x_0	= initial distance along slope from contact surface to plate edge, 113.82 mm
	r	= radius of knife edge, 37.5 mm
	$d\theta'$	= change in end rotation, radians
	x_c	= distance along slope from projected centre of column to plate edge, 103.63 mm
	θ_0	= initial slope of knife edge, 15.20 degrees
	$d\theta$	= change in end rotation, degrees

5.3 Cross-Sectional Strength

A typical 300mm long SPS 10-50-10 stub column centred within the loading platens of the Tinius Olsen testing machine is shown in Figure 5.4. The instrumentation, (visible LVDTs and frame) and the bearing column are highlighted.

Figure 5.4 Stub Column Test Set-up

Characteristic load versus axial displacement and load versus lateral mid-height deflection graphs are illustrated in Figures 5.5, 5.6 and 5.7 for a SPS stub column, steel faceplate and elastomer core, respectively. Points 'a', 'b' and 'c' on the composite load versus deflection curves in Figure 5.5 correspond to the loads at which all four strain gauges reach the yield strain, strain hardening occurs, and the ultimate compressive resistance is reached, respectively. Points 'a' on Figures 5.6 and 5.7 indicate the compressive resistance for a single steel plate and the core.

(a) load versus axial displacement

(b) load versus lateral mid-height deflection

Figure 5.5 Typical Compressive Test Results, 300mm SPS Stub Column, IS3-0b

(c) load versus compressive strains

Figure 5.5 Typical Compressive Test Results Continued – 300mm SPS Stub Column, (IS3-0b)

(a) load versus axial displacement

Figure 5.6 Typical Compressive Test Results, 300mm Steel Faceplate

(b) load versus lateral mid-height deflection

Figure 5.6 Typical Compressive Test Results Continued, 300mm Steel Faceplate

(a) load versus axial displacement

Figure 5.7 Compressive Test Results, 300mm Elastomer Core

(b) load versus lateral mid-height deflection

Figure 5.7 Compressive Test Results Continued, 300mm Elastomer Core

The compressive resistance of the two stub columns, two steel plates and elastomer core with their corresponding failure modes are summarized in Table 5.3. The debonding of the steel faceplates from the elastomer core at an average axial strain of $22,154 \mu\epsilon$ and their subsequent local buckling from the stub column, shown in Figures 5.8(a) and (b) respectively, were the result of the interface stresses exceeding the bond capacity. The slight double curvature shape of the stub column in Figure 5.8(a) is the result of localized non-uniform instability where one plate started to delaminate prior to the other. Subsequent to delamination, the deformed shape of the compressed core is symmetric about mid-height.

The compression tests on the steel plates and core were conducted to demonstrate the stabilizing effect that the core provides to the steel faceplates. Both plates buckled at

an average compressive stress of $0.81F_y$, which is consistent with their classification; class 4.

The elastomer core compressed with a symmetric-about-mid-height, laterally deflected shape consistent with a fixed-ended column. After significant lateral deflections at mid-height of approximately 11.1 times that at ultimate, shown in Figure 5.8(c), the elastomer fractured through the thickness from the tension face towards the compression face as illustrated in Figure 5.8(d).

In summary, two critical observations of the stub column tests were:

- the elastomer core stabilizes the steel faceplates so that not only can they reach full yield, but they can exceed yield and do not buckle until extensive strain hardening has occurred.
- A direct comparison of the yield capacity of the stub column with yield strengths of the steel plates and the core contribution with the same axial deformation indicates that the core must be confined, and has a strength up to three times higher than that unconfined.

Table 5.3 Results Summary for Stub Column and Components

Specimen Designation	Axial Load (kN)		Failure Mode
	a	b	
IS3-0a	1415	1542	delamination and buckling of both steel plates
IS3-0b	1416	1538	delamination and buckling of both steel plates at an average axial strain of 22,154 $\mu\epsilon$
SPLATE1	531	-	buckling at $0.82F_y$
SPLATE2	511	-	buckling at $0.79F_y$
CORE	175	118	buckling followed by a fracture at lateral deflections equal to 11.1 times that at ultimate

(a) debonding – IS3-0b

(b) local buckling of faceplates – IS3-0b

(c) ultimate lateral deflection – CORE

(d) brittle fracture – CORE

Figure 5.8 Failure Modes of Stub Column and Components

5.4 Overall Member Stability

A typical in-plane compression test set-up for a 1500mm length is shown in Figure 5.9. Details (b), (c) and (d) illustrate the knife edge load assembly, LVDT frame and knife edge reaction assembly, respectively. Also highlighted in the figure are the line of action of the load, the lateral deflection of the member and the LVDT numbering scheme.

Figure 5.9 In-Plane Compression Set-up

Figure 5.10 Characteristic Load versus Lateral Mid-height Deflection Curves

The in-plane behaviour is best described by a series of characteristic load versus out-of-plane mid-height deflection curves for columns of varying slenderness ratios, such as those illustrated in Figure 5.10. Points 'a' and 'b' on each of the curves represent the ultimate compressive strength and the load at the termination of the test, respectively. For all of the compression members except for IS2-1, (500mm), and IS3-5, (2500mm), termination of the test coincided with a sudden debonding failure of one or both steel faceplates.

Typical load versus axial displacement, load versus lateral mid-height deflection and load versus end rotation curves, strain gauge locations and typical strain distributions through the core are given for each column slenderness tested in Figures 5.11 to 5.15. Strain Distributions are illustrated for each of the cross-sections for load levels associated

with points 'a' and 'b.' Each point on the distribution curves, (solid circle), is an average of two strain measurements taken across the section at that particular elevation. Positive and negative values represent tensile and compressive strains, respectively. Assuming that the axial strains in the core are linear, and given that the strains at the interface must be equal for fully bonded surfaces, the strain distributions through the thickness can be drawn as shown. The dotted lines, representing strain distributions through the steel thicknesses, are based on these assumptions. The yield strain ($1619 \mu\text{s}$) as determined from the tension coupon tests is shown on all relevant strain distribution graphs. Note, for load versus axial displacement and load versus lateral mid-height deflection graphs illustrating more than one curve, the load and deflection values inserted correspond to the title of the figure. The axial strain values for each nominal slenderness are listed for load points 'a' and 'b' in Table 5.4.

The slenderness ratio, ultimate compressive capacity and corresponding failure mode, and the load and delamination details associated with the termination of the test well beyond ultimate are summarized in Table 5.5 for each test. Note, only one series of photographs is shown for each nominal slenderness ratio.

(a) typical load versus axial displacement

(b) typical load versus lateral mid-height deflection

Figure 5.11 Compression Test Results - IS31-b (500mm)

(c) typical load versus end rotation

(d) strain gauge location

(e) mid-height strain distribution

Figure 5.11 Compression Test Results Continued – IS3-1b (500mm)

(d) strain gauge location

(e) quarter-height strain distribution (top)

(f) mid-height strain distribution

(g) quarter-height strain distribution (bot)

Figure 5.12 Compression Test Results Continued- IS4-2 (1000mm)

Figure 5.13 Typical Compression Test Results – IS4-3 (1500mm)

(d) strain gauge location

(e) quarter-height strain distribution (top)

(f) mid-height strain distribution

(g) quarter-height strain distribution (bot)

Figure 5.13 Compression Test Results Continued- IS4-3 (1500mm)

(a) load vs. axial displacement

(b) load vs. lateral mid-height deflection

(c) load vs. end rotation

Figure 5.14 Compression Test Results – IS2-4 (2000mm)

(d) strain gauge location

(e) quarter-height strain distribution (top)

(f) mid-height strain distribution

(g) quarter-height strain distribution (bot)

Figure 5.14 Compression Test Results Continued- IS2-4 (2000mm)

Figure 5.15 Compression Test Results – IS3-5 (2500mm)

(d) strain gauge location

(e) quarter-height strain distribution (top)

(f) mid-height strain distribution

(g) quarter-height strain distribution (bot)

Figure 5.15 Compression Test Results Continued- IS3-5 (2500mm)

Table 5.4 Axial Strains through Thickness of Typical Length Specimens

Test	position along length	Strains at Ultimate Compressive Capacity, (ms)						Strains at Point b - Termination of Test, (ms)					
		1	2	3	4	5	6	1	2	3	4	5	6
IS3-1b	0.75	-595.6	-883.3	-1073.1	-2022.6	-2212.5	-2084.3	6147.7	-4210.6	-7065.6	-21340.5	-24195.5	-39223.5
	0.50	-542.3	-724.7	-849.2	-1222.6	-1347.1	-1667.0	296.8	-623.7	-898.9	-1724.5	-1999.7	-1750.6
	0.25	-459.4	337.7	-169.7	-1691.7	-2199.1	-3010.8	3349.9	4536.8	-80.4	-13932.0	-18549.2	-22830.0
IS4-2	0.75	-421.4	-215.6	-306.6	-579.7	-670.7	-3301.1	734.4	619.2	-109.2	-2294.4	-3022.8	-9324.7
	0.50	-232.2	-310.7	-588.2	-1420.8	-1698.3	-1854.4	469.7	429.6	-36.0	-1432.8	-1898.4	-1753.3
	0.25	-9.7	-472.8	-768.1	-1654.1	-1949.5	-1993.3	3401.2	-46.0	-3578.4	-14175.8	-17708.2	-19613.4
IS2-4	0.75	-209.8	-406.8	-627.8	-1290.8	-1511.8	-1813.4	486.3	248.5	-76.1	-1049.8	-1225.6	-2588.9
	0.50	109.3	-141.5	-370.5	-1057.6	-1286.6	-2268.0	946.5	467.5	128.9	-887.0	-20422.1	-27982.4
	0.25	180.6	-184.7	-434.4	-1183.5	-1433.2	-1831.8	5552.9	1316.3	-3031.4	-16074.5	-703.8	-986.0
IS3-5	0.75	-28.3	-249.7	-441.7	-1017.9	-1209.9	-1600.4	790.1	424.9	142.8	-703.8	-49.9	-54.8
	0.50	141.5	-64.4	-299.5	-1004.8	-1239.9	-1509.9	22.4	-30.2	-35.1	-49.9	-54.8	-49.8
	0.25	475.4	95.8	-262.8	-1338.4	-1696.9	-3260.4	7312.4	3919.2	-1251.6	-16764.1	-21934.9	-31339.6
	0.25	220.6	-88.2	-310.6	-977.7	-1200.0	-1588.6	38.1	-1.0	8.8	38.1	47.9	-57.5

Note, positions cited along column length are taken as a fraction of the length relative to the bottom

Table 5.5 Compression Test Results

Spec. Desig.	L/r	Ultimate Compressive Resistance			Pt. b - Termination of Test		
		load, a (kN)	Failure Mode	Photo	load, b (kN)	Delaminated Plate	Photo
IS2-1	21.45	993	global buckling	-	913	-	-
IS3-1b	20.98	957	global buckling	5.16(a)	759	tension	5.16(b)
IS4-2	37.89	961	global buckling	5.17(a)	618	both	5.17(b)
IS4-3	54.76	810	global buckling	5.18(a)	363	both coupled with brittle core fracture	5.18(b)
IS2-6	56.31	800	global buckling	-	443	compression	-
IS4-7	53.25	833	global buckling	-	327	compression	-
IS2-4	71.18	638	global buckling	5.19(a)	241	compression	5.19(b)
IS3-5	87.93	528	global buckling	5.20(a)	135	-	5.20(b)

(a) $C_r = 957$ kN **(b) just prior to failure****Figure 5.16 Specimen IS3-1b (500mm)**

(a) $C_r = 961 \text{ kN}$

(b) just prior to failure

Figure 5.17 Specimen IS4-2 (1000mm)

(a) $C_r = 810 \text{ kN}$

(b) prior to failure

Figure 5.18 Specimen IS4-3 (1500mm)

(a) $C_r = 639$ kN

(b) just prior to failure

Figure 5.19 Specimen IS2-4 (2000mm)

(a) $C_r = 528$ kN

(b) prior to failure

Figure 5.20 Specimen IS3-5 (2500mm)

As anticipated with the series of slendernesses between approximately 20 and 88, all columns failed by global inelastic buckling, with a decreasing ultimate compressive capacity corresponding to an increasing slenderness. Based on strain measurements, it was observed, as expected, that the ultimate compressive strength coincided with the full yielding of the compression faceplate at mid-height. Test results corroborate Braun's conclusions, (Braun 1999), that compressive moduli of the core greater than a specified minimum of 375 MPa will prevent local buckling or failure modes associated with weak core laminates. Conditional tests conducted for similar nominal slendernesses gave essentially the same ultimate compressive strength and general behaviour.

5.5 Finite Element Analyses and Comparison

Objective:	To model the cross-sectional strength, buckling capacities and load-deflection relationships of experimentally tested columns of varying slenderness.
Analysis Type:	Nonlinear, static
Element Type:	Structural solid, SOLID45

5.5.1 General

The finite element program ANSYS, version 5.5, was used to model the in-plane compression test specimens to predict the compression strength of the CSL columns with varying slenderness ratios. Nodal and elemental solutions of the numerical analyses were compared to experimental strains, stresses and deflections to verify the finite element modelling technique. The following sections discuss the solution options used, material characterization of the hyperelastic core and the modeled geometry and boundary

conditions. The results of the analyses and their validity are then discussed, concluding with the proposed mathematical models for CSL columns (axially loaded members).

5.5.2 Analysis Assumptions and Modeling Notes

The Newton-Raphson approach was used for this solution since the compressive specimens are subjected to large deformations and there are significant shear deformations within the flexible core. The stress stiffening option was used in conjunction with the large strain effects to account for any additional in-plane stiffness resulting from out-of-plane elemental stresses.

5.5.3 Material Characterization

The multilinear stress-strain curve derived experimentally from the tension coupon tests and represented by points labeled on Figure 3.1 was used to model the steel.

Due to the discrepancies arising from the ninth-order Mooney-Rivlin approximation of the elastomer stress-strain characteristics within $\pm 20,000 \mu\text{s}$, and since the core is primarily in compression, the elastomer material was simply modeled with structural elements similar to those used for steel with a specified elastic modulus equal to that determined from the core-cast compression disc tests with a value of 378 MPa. Note, the test data indicated tension in the core only after ultimate and only when large lateral deformations had occurred. Hence, differences arising in assigning the tension modulus the same value as the compression modulus would have no effect on predictions of ultimate capacity and little or no effect on this portion of the analytical load-deflection curve.

5.5.4 Geometry, Boundary Conditions and Loading

Figure 5.21 illustrates the geometry and boundary conditions used to model the 300mm stub columns. The geometry of both stub column models were based on their respective measured cross-sectional dimensions and lengths. Load was applied by prescribing uniform displacements on the top load plate. Additional boundary conditions included restraint of the reaction plate in the x-, y- and z-directions, and restrained rotation of the top load plate.

Figure 5.21 Finite Element Geometry and Boundary Conditions for Stub Column Model, 300mm

Figure 5.22 illustrates the finite element model used for the 1500mm column with all corresponding boundary conditions. The geometry of each column model was based on measured cross-sectional dimensions and the measured unsupported length between the knife edge-knife edge plate contact pairs. The initial out-of-straightness for each column was generated by applying a uniform lateral pressure along the length of the column in the initial load step which produced a parabolic deflected shape with a maximum out-of-straightness at mid-height similar to that shown in Figure 5.23. The magnitude of this pressure can be adjusted to give an out-of-plane displacement less than or equal to this maximum out-of-straightness or to some weighted average value which may more closely approximate the effects of the initial out-of-straightness, as shown in Figure 5.23(b) and (c). Analyses were conducted of each column using both methods.

The pinned-ended columns were loaded by prescribing uniform displacements along an eccentrically loaded line of action on the top rigid plate (knife edge plate), as illustrated in Figure 5.24. Boundary conditions along this line allow displacements in the y-direction while fixing them in both the x- and z-directions. Reactions were taken out along the corresponding line for the bottom plate (knife edge plate) which was fixed against displacement in all three directions. The magnitude of the eccentricity of the applied load, 9.83mm, is based on the initial position of the knife edge to the sloped knife edge plate as described previously in Section 5.2. Note, the nodes used to generate the mesh for the core were aligned with this eccentricity to produce four and two elements through the core thickness on either side as shown in Figure 5.24.

Figure 5.22 Finite Element Geometry and Boundary Conditions for Compression Model, 1500mm

Figure 5.23 Initial Out-of-Straightness Approximation Methods

Figure 5.24 Finite Element Model for Eccentrically Applied Load

5.5.5 Discussion

The characteristic load versus axial displacement curve determined numerically for a stub column is illustrated along with the corresponding curve for specimen IS3-0b. The plateau identified on the curve is generally associated with a member's cross-sectional strength. The test-to-predicted ratios for models IS3-0a and IS3-0b are 1.06 and 1.04, respectively. Points 'b' on the curves indicate the start of strain hardening in the sections which is reflected by a constant increase in load capacity. Note, the numerical analyses were conducted to a maximum axial displacement of 10mm, and stopped as the particular model and solution strategy do not recognize shear stresses in excess of the allowable bond stress as a debonding failure. Figure 5.25 (b) and (c) give the axial stresses for the steel faceplates and core and the interface shear stresses, respectively. As anticipated and illustrated in the axial stress diagrams, the ultimate compressive capacity is reached when the maximum stress on the concave face reaches yield. Note, the concave and convex side convention is illustrated in Figure 5.25(a).

Figures 5.26 to 5.30 illustrate the analytical and experimental axial load versus lateral mid-height deflection curves, axial stresses in the steel faceplates and core, and the corresponding interface shear stresses for the series of pinned-ended columns which failed by overall member stability. In general, the characteristic behaviour is well-described by the solid element models used, as the mean test-to-predicted ratio for the test series was 1.033 with a coefficient of variation of 0.085. Variations in the ultimate compressive capacity and mid-height deflection are sensitive to initial out-of-straightnesses and small variations in the eccentricity of the line of action of the load, both of which are difficult to determine accurately, (for small values). To illustrate this

point, two additional analytical curves representing the initial eccentricity $\pm 2\text{mm}$ have been plotted for one column length, IS3-5, in Figure 5.30.

Recognizing this sensitivity led to a small analytical parametric study for the series of tests in which the eccentricity of the applied load was varied about the initial value determined by measurement. Also included in the parametric study were two variations in the interpretation of how to model the measured initial out-of-straightness analytically. The experimental values, predicted values and test-to-predicted ratios associated with the parametric study are given in Table 5.6. The test-to-predicted values cited are associated with $e_{\text{max}} = 9.83\text{mm}$, (as this was well founded by measurement), and an initial out-of-straightness equal to δ_{avg} , as the parabolic curves with this as its maximum amplitude gave the best fit curve to the series of initial out-of-straightness measurements. The predicted values associated with these conditions are highlighted in green in the table. Note, in general all the data is presented (unless otherwise noted), corresponding to the analyses with these conditions.

An additional set of interface shear stresses were plotted for model IS4-3 at the maximum lateral mid-height deflection of 75mm obtained in the analyses, and is shown in Figure 5.28(d) to illustrate the increase in interface shear stresses between the steel and elastomer. Specimen IS4-3 debonded at a lateral mid-height deflection of 84.25mm.

(a) load versus axial displacement

(b) axial stresses at point a – first yield across faceplates

(c) interface shear stresses at point a – first yield across faceplates

Figure 5.25 Analytical Results – IS3-0b (300mm Stub Column)

(a) load versus lateral mid-height deflection

(b) axial stresses at ultimate compressive capacity

Figure 5.26 Analytical Results – IS3-1b (500mm)

Figure 5.26 Analytical Results Continued— IS3-1b (500mm)

Figure 5.27 Analytical Results – IS4-2 (1000mm)

(b) axial stresses at ultimate compressive capacity

(c) interface shear stresses at ultimate compressive capacity

Figure 5.27 Analytical Results Continued— IS4-2 (1000mm)

(a) load versus lateral mid-height deflection

(b) axial stresses at ultimate compressive capacity

Figure 5.28 Analytical Results – IS4-3 (1500mm)

(c) interface shear stresses at ultimate compressive capacity

(d) interface shear stresses at maximum lateral mid-height deflection, 77mm

Figure 5.28 Analytical Results Continued— IS4-3 (1500mm)

(a) load versus lateral mid-height deflection

Figure 5.29 Analytical Results – IS2-4 (2000mm)

(b) axial stresses at ultimate compressive capacity

Figure 5.29 Analytical Results Continued – IS2-4 (2000mm)

(c) interface shear stresses at ultimate compressive capacity

Figure 5.29 Analytical Results Continued – IS2-4 (2000mm)

(a) load versus mid-height deflection

Figure 5.30 Analytical Results – IS3-5 (2500mm)

(b) axial stresses at ultimate compressive capacity

Figure 5.30 Analytical Results Continued – IS3-5 (2500mm)

(c) interface shear stresses at ultimate compressive capacity

Figure 5.30 Analytical Results Continued – IS3-5 (2500mm)

Table 5.6 Analytically Determined Ultimate Compressive Capacities and Test-to-Predicted Ratios

		IS2-1 (500mm)	IS31-b (500mm)	IS4-2 (1000mm)	IS4-3 (1500mm)	IS2-6 (1500mm)
Analytical Results	Experimental	993	956	961	810	800
	initial o.o.s. = δ_{max}					
	$e_{max}=9.83\text{mm}$	850.0	1005.0	845.5	751.3	688.0
	$e_{min}=\text{varies}$	879.7	1013.5	857.2	764.3	694.2
	$e=e_{tmax}-4\text{mm}$	967.7	1123.0	946.9	835.3	760.1
	$e=e_{tmax}-2\text{mm}$	918.1	1060.9	904.8	789.4	723.4
	$e=e_{tmax}+2\text{mm}$	830.2	955.5	816.1	716.0	658.2
	$e=e_{tmax}+4\text{mm}$	792.8	911.5	768.8	685.0	631.6
	initial o.o.s. = δ_{avg} $\delta_{avg} = (\delta_1 + \delta_2 + \dots \delta_n)/(n+1)$	912.6	982.6	870.8	770.4	729.4

		IS4-7 (1500mm)	IS2-4 (2000mm)	IS3-5 (2500mm)	average t/p	COV
Analytical Results	Experimental	833	638	528		
	initial o.o.s. = δ_{max}					
	$e_{max}=9.83\text{mm}$	836.0	635.9	560.2	1.055	0.089
	$e_{min}=\text{varies}$	848.2	647.8	572.7	1.037	0.087
	$e=e_{tmax}-4\text{mm}$	945.2	700.1	612.9	0.946	0.084
	$e=e_{tmax}-2\text{mm}$	886.1	665.5	584.4	0.997	0.082
	$e=e_{tmax}+2\text{mm}$	791.8	609.6	539.2	1.100	0.084
	$e=e_{tmax}+4\text{mm}$	738.8	585.5	520.5	1.154	0.085
	initial o.o.s. = δ_{avg} $\delta_{avg} = (\delta_1 + \delta_2 + \dots \delta_n)/(n+1)$	812.2	658.4	552.7	1.033	0.085

note: all loads are expressed in kN

5.6 Limit States Design

The development of design equations requires an understanding of the behaviour under the specific load action. For compression, these limit states are associated with the cross-sectional strength, elastic and inelastic global buckling and local buckling, fatigue and serviceability requirements as illustrated in Figure 5.31.

Figure 5.31 Failure Modes and Limit States for CSL Columns (after Braun, 1999)

Local buckling as a probable failure mode is precluded by specifying a minimum core stiffness which will provide the required stability. Assuming the steel is fully yielded at the cross-sectional strength capacity, then axial strains are approximately 1600 μs .

Corresponding stress in the core is equal to 0.6 MPa with a resulting load carrying capacity of 6 kN. The total contribution of the core would be less than approximately 0.5%, hence prediction of the cross-sectional strength may be adequately described using Equation 5.2 replicated from § 13.3.1 of CAN/CSA-S16.1-94;

$$C_r = \Phi A F_y, \quad (5.2)$$

where, C_r = axial compressive resistance, kN
 Φ = resistance factor
 A = area of steel cross section, mm²
 F_y = yield strength of the steel faceplates, MPa

Φ was taken as 1.0 since all material and geometric properties were based on measurements of each test specimen.

For columns that fail by either inelastic or elastic buckling, it is anticipated that the core contribution to compressive resistance is less than or equal to that for cross-sectional strength. The ultimate compressive capacity can therefore be adequately described by equations given in CAN/CSA-S16.1-94 with slenderness defined by Equation 5.1.

$$C_r = \Phi A F_y (1 + \lambda^{2n})^{-\frac{1}{n}} \quad (5.3)$$

where, C_r = axial compressive resistance, kN
 Φ = resistance factor
 A = area of steel cross section, mm²
 F_y = yield strength of the steel faceplates, MPa
 n = compressive resistance parameter, 1.34

$$\lambda = \frac{KL}{r} \sqrt{\frac{F_r}{\pi^2 E}} \quad (5.4)$$

where, λ = nondimensional slenderness parameter
 K = effective length factor
 L/r = slenderness ratio
 E = modulus of elasticity of steel faceplates, MPa

Note, the effective length factor, K , is equal to one for pinned-pinned columns and the compressive resistance factor, ϕ , should be taken as 1.34 since the steel faceplates in the CSL columns were cold-formed and non-stress relieved.

Since the columns were loaded through a constant eccentricity of 9.83mm, (single curvature), then the compressive resistance should be based on strength formulations associated with the overall member stability of a beam-column, as replicated in Equations 5.5 and 5.6 from §13.8.1 of CAN/CSA-S16.1-94;

$$\frac{C_f}{C_r} + \frac{U_{1x} M_{fx}}{M_r} \leq 1 \quad (5.5)$$

where, C_f = applied axial load, kN
 C_r = compressive resistance, kN
 M_{fx} = applied moment, kNm
 M_r = moment resistance, kNm
 U_{1x} = magnification factor for applied moment described below

$$U_1 = \left[\frac{\omega_1}{1 - \frac{C_f}{C_e}} \right] \quad (5.6)$$

where, ω_1 = uniform bending effect coefficient, 0.6
 C_e = Euler buckling capacity of steel faceplates

Note, all member resistances should be based on the steel sections alone. In accordance with §13.6 and recognizing there are no concentrated end moments applied to the column, ω_1 should be taken as 0.6. M_{fx} , the factored moment about the principal axis, is equal to the eccentricity multiplied by the applied compressive force, C_f . The eccentricity is taken as the net value of the initial eccentricity of 9.83mm and the maximum out-of-straightness which may increase or decrease the eccentricity depending on the relative orientation of the column within the test set-up.

Based on the assumptions described, measured geometric and material properties, measured imperfections and the appropriate resistance formulation presented, the compressive resistances were calculated for each column and are listed in Table 5.7. Also listed are the corresponding test-values and the test-to-predicted ratios. The mean and coefficient of variation for the test-to-predicted values for this test series were 1.01 and 0.048, respectively. The equations given in §16.1 based on the steel section alone adequately describe the compressive resistance of the CSL beam columns.

The compressive resistance of the CSL columns, expressed non-dimensionally as a function of the cross-sectional strength, is given for those assuming no initial out-of-straightness or eccentricity and those assuming values equal to those measured experimentally are illustrated in Figure 5.32. Also shown are the experimental values. This figure clearly illustrates the significant effect of the initial eccentricity, (9.83mm is relatively large compared to cross-sectional dimensions), on the compressive resistance.

Table 5.7 Test-to-Predicted Compressive Strengths

Specimen Designation	Compressive Resistance (kN)		
	test, t	predicted, p	t/p
IS3-0a	1415	1293.9	1.09
IS3-0b	1416	1293.9	1.09
IS2-1	993	1013.3	0.98
IS3-1b	957	1056.4	0.91
IS4-2	961	946.4	1.02
IS4-3	810	800.8	1.01
IS2-6	800	770.03	1.04
IS4-7	833	837.47	0.99
IS2-4	638	646.6	0.99
IS3-5	528	533.6	0.99

Figure 5.32 C_r/C_y versus Slenderness Ratio for SPS 10-50-10 Columns

Given the accuracy in which the solid finite element models predict the in-plane behaviour of the CSL members subjected to compression, the best predictor of strength and stiffness for more complex structures constructed from a series of plates, like ship hulls, would be the use of models constructed of solid finite elements such as those described and verified in Section 5.5.

Chapter 6

Summary, Conclusions, Recommendations and Future Work

6.1 Summary

Product oil tankers will continue to have accidents. While legislation and the implementation of improved operating procedures and navigational technology reduce the frequency of accidental or extreme load events that result from human and mechanical error, these will not eliminate the occurrence of accidents altogether. Impact resistant structures must be developed to anticipate these load events and to minimize the negative environmental consequences associated with them. These structures must provide equivalent or superior strength and stiffness to existing structures for normal operating loads over the anticipated service life.

CSL plate construction, consisting of two steel faceplates fully bonded to a structural polyurethane elastomer core, has been developed to provide impact resistant maritime and civil structures. The resilient, tough, energy absorptive core also acts as a crack arrester and prevents (inhibits) cracks within the steel (resulting from fatigue or penetration) from propagating through the sandwich into the inner plate of the inner hull (cargo liner), reducing the possibility of oil outflow. In addition, the engineered core material also provides effective acoustical and thermal insulation and improved dampening characteristics. CSL construction greatly simplifies structures which are traditionally built with stiffened steel plates and advantageously eliminates numerous

fatigue and corrosion prone details. This simplification also results in better coatings and eases maintenance.

To fully integrate CSL construction into the maritime and civil industry, design equations must be developed for the probable limit states associated with fundamental behaviour in flexure and compression. This requires an understanding of this fundamental behaviour and a parallel set of limit states that describe this behaviour for CSL plates, (material and geometric specifications should be provided which preclude local failures and allow the overall member stability to govern). These limit states and specifications can then be used to develop a test programme which would generate experimental data to verify the limit states and analytical modelling techniques. Rational design equations based on experimental and analytical evidence could then be developed. Ultimately, these design equations would be scrutinized and verified by regulatory bodies and incorporated into design standards, where their adoption and public education would complete the CSL's integration into the industry. As part of the verification process, in-field tests and trials may be conducted to provide historical performance records for non-laboratory conditions.

This thesis concentrates on the production of experimental data, the verification of finite element modelling techniques, the development of design equations based on identified limit states and the verification of these equations. Where necessary, data has also been generated (bond, fatigue) to give empirical rules where rational mathematical expressions cannot describe the capacity.

All material tests on the elastomer core and steel required for the analyses were conducted in accordance with appropriate ASTM standards. Forty-seven bond tests were

conducted in both direct tension and shear for target temperatures ranging from -35°C to 100°C to determine the bond strength between the steel and the elastomer core.

To characterize the fundamental behaviour and obtain the ultimate capacity of CSL plates subjected to flexural or axial loads, six beams and ten columns, (with varying slenderness), with similar 200mm wide, SPS 10-50-10 cross-sections were tested statically. Each of these was modeled analytically using solid finite elements, measured material and geometric properties, appropriate boundary conditions and non-linear solution techniques and compared with corresponding test data. Further analyses were conducted to understand the influence of initial out-of-straightness assumptions and eccentricities on in-plane compression behaviour and strength.

In addition, four SPS 10-50-10 flexural specimens were subjected to cyclic loading to determine the fatigue resistance of the steel-elastomer interface bond in terms of maximum allowable bond strength. One of the four specimens tested included a typical steel fabrication detail.

6.2 Conclusions

The following conclusions can be made regarding this research;

- based on material characterization tests, the engineered elastomer EC-609-002/18 meets the design requirements specified for maritime structures, has a tensile-to-compressive modular ratio (E_t/E_c) equal to 1.7, and has material properties dependent on cast and curing conditions,

- shear bond tests give the most appropriate characterization of bond stress. Tests for bond strength on isolated samples are significantly influenced by Poisson's effect and are not representative of continuous samples,
- shear bond strength values decrease with increasing temperature with a minimum allowable stress of 2.5 MPa measured at 100 °C,
- for all large-scale tests, a compressive core modulus of 378 MPa was sufficient to stabilize the steel faceplates which were subjected to compressive strains of 20,000 to 40,000 μs , and prevent all local buckling failure modes associated with laminate construction, (face wrinkling, debonding and local buckling),
- for isolated samples with a core moduli associated with the elastomer formulation used, the ratio of experimental flexural rigidity to that of the steel sections alone is 0.54,
- the application of solid elements to model the determined flexural behaviour, based on a ninth-order curve-fit to describe the elastomer core stress-strain properties, gave an average test-to-predicted ratio and coefficient of variation for flexural stiffness and plastic moment capacity of 0.98 and 0.021, and 0.96 and 0.050, respectively,
- the solid element modelling techniques used to predict the in-plane compression behaviour and overall member stability, based on a linear compressive modulus of elasticity to describe the elastomer core stress-strain properties, gave an average test-to-predicted ratio and coefficient of variation for the ultimate compressive capacity of 1.036 and 0.053,

- flexural strength of CSL members is equal to the plastic moment capacity of the steel sections alone, with a mean test-to-predicted ratio and coefficient of variation of 0.98 and 0.019, respectively,
- overall member strength of CSL beam-columns can be described by the corresponding limit state design equation in CAN/CSA-S16.1-94, with a mean test-to-predicted ratio and coefficient of variation of 1.01 and 0.048, respectively for members with varying slenderness within the approximate range of 20 to 90, and
- the steel-elastomer interface bond stress does not govern for fatigue loading, (as determined from a series of fatigue tests in which the applied bond stress range never exceeded 0.45 of the critical bond strength).

6.3 Recommendations and Future Work

Obviously, the introduction of a new construction technology into broad applications such as maritime and civil structures will require extensive experimental and analyses work that are beyond the fundamental behaviour for the load actions described in this thesis and may include; tests associated with characterizing performance when subjected to fire load; impact resistance; tests to characterize vibration, thermal and acoustic properties, common load combinations for CSL plates (transverse bulkheads with large transverse shear) and torsion. Note, findings of these tests may be augmented and supported by field trials of sections placed in service.

Both bond strength and fatigue life are empirically based and require a substantial number of tests to provide a statistical sample that represents the full range of behaviour and conditions. As a result, more tests are required for bond strength to include;

- varying surface preparations, (other primers, bonding agents, surface roughness),
- varying faceplate materials, (aluminum, stainless steel, galvanized steel), and
- a more comprehensive temperature range corresponding to the anticipated operating loads in a temperature control chamber to provide constant ambient temperature conditions during the test,

and for fatigue strength to encompass a broader range of shear bond stress to describe a complete S-N curve for CSL members.

References

- Allen, H.G. (1969). *Analysis and Design of Sturctural Sandwich Panels*. Pergamon Press.
- American Society for Testing Materials. ASTM (1984). *Standard Test Methods for Rubber Properties in Compression, Designation D575-83*. Annual Book of ASTM Standards, Vol. 09.01, ASTM, Philadelphia, Pennsylvania, pp. 144-147.
- American Society for Testing Materials. ASTM (1984). *Standard Test Methods for Rubber Properties in Tension, Designation D412-83*. Annual Book of ASTM Standards, Vol. 09.01, ASTM, Philadelphia, Pennsylvania, pp. 56-69.
- ANSYS. (1999). *Release 5.5, ANSYS Analysis Guides*. ANSYS Inc., Houston, Pennsylvania, USA.
- ANSYS. (1999). *Release 5.5, ANSYS Elements Manual*. ANSYS Inc., Houston, Pennsylvania, USA.
- ANSYS. (1999). *Release 5.5, ANSYS Theory Manual*. ANSYS Inc., Houston, Pennsylvania, USA.
- BASF. (1997). *BASF Polyurethane – The Better Solution*. BASF
- Bennett, M.R.L. (1998). *Development and Behaviour of Unidirectional Double Hull Sandwich Plate System: Experimental Investigation*. Master's Thesis, Carleton University, Ottawa, Canada.
- Braun, D. (1999). *Behaviour of Composite Structure Laminate Plates*. Master's Thesis, Carleton University, Ottawa, Canada.
- Ferro, A. (1998). *Development and Behaviour of Unidirectional Double Hull Sandwich Plate System: Analytical Investigation*. Master's Thesis, Carleton University, Ottawa, Canada.
- Phillips, L.N. (1989). *Design with Advanced Composite Materials*. The Design Council. London, England. Springer-Verlag, pp. 243-300.
- Plantema, F.J. (1966). *Sandwich Construction*, John Wiley & Sons Inc., U.S.A.